## STATSHIELD® METAL-IN SERIES

## **Specifications:**

**Standard Document** ANSI/ESD S541 (ANSI/ESD S20.20)

ANSI/ESD S11.4

**Electrical Properties** 

**Typical Values** 

Surface Resistance:  $1 \times 10^4 \text{ to} < 1 \times 10^{11} \text{ ohms}$ Outer Surface  $1 \times 10^4 \text{ to} < 1 \times 10^{11} \text{ ohms}$ Inner Surface

Discharge Shielding <20 nJ

Charge Generation Teflon: 0.09 nC/sq. in. Quartz: 0.01 nC/sq. in.

Capacitance Probe (to dissipate 1 KV) <30 volts Meets Requirements of:

**ESD Protective Packaging** Level 3 Technical Requirements

Test Procedures/Method

ANSI/ESD STM11.11 ANSI/ESD STM11.11 ANSI/ESD STM11.31, EIA 541

Modified Incline Plane Modified Incline Plane

ANSI/EIA-541/Appendix E, 1kV Discharge

**Physical Properties** 

Date & Lot Code

Weld

Soft Fold Bottom

Film Thickness Nominal 3.0 mil (0.07mm) ±10%

Width (Inside Dimensions) Nominal -0" / + 0.250"

Nominal ± 0.125"; Offset 0 to 1/4" Length (Inside Dimensions)

**Light Transmission** >40% (Tobias) Heat Seal >10 lbs/in Tensile Strength 4600 PSI, 32 MPa

Puncture Resistance >10 lbs Non-corrosive Pass Silicone Not detected

Marking Adhesion Pass MIL-STD-3010, 1003

**ASTM D-1003** 375°F, 1/2 sec 60 psi

ASTM D882 MIL-STD-3010, 2065 MIL-STD-3010, M3005

**FTIR** 

IPC-TM-650 2.4.1

#### ANSI/ESD S541 Section 6.2 Outside an EPA

"Transportation of sensitive products outside of an EPA shall require packaging that provides:

- 1. Low charge generation
- 2. Dissipative or conductive materials for intimate contact
- 3. A structure that provides electrostatic discharge shielding."

#### RoHS, REACH and Conflict Minerals Statement

See the Desco Industries RoHS, REACH, and Conflict Minerals Statement:

https://desco.descoindustries.com/pdf/Regulatory Statements Desco Statshield Bags.pdf

See the Desco Limited Warranty:

Desco.DescoIndustries.com/Limited-Warranty.aspx

### Outer Polvester Laver Aluminum Shielding Layer Low Charging Static Dissipative Proprietary Inner Polvethylene Laver

Low Charging Static Dissipative Proprietary

Opening

Length (L)

Weld

Seal

### **Mixed Unsortable Plastic Scrap**

Mixed unsortable plastic scrap shall contain assorted plastics of multiple grades that are co-extruded, bonded or laminated together which are unsortable into individual grades

Desco's bags are recyclable

Statshield® bags are packaged 100 per package in an oversized shielding bag. See Shielding Bag Storage at TB-7057.

Overall Width (OW)

**STATSHIELD®** 

Metal In Construction

Discharge Shielding

RoHS

Static Shielding Bag

ATTENTION: Contents may be Static Sensitive

DescoIndustries.com

Made in America

Width (W)

Side Weld Seals 3/8 in. (±0.10)

\*\* Bags are printed (hot stamped or thermal transferred) with an ESD protective symbol and a lot code for traceability. \*\*

> Statshield® and Statfree® are Registered Trademarks of Desco Industries Inc. See Bag Selection Chart Click HERE.



Made in the United States of America

Specifications and procedures subject to change without notice.

# STATSHIELD® BAG, SHIELDING, METAL-IN, 3.0 MIL (0.07mm)



DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407 PHONE (781) 821-8370

**DRAWING** NUMBER 13405

DATE: September 2021

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Antistatic Control Products category:

Click to view products by Desco manufacturer:

Other Similar products are found below:

13020 13490 13870 13879 13881 13883 13882 14404 2202SP 3039 37061 42470 09060 09857 42516 37059 04563 17252 19691 19695 09037 09826 09813 66070 100816 68101 68103 98132 73741 13868 13485 13457 13245 13468 13420 13332 13205 13135 91070 8031 8523 66085 40931 37081 13080 13215 13806 73749 010-0225 17260