



Blue, Grey, Black

Specifications

Standard Document

ANSI/ESD S20.20

Electrical Properties

Charge Decay:
Rtt Resistance:
Rtg Resistance:

Typical Values

<0.01sec.
 1×10^6 to $< 1 \times 10^9$ ohms
 1×10^6 to $< 1 \times 10^9$ ohms

Physical Properties

Construction: Heat fused vinyl composite
Thickness: 0.125" (3.2mm)
Color:* Blue, Grey, Black
Texture:* Light Embossing
Hardness: 45 Shore "A"
Tensile Strength: >300 psi
Tear Strength: >80 lbs/inch
Elongation: >80%
Abrasion Resistance: >750 cycles

Meets Requirements of:

Worksurface

Test Procedures/Method

FTMS 101C, M 4046
ANSI/ESD S4.1 and ESD TR53
ANSI/ESD S4.1 and ESD TR53

Other Properties

Chemical Resistance: Resistance to degradation by inorganic acids, organic acids, reducing agents, aliphatic hydrocarbons, mineral oil, aldehydes, and amines

Tolerances:

Width ± 0.250 "
Length ± 0.250 " every 1 linear foot of running material.
Thickness $\pm 10\%$

Matting materials have a tendency to shrink slightly when first unrolled. In applications where length is critical, allow the material to relax for at least 4 hours before cutting to size. Always trim with a sharp knife or razor blade.

*Color and texture may vary between lots and mills.

For product listings, [Click Here](#).

Grounding & Cleaning

If the material is used on top of an already properly grounded surface, [grounding hardware](#) may not be necessary. Where no properly grounded surface is available, [grounding hardware](#) is required to provide a path-to-ground. Rtg compliance verification measurements must be made as outlined in ESD TR53 with a [surface resistance meter](#).

See Tech Bulletin [TB-7000](#) for Reztore® Surface & Mat Cleaner Application Instructions.

Limited Lifetime Warranty:

Desco warrants for one year that Statfree® matting products will be free of defects in materials and workmanship and will guarantee dissipative/conductive mat properties for the life of the mat. Damage to matting caused by misuse of any kind, including using inappropriate cleaners is not covered by [Desco Limited Warranty](#).

RoHS 3, REACH, and Conflict Minerals Statement

See the Desco Industries RoHS 3, REACH, and Conflict Minerals Statement:

<http://www.descoindustries.com/ROHS.aspx>

See the Desco Limited Warranty:

<http://desco.descoindustries.com/Limited-Warranty.aspx>

See the Desco Disclaimer:

<http://desco.descoindustries.com/Disclaimer.aspx>

Specifications and procedures subject to change without notice.

STATFREE® Z2, VINYL, DISSIPATIVE, 3-LAYER, 0.125" (3.2MM)

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com
PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407
PHONE (781) 821-8370

STATFREE® Z2
DRAWING PM-112

DATE:
March
2021



Made in the
United States of America

DESCO

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [Antistatic Control Products](#) category:

Click to view products by [Desco](#) manufacturer:

Other Similar products are found below :

[13020](#) [13490](#) [13870](#) [13879](#) [13881](#) [13883](#) [13882](#) [14404](#) [2202SP](#) [3039](#) [37061](#) [42470](#) [09060](#) [09857](#) [42516](#) [37059](#) [04563](#) [17252](#) [19691](#)
[19695](#) [09037](#) [09826](#) [09813](#) [66070](#) [100816](#) [68101](#) [68103](#) [98132](#) [73741](#) [13868](#) [13485](#) [13457](#) [13245](#) [13468](#) [13420](#) [13332](#) [13205](#) [13135](#)
[91070](#) [8031](#) [8523](#) [66085](#) [40931](#) [37081](#) [13080](#) [13215](#) [13806](#) [73749](#) [010-0225](#) [17260](#)