

2-Layer

Grounding & Cleaning

If the material is used on top of an already properly grounded surface, grounding hardware may not be necessary. Where no properly grounded surface is available, grounding hardware is required to provide a path-to-ground. Rtg compliance verification measurements must be made as outlined in ESD TR53 with a surface resistance meter.

See Tech Bulletin TB-7000 for Reztore® Surface & Mat Cleaner Application Instructions.

Limited Lifetime Warranty:

Desco warrants for one year that Statfree® matting products will be free of defects in materials and workmanship and will quarantee dissipative/ conductive mat properties for the life of the mat. Damage to matting caused by misuse of any kind, including using inappropriate cleaners is not covered by Desco Limited Warranty.

RoHS 3, REACH, and Conflict Minerals Statement See the Desco Industries RoHS 3, REACH, and Conflict Minerals

http://www.descoindustries.com/ROHS3.aspx

See the Desco Limited Warranty:

http://desco.descoindustries.com/Limited-Warranty.aspx

See the Desco Disclaimer:

http://desco.descoindustries.com/Disclaimer.aspx

STATFREE T2™ DISSIPATIVE RUBBER



Specifications

Standard Document Meets Requirements of:

ANSI/FSD S20 20 Worksurface

Electrical Properties Typical Values Test Procedures/Method Dissipative Surface Laver

Rtt Resistance: 1×10^6 to $< 1 \times 10^9$ ohms ANSI/ESD S4.1 and ESD TR53 $1 \times 10^6 \text{ to} < 1 \times 10^9 \text{ ohms}$ Rta Resistance: ANSI/ESD S4.1 and ESD TR53

Ground Plane Layer

ANSI/ESD S4.1 and ESD TR53 Rtt Resistance: $< 1 \times 10^{6} \text{ ohms}$

Physical Properties

Construction: Dual-layer rubber material¹

Thickness: 0.060" (1.5mm)

Color:2 Blue (Top), Dark Blue (Top), Dark Grey (Top), Green (Top), Black (Bottom)

Embossing:2 Slight Texture

0.43 lbs./sq. ft. (0.2g/cm2) Weiaht:

65 ± 5 Shore "A". per ASTM-D2240 Hardness:

Other Properties

Heat Resistance Does not melt or burn when coming into contact with hot solder and soldering irons. Chemical Resistance: Resistance to degradation by inorganic acids, organic acids, reducing agents, aliphatic

hydrocarbons, mineral oil, aldehydes, and amines.

¹Rubber material isvulcanized and may contain sulfur. ²Color and texture may vary between lots and mills.

Tolerances:

Width ± 0.250"

Length ± 0.250" every 1 linear foot of running material.

Thickness ±10%

Matting materials have a tendency to shrink slightly when first unrolled. In applications where length is critical, allow the material to condition for at least 4 hours before cutting to size. Always using care trim with a sharp knife or razor blade.

For product listings, Click Here

Made in the United States of America

**Tray liners have 3/4" radius corners and do not include grounding hardware.

STATFREE T2™ DISSIPATIVE, RUBBER, 2-LAYER, 0.060" (1.5mm)

Specifications and procedures subject to change without notice.



DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407 PHONE (781) 821-8370

MATERIAL STATFREE T2™ **DRAWING PM-104**

DATE: May 2020

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Antistatic Control Products category:

Click to view products by Desco manufacturer:

Other Similar products are found below:

13020 13490 13870 13879 13881 13883 13882 14404 2202SP 3039 37061 42470 09060 09857 42516 37059 04563 17252 19691 19695 09037 09826 09813 66070 100816 68101 68103 98132 73741 13868 13485 13457 13245 13468 13420 13332 13205 13135 91070 8031 8523 66085 40931 37081 13080 13215 13806 73749 010-0225 17260