





Description

Desco's Disposable ESD Mat meets ANSI/ESD S20.20 worksurface required limit and recommendation of ANSI/ESD S4.1 for contact with ESD susceptible items. The material is intended to be a sacrificial material to protect a more expensive worksurfaces from damage caused by conformal coating, solder fluxes, or other contaminates. The material is made from a 100% recyclable dissipative impregnated worksurface material and has an internal conductive layer so that it does not generate a static charge and will control the discharge rate from all conductors (including ESD susceptible items) that are placed on the surface. The mat may be grounded by placing it onto an already grounded ESD worksurface.

PROPERTIES
Surface Resistance
High-Voltage Discharge Resistance
Static Shielding
Corrosivity
Antistat Transfer
Sloughing Test

Recyclability Biodegradability

TYPICAL VALUES

10E6 - 10E8 ohms
Failure rate 0/5 (no oxide damage in five consecutive tests)
99.9% attenuation at 10kV; 99.6% attenuation at 30kV

Contains 1-3 ppm reducible sulfur

No transfer
Negligible surface damage at 10 cycles and <5% of surface damage at 200 cycles in Taber Abrasion Test.
No conductive particles abrased from surface
Complete recyclability of package

Biodegradation in or on moist soil

TEST PROCEDURES/METHOD

ANSI/ESD S4.1

Rockwell International Test Report of December 20, 1991 EIA 541, appendix E, capacitive probe test FED-STD-101, Method 3005 for reducible sulfur Rockwell International Test Report of January 8, 1992 ASTM D4060 at 70 rpm with CS-17 abrasive-coated wheels and 1000 grams load Rockwell International Test Report of January 8, 1992

Rockwell International Test Report of January 8, 1992

"Resistance-to-groundable point 1 x 10E6 to 1 x 10E9 ohms. Resistance from point-to-point greater than 1 megohm. These guidelines represent a range of resistance that has generally been proven to provide protection in the manufacturing environment." [ANSI/ESD S4.1 section 8. Resistance Guidelines]

"[Rtg is] The most important functional consideration for worksurfaces. This establishes the resistance of the primary path to ground for items, placed on the surface. When worksurface materials are being selected, consideration should be given to possible Charged Device Model (CDM) damage to ESD sensitive products. If CDM damage is a concern then setting a lower resistance limit for the worksurface should be considered. Typically, the lower limit for these types of worksurfaces is 1 X10E6 ohms." [ESD Handbook TR20.20 section 5.3.1.7 Electrical Considerations]

Available Sizes

Item	Size - L" x W"
<u>82100</u>	11 x 14
<u>82101</u>	14 x 22

Custom sizes available. Ask for quote.

RoHS Compliance Statement

None of the following materials are intentionally added in manufacturing this product: lead, mercury, cadmium, hexavalent chromium, polybrominated biphenyls (PBB) or polybrominated diphenyl ethers (PBDE) as outlined in the Directive 2002/95/EC Article 4.1. See Desco Inc. letter on-line at Desco.com.

Unless otherwise noted, tolerance is ±10%

Specifications and procedures subject to change without notice.

Disposable ESD Mats

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: <u>Desco.com</u> PHONE (909) 627-8178 FAX (909) 627-7449

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407 PHONE (781) 821-8370 FAX (781) 575-0172

DRAWING NUMBER 82100 DATE: March 2011



X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Antistatic Control Products category:

Click to view products by Desco manufacturer:

Other Similar products are found below:

13020 13490 13870 13879 13881 13883 13882 14404 2202SP 3039 37061 42470 09060 09857 42516 37059 04563 17252 19691 19695 09037 09826 09813 66070 100816 68101 68103 98132 73741 13868 13485 13457 13245 13468 13420 13332 13205 13135 91070 8031 8523 66085 40931 37081 13080 13215 13806 73749 010-0225 17260