


Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 4061266011 Printed: 2013-07-03









Part Number: 4061266011

Frequency Range: Low Permeability, 61(ui=125) material

Description: 61 SOLID ROD

Application: Inductive Components

Where Used: Open Magnetic Circuit

Part Type: Rods


Mechanical Specifications

Weight: 5.800 (g)

Part Type Information

Pressed Fair-Rite rods are used extensively in high-energy storage designs. These rods can also be used for inductive components that require temperature stability or have to accommodate large dc bias requirements.

- -The 'A' dimension can be centerless ground to tighter tolerances.
- -Figure 2 rods have a 0.6 mm (.024") maximum chamfer on the end faces.
- -For frequency tuned rod designs see section Antenna/RFID Rods.
- -For any rod requirement not listed here, feel free to contact our customer service group for availability and pricing.



Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 4061266011 Printed: 2013-07-03









Mechanical Specifications

Dim	mm	mm	nominal	inch
		tol	inch	misc.
Α	6.35	±0.25	0.250	
В	-	-	-	
С	38.10	±0.75	1.500	-
D	ı	ı	-	-
Е	ı	ı	-	-
F	ı	ı	-	-
G	ı	ı	-	-
Н			-	-
J			-	-
K	-	-	-	-

Flectrical Specifications

Liberiou Openiourone			
Typical Impedance (Ω)			
Electrical Properties			

Land Patterns

V	W	Х	Υ	Z
-	-	-		-

Winding Information

Turns	Wire	1st Wire	2nd Wire
Tested	Size	Length	Length
-	-	-	-

Reel Information

Tape Width	Pitch	Parts 7 "	Parts 13 "	Parts 14 "
mm	mm	Reel	Reel	Reel
-	-	-	-	-

Package Size

Pkg Size
-
(-)

Connector Plate

# Holes	# Rows
-	-

Legend

+ Test frequency

Preferred parts, the suggested choice for new designs, have shorter lead times and are more readily available.

The column H(Oe) gives for each bead the calculated dc bias field in oersted for 1 turn and 1 ampere direct current. The actual dc H field in the application is this value of H times the actual NI (ampere-turn) product. For the effect of the dc bias on the impedance of the bead material, see figures 18-23 in the application note How to choose Ferrite Components for EMI Suppression.

A 1/2 turn is defined as a single pass through a hole.

_ I/A - Core Constant

Ae: Effective Cross-Sectional Area

 A_{l} - Inductance Factor $\left(\frac{L}{N^{2}}\right)$

I e: Effective Path Length

Ve: Effective Core Volume

NI - Value of dc Ampere-turns

N/AWG - Number of Turns/Wire Size for Test Coil



Fair-Rite Product's Catalog Part Data Sheet, 4061266011 Printed: 2013-07-03







Ferrite Material Constants

0.25 cal/g/°C Specific Heat 3.5 - 4.5 mW/cm - °C Thermal Conductivity Coefficient of Linear Expansion 8 - 10x10-6/°C 4.9 kgf/mm² Tensile Strength Compressive Strength 42 kgf/mm² 15x103 kgf/mm2 Young's Modulus Hardness (Knoop)..... 650 Specific Gravity $\approx 4.7 \text{ g/cm}^3$ The above quoted properties are typical for Fair-Rite MnZn and NiZn ferrites.

See next page for further material specifications.

Fair-Rite Products Corp. Your Signal Solution® Ferrite Components for the Electronics Industry

Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

A high frequency NiZn ferrite developed for a range of inductive applications up to 25 MHz. This material is also used in EMI applications for suppression of noise frequencies above 200 MHz.

EMI suppression beads, beads on leads, SM beads, wound beads, multi-aperture cores, round cable snap-its, rods, antenna/RFID rods, and toroids are all available in 61 material.

Strong magnetic fields or excessive mechanical stresses may result in irreversible changes in permeability and losses.

Fair-Rite Product's Catalog Part Data Sheet, 4061266011

Printed: 2013-07-03








61 Material Characteristics:


Property	Unit	Symbol	Value
Initial Permeability @ B < 10 gauss		μ_i	125
Flux Density	gauss	В	2350
@ Field Strength	oersted	н	15
Residual Flux Density	gauss	B,	1200
Coercive Force	oersted	Hc	1.8
Loss Factor	10-6	tan δ/μ,	30
@ Frequency	MHz		1.0
Temperature Coefficient of Initial Permeability (20 -70°C)	%/°C		0.10
Curie Temperature	°C	Tc	>300
Resistivity	Ωcm	ρ	1x10 ⁸

Complex Permeability vs. Frequency




Measured on a 19/10/6mm toroid using the HP 4284A and the HP 4291A.

Percent of Original Impedance vs. Temperature




Measured on a 2661000301 using the HP4291A.

Initial Permeability vs. Temperature



Measured on a 19/10/6mm toroid at 100kHz.

Hysteresis Loop



Measured on a 19/10/6mm toroid at 10kHz.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Ferrite Toroids / Ferrite Rings category:

Click to view products by Fair-Rite manufacturer:

Other Similar products are found below:

28B0138-7 28B0200-4 28B0250-1 28B0137-3 432202094771 4327 018 35221 432703033201 4327 030 37511 4327 030 37911 4327 030 57161 432202101631 4327 030 12521 5343232001 5943000901 5961004101 28B1250-2 28B2000-3 28B1387-1 28B2400-0 5961000811 5968003801 5975011101 5977000501 5975001821 28B0355-0 M-060 CST29/19/7.5-4S2 T9X8X5 4077485111 TN10/6/4-3F3 TN14/9/5-3F3 MP-050125-2 TX10/6/4-3E5 MS-050125-2 MS-065075-2 MS-106075-2 MS-130060-2 MS-157060-2 MS-157075-2 MS-157125-2 MS-184026-2 MS-184075-2 MS-184125-2 MS-225014-2 MS-226014-2 MS-226125-2 MS-300014-2 RT-100-60-30 RT-100-60-80 RT-100-70-50