

3DP-ASA1.75-01-W

ASA filament, white, 1.75 mm, 1 kg

VERSATILE & EASY TO USE

- Polyethylene terephthalate (ASA) is a Acrylonitrile Styrene acrylate copolymer.
- Perfect combination of clarity and strength. The clarity of ASA approaches that of Acrylic and impact resistance is close to Polycarbonate
- Very low shrinkage makes printing large flat surfaces a breeze
- Easy to print with a variety of 3D printers

Features

- Very high strength ASA filament with 1.75 mm diameter
- ASA maintains the good quality and main characteristics of ABS as an engineering plastic
- Strong weather resistance and high temperature resistance.
- Anti-static, very low shrinkage and excellent chemical resistance
- Suitable for printing on any acrylic, glass, Kapton and other printing platforms
- Can be used in a variety of 3D printers

Packaging

Q'ty in crtn, pcs	8
Crtn volume, CUM	0.033
Crtn weight, kgs	11.74
Individual package size LxWxH:	213x72x215 mm
Carton size LxWxH:	450x310x240 mm
Country of origin	CN
Barcode	8716309129527
Customs code	3916909000

Certificates



Specifications

Material: ASA (KIBILAC PW-997S material), 1.75 mm diameter

Weight: 1 kg/spool (2.2 lbs)

Density at 240°C: 1.057 g/cm³

Printing temperature: 230-250 °C

Hot Pad: 80-120 °C

Melt Flow Index g/10 min ASTM: 16g/10 min (for test method ISO1133, 220°C x 10 Kg (98N))

Heat Deflection temperature: 92°C (for test method ASTM D-648)

Vicat Softening Temperature: 107°C (for test method ASTM D-1525, ISO 306)

Tensile Strength: 440 kg/cm² Mpa (for test method ASTM D-638(ISO527))

Flexural Strength: 780 kg/cm² Mpa (for test method ASTM D-790(ISO178))

Flexural Modulus: 2750 kg/cm² Mpa (for test method ASTM D-790(ISO178))

Rockwell Hardness: R103 (for test method ASTM D-785(ISO2039/2))

Yield Strength at 50 mm/min: 31 MPa

Impact Strength: 8.7 KJ/m²

Ensil Break: 2-3 %

Diameter: 1.75 ± 0.05 mm

Spool dimensions: 200 mm diameter x 67 mm height x 53 mm central hole

System requirements

A 3D printer with 1.75 mm extruder of temperature around 240 °C, suitable for ASA filament

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [3D Printers and Accessories](#) category:

Click to view products by [Gembird](#) manufacturer:

Other Similar products are found below :

[3DP-PLA-01-MTNB](#) [3DP-PLA1.75-01-P](#) [3DP-PLA1.75-01-GB](#) [3DP-PLA+1.75-02-W](#) [3DP-PETG1.75-01-R](#) [PLA 1,75 RACE GREEN](#) [3DP-PLA1.75-01-G](#) [3DP-HIPS1.75-01-R](#) [PETG 1,75 DARK STEEL](#) [3DP-ABS1.75-01-FY](#) [3DP-PLA1.75-01-Y](#) [3DP-TPE1.75-01-Y](#) [PETG 1,75 DARK STEEL SOLO 0,33](#) [3DP-PLA-01-MTBK](#) [3DP-PLA1.75-01-BR](#) [3DP-ABS1.75-01-G](#) [3DP-ABS1.75-01-FG](#) [3DP-PLA1.75GE-01-W](#) [3DP-ABS1.75-01-GR](#) [3DP-PLA+1.75-02-BK](#) [3DP-PLA+1.75-02-G](#) [3DP-PETG1.75-01-G](#) [3DP-PETG1.75-01-BK](#) [3DP-PETG1.75-01-GR](#) [3DP-PLA+1.75-02-Y](#) [3DP-PLA1.75-02-CARBON](#) [3DP-PVA-01-NAT](#) [PLA 1,75 FULL METALLIC](#) [3DP-PLA-01-MTO](#) [3DP-ABS1.75-01-S](#) [ASA 1,75 DARK GRAY](#) [3DP-PLA1.75-01-FR](#) [3DP-ABS1.75-01-BK](#) [3DP-PLA1.75-01-B](#) [3DP-ABS1.75-01-W](#) [PETG 1,75 LIGHT STEEL SOLO 0,33](#) [3DP-PLA1.75-01-W](#) [3DP-PETG1.75-01-Y](#) [3DP-PLA1.75-01-R](#) [3DP-PLA+1.75-02-O](#) [3DP-PLA-01-MTSG](#) [3DP-PLA-FL-01-BK](#) [3DP-PLA1.75GE-01-R](#) [3DP-PLA1.75-02-MAR](#) [3DP-PLA1.75-01-BK](#) [3DP-PETG1.75-01-B](#) [3DP-PLA1.75-01-NAT](#) [3DP-PLA-01-MTP](#) [3DP-PLA1.75-01-BS](#) [3DP-PLA+1.75-02-B](#)