## **DURALECTRIC™**

# The Ultimate in Durable Wire, Cable and Conduit Jacketing




## Virtually Maintenance-Free Dielectric Jacketing Material Protects Wires, Cables and Conduits in Mission-Critical Applications

Most wire and cable specifiers have simple expectations, such as dielectric materials that don't break down over time—requiring expensive replacement long before the lifetime of the ship, plane of vehicle is reached. They also want jacket materials that can withstand high heat, extreme UV radiation, demanding weather conditions and caustic chemicals and fluids. Glenair **Duralectric**<sup>TM</sup> material delivers on these expectations—and a whole lot more. The dielectric material is a special formula with extremely-high durability in such measures as UV weathering, temperature tolerance, low smoke and toxicity index, flame resistance, and halogen free (IEC754-1) ratings.



Duralectric™ (shown here in its desert tan color) is the perfect solution for wire protection conduits used in military vehicles, aircraft and other mission-critical applications.



### Material Specifications

Glenair *Duralectric*<sup>™</sup> weatherproof jacketing is halogen free, flame resistant, and functional to 260°C. *Duralectric*<sup>™</sup> far surpasses the accelerated solar weathering standards under IEC 60068-2-5, and is tested to 56 accelerated days, equivalent to 53 years of solar exposure. Glenair can supply the material in a variety of formats, including blown jacketing, as an extrusion over wire and cable, as an overmolding compound and as a self-vulcanizing repair tape.

Originally qualified to the US navy Mil-PRF-24758A specification, *Duralectric*<sup>™</sup> is available in standard US Navy haze gray in accordance with Fed Std 595B #26270. Other colors are also standard including black, and Fed Std #3446 Desert Tan. Additional Made-to-Order colors are available. The material has the following performance characteristics:

#### GLENAIR *Duralectric™* MATERIAL SPECIFICATIONS

Temperature rating: -70°C to +200°C (with excursions to 260°C)

Halogen free per iec 60614-1. Less than 5mg of hcl per 1 gm of product tested.

Accelerated Weathering (Solar) per IEC 60068-2-5; 56 days exposure

Flame Resistant per IEC 60614-1; Material does not sustain combustion when the source of flame is removed.

Low Smoke Index per NES 711 (11.75); Minimum standard is 25. The Glenair tested level is 11.75. This makes the material acceptable for interior applications as well as topside.

Smoke Density Class F1 Per NF F 16-101 IAW DIN EN 60695-2-11:2001

Toxicity Index per NES 713 (1.9); Minimum standard is 5. The Glenair tested level is 1.9. This makes the material acceptable for interior applications as well as topside.

Colorable to Fed Std 595B

Markable IAW MIL-PRF-24758A

Oxygen Limiting Index = 45.1 Per EN ISO 4589-2:1999; Minimum is 28.

12 Sec Vertical Burn: (Pass) Per 14CFR Part 25.853(a) amdt 25-116 App F Part 1 (a)(1)(ii)

Fluids Per MIL STD 810F, Method 504

Fuel (MIL-T-83133): JPG

Hydraulic Fluid (MIL H 5606): ROYCO 756

Lube Oil (MIL-L-23699): ROYCO-500

Cleaner (MIL-C-85570): CALLA-855

Solvent (Isopropyl Alcohol): TT-I-735

De Icer (AMS-1432): E36 Runway Deicer

Coolant (MIL-C-87252): Coolanol 25R

Fire Extinguishant Foam: AMEREX AFFF





GLENAIR PART NO. 687-758

Duralectric<sup>TM</sup> material sealing tape designed for temporary repair of cable and conduit. Glenair Master Seal effectively stops water incursion until a permanent repair can be made.



# A World of Interconnect Solutions

#### Glenair, Inc.

1211 Air Way • Glendale, California • 91201-2497 Telephone: 818-247-6000 • Fax: 818-500-9912 • sales@glenair.com www.glenair.com

**Glenair Power Products Group** 25 Village Lane Wallingford, CT 06492

Telephone: 203-741-1115 Facsimile: 203-741-0053 sales@glenair.com

**Glenair UK Ltd** 40 Lower Oakham Way Oakham Business Park P.O. Box 37, Mansfield Notts, NG18 5BY England

Telephone: 44-1623-638100 Facsimile: 44-1623-638111 sales@glenair.co.uk

Telephone:

Facsimile:

**Glenair Microway Systems** 7000 North Lawndale Avenue Lincolnwood, IL 60712

Telephone: 847-679-8833 Facsimile: 847-679-8849 **Glenair Nordic AB** Telephone: 46-8-50550000 Gustav III: S Boulevard 46 Facsimile: S - 169 27 Solna 46-8-50550001 Sweden sales@glenair.se

**Glenair Electric GmbH** Siemensstrasse 9 D-61449 Steinbach Germany

Telephone: 49-6171-5905-0 Facsimile: 49-6171-5905-90 germany@glenair.com

**Glenair Iberica** C/ La Vega, 16 34-925-89-29-88 45612 Velada 34-925-89-29-87 Spain sales@glenair.es

Glenair Italia S.R.L. Via Santi. 1 20037 Paderno Dugnano Milano, Italy

Telephone: 39-02-9108-2121 Facsimile: 39-02-9904-3565 sales-italia@glenair.it

**Glenair France SARL** Telephone: 7. Avenue Parmentier 33-5-34-40-97-40 Immeuble Central Parc #2 Facsimile: 31200 Toulouse 33-5-61-47-86-10 sales@glenair.fr France

© 2011 Glenair, Inc.

Printed in U.S.A.

#### **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Adhesive Tapes category:

Click to view products by Glenair manufacturer:

Other Similar products are found below:

56-YELLOW-34"X72YD 00-021200-13972-7 021200-64630 60 TAPE (1") 62-GRAY-12"X36YD 62-GRAY-1"X36YD 69-1"X36YD 764
1"x36yd-Red 764-1"x36yd-White PG ASSY 9500PC-3/4 967454-1 1181 19MM X 16,5 METERS 130C-1X15FT E39-RS1-CA 1900-48mm

22-1/2X36YD 88-SUPER-34X44FT 890103N001 2670 96 EVK-TA-TM047NBH01 20-1"X60YDS 2020-18mmx55m H150 363 3900
Blue 3939-24mmx55m 44-TAN-14"X90YD 4504-34x18 471-Trans-1"x36yd-Bulk 5414 34X36 35-Gray-1/2 4008-12"X36YD 4104
34"x18yd 4116 444-1"x36yd 44661" 4466W-1/2"x36yd 4492B-12"x72yd 4492B-1"x72yd 4496W-12"x36yd 4508-1"x36yd 4516-3/8x36

4726 1/2"X36YD 054007-43154 054007-43152 06149 11-32-2857 5419 1/2"