

TECHNICAL DATA SHEET

Ball bearing steel type CR

General notes:

- » ball bearing steel (Material number 1.3505, 100Cr6, AISI 52100)
- » magnetizable
- » hardened by heat treatment, max. hardness 68 HRC
- » moderate resistance to corrosion
- » generally used where strength, hardness and wear resistance are of primary concern
- yetypical applications include the production of high quality cutters and pliers ideal for cutting single or multiple filars and for lateral or internal cuts. Typical applications include cutting stents, braided mesh, catheters and guide wires in medical device manufacturing

Composition

| Component | Wt.% | Component | Wt.% | Component | Wt.% |
|-----------|-----------|-----------|-----------|-----------|-----------|
| С | 0.95-1.10 | Si | 0.15-0.35 | Mn | 0.25-0.45 |
| Р | ≤0.030 | s | ≤0.030 | Cr | 1.35-1.65 |

Mechanical properties

| Density | 7.85 g/cm ³ |
|----------------------------|------------------------|
| Hardness, Rockwell | 65-68 HRC |
| Tensile strength, ultimate | 2400 MPa |
| 0.2% Yield stress | 1800 MPa |
| Elongation, break | 40% |
| Modulus of elasticity | 212 GPa |

Thermal properties

| Coef. of lin. therm expansion | 12.0 E-6/°C | 20°C-100°C |
|-------------------------------|--------------|------------|
| Coef. of lin. therm expansion | 13.0 E-6/°C | 20°C-300°C |
| Specific heat capacity | 0.46 J/(g·K) | |
| Thermal conductivity | 33 W/(m·K) | |

Electrical properties

Resistivity 0.30 E-4 Ohm.cm

This document contains information based on average values as obtained from the results of laboratory tests and observations made on the material. Ideal-tek SA declines all responsibility from an improper use of the product described in this document.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Pliers & Tweezers category:

Click to view products by Ideal-Tek manufacturer:

Other Similar products are found below:

0031 32750 PN-5050/38D PG-TP-30D PG-DP-18-N G77015 4-1532129-2 77 12 115 0037 T0058765801 571 76C 37 31 125 RX 8130 37 33 125 DRP10N 32 11 135 36 12 130 0036 64 11 115 0032 6231-08 PN 5050/19D PNI 5000 TP 5000/15D TR 30 15 V TR 5000 PR TR 58 R A D 00 20 08 US2 13 01 614 87 28 250 SBA INCP8 30993 011820101 011830101 011910110 003780032 003780041 134-69-160 134-69-180 135-49-VDE-190 137-49-VDE-180 137-49-VDE-200 137-49-VDE-240 137-69-180 137-69-200 137-69-240 138-69-200 140-49-VDE-170