
Y5V Dielectric

General Specifications






GENERAL DESCRIPTION


Y5V formulations are for general-purpose use in a limited temperature range. They have a wide temperature characteristic of +22% -82% capacitance change over the operating temperature range of -30°C to +85°C.


These characteristics make Y5V ideal for decoupling applications within limited temperature range.





PART NUMBER (SEE PAGE 4 FOR COMPLETE PART NUMBER EXPLANATION)

















Y5V Dielectric

Specifications and Test Methods



Parameter/Test		Y5V Specification Limits	Measuring Conditions							
Operating Tem	perature Range	-30°C to +85°C	Temperature Cycle Chamber							
Capacitance		Within specified tolerance								
Dissipation Factor		≤ 5.0% for ≥ 50V DC rating ≤ 7.0% for 25V DC rating ≤ 9.0% for 16V DC rating ≤ 12.5% for ≤ 10V DC rating	Freq.: 1.0 kHz ± 10% Voltage: 1.0Vrms ± .2V For Cap > 10 μF, 0.5Vrms @ 120Hz							
Insulation Resistance		10,000MΩ or 500MΩ - μ F, whichever is less	Charge device with rated voltage for 120 ± 5 secs @ room temp/humidity							
Dielectric	Strength	No breakdown or visual defects	Charge device with 250% of rated voltage for 1-5 seconds, w/charge and discharge current limited to 50 mA (max)							
	Appearance	No defects	Deflectio	n: 2mm						
Resistance to	Capacitance Variation	≤ ±30%	Test Time: 30 seconds 1mm/sec 90 mm							
Flexure Stresses	Dissipation Factor	Meets Initial Values (As Above)								
	Insulation Resistance	≥ Initial Value x 0.1								
Solderability		≥ 95% of each terminal should be covered with fresh solder	Dip device in eutectic solder at 230 ± 5°C for 5.0 ± 0.5 seconds							
	Appearance	No defects, <25% leaching of either end terminal								
	Capacitance Variation	≤ ±20%								
Resistance to Solder Heat	Dissipation Factor	Meets Initial Values (As Above)	Dip device in eutectic solder at 260°C for 60 seconds. Store at room temperature for 24 ± 2 hours before measuring electrical properties.							
	Insulation Resistance	Meets Initial Values (As Above)								
	Dielectric Strength	Meets Initial Values (As Above)								
	Appearance	No visual defects	Step 1: -30°C ± 2°	30 ± 3 minutes						
	Capacitance Variation	≤ ±20%	Step 2: Room Temp	≤ 3 minutes						
Thermal Shock	Dissipation Factor	Meets Initial Values (As Above)	Step 3: +85°C ± 2°	30 ± 3 minutes						
	Insulation Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	≤ 3 minutes						
	Dielectric Strength	Meets Initial Values (As Above)	Repeat for 5 cycles and measure after 24 ±2 hours at room temperature							
	Appearance	No visual defects	-							
	Capacitance Variation	≤ ±30%	Charge device with twice rated voltage in test chamber set at 85°C ± 2°C							
Load Life	Dissipation Factor	≤ Initial Value x 1.5 (See Above)	for 1000 hours (+48, -0)							
	Insulation Resistance	≥ Initial Value x 0.1 (See Above)	Remove from test chamber and stabilize at room temperature for 24 ± 2 hours before measuring.							
	Dielectric Strength	Meets Initial Values (As Above)								
Load Humidity	Appearance	No visual defects								
	Capacitance Variation	≤ ±30%	Store in a test chamber set at 85°C ± 2°C/ 85% ± 5% relative humidity for 1000 hours							
	Dissipation Factor	≤ Initial Value x 1.5 (See above)	(+48, -0) with rated voltage applied. Remove from chamber and stabilize at room temperature and humidity for 24 ± 2 hours before measuring.							
	Insulation Resistance	≥ Initial Value x 0.1 (See Above)								
	Dielectric Strength	Meets Initial Values (As Above)	24 ± 2 nours before measuring.							

Y5V Dielectric

Capacitance Range



PREFERRED SIZES ARE SHADED

SIZE		020	0402				0603				0805				1206				1210						
Solderi	Soldering Reflow Only		Reflow/Wave				Reflow/Wave				Reflow/Wave				ReflowMfeve				Reflow/Wave						
Packag	Packaging All Paper		All Paper					All Paper				Paper/Embossed				Paper/Embossed				Paper/Embossed					
(L) Length mm		0.60 ±	1.00 ± 0.10						1.60	± 0.15		2.01 ± 0.20				3.20 ± 0.20				3.20 ± 0.20					
		(0.024 ± 0.004)				40 ± 0.	.004)		(0	.063 :	± 0.00	6)	(0.079 ± 0.008)				(0.126 ± 0.008)				(0.126 ± 0.008)				
W) Width	mm	nm 0.30 ± 0.09		0.50 ± 0.10					.81 ± 0.15					1.25 ± 0.20				1.60 ± 0.20				2.50 ± 0.20			
(in.)		(0.011 ± 0.004)			(0.020 ± 0.004)				(0.032 ± 0.006)				(0.049 ± 0.008)				(0.063 ± 0.008)				(0.098 ± 0.008)				
(t) Terminal	(t) Terminal mm				0.25 ± 0.15				0.35 ± 0.15			0.50 ± 0.25				0.50 ± 0.25				.50 ± 0.25					
(in.)		(0.006 ± 0.002)		(0.010 ± 0.006			.006)		(0.014 :		± 0.006)		(0.020 ± 0.010		0)		(0.020 ± 0.010)			(0.020 ± 0.010)					
	WVDC	6.3	10	6	10	16	25	50	10	16	25	50	10	16	25	50	10	16	25	50	10	16	25	50	
Сар	820																				~	<	₩.		
(pF)	1000		Α																-		<		7	<u> </u>	
	2200		Α																	(5		للا	ŢŢ.	
	4700		Α																		$\overline{}$	4			
Сар	0.010	A	Α																		ŀ	+			
(μF)	0.022	Α																		1				ш	
	0.047	Α				С																			
	0.10				С	С					G	G				K									
	0.22									G															
	0.33									G															
	0.47					С				G	G														
	1.0			С	С				G	G	J			N	N	N		М	М	М				N	
	2.2				С				J					N	N				K	Q					
	4.7												N	N	N			Р	Q			N	N		
	10.0												N	Р			Q	Q	Х		Х	Q	Q	Z	
	22.0																Q				Х	Z			
	47.0																								
	WVDC	6.3	10	6	10	16	25	50	10	16	25	50	10	16	25	50	10	16	25	50	10	16	25	50	
SIZE		020	0402					0603					90	305		1206					1210				
Letter	Α	С	E		G	JK		K	М		N		Р	P Q		Х		Υ		Z					
Max.	0.33	0.56	0.71	0.90		0.9	4			1.27		1.40		1.52 1.78		2.2		2.54		.79					
Thickness	(0.013)	(0.022)	(0.028)			37)	(0.040)	+		(0.05	55)	(0.060)	(0.	(0.070) (0.09		0) (0.100)		(0.110)							
PAPER							7	1 (-	-,	, , ,		` /	EMBOSSED				-, (,								
PAPER EMBOSSED																									

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Multilayer Ceramic Capacitors MLCC - SMD/SMT category:

Click to view products by Kyocera AVX manufacturer:

Other Similar products are found below:

D55342E07B523DR-T/R NCA1206X7R104K16TRPF NIN-FB391JTRF NIN-FC2R7JTRF NMC0402XPD0220J50TRPF

NMC0402X5R105K6.3TRPF NMC0402X5R224K6.3TRPF NMC0402X7R103J25TRPF NMC0402X7R153K16TRPF

NMC0402X7R392K50TRPF NMC0603NPO1R8C50TRPF NMC0603NPO20J50TRPF NMC0603NPO330G50TRPF

NMC0603X5R475M6.3TRPF NMC0805NPO220J100TRPF NMC0805NPO270J50TRPF NMC0805NPO681F50TRPF

NMC0805NPO820J50TRPF NMC1206X7R102K50TRPF NMC1210Y5V105Z50TRPLPF NMC-L0402NPO7R0C50TRPF NMC-L0603NPO2R2B50TRPF NMC-P1206X7R103K1KVTRPLPF NMC-Q0402NPO8R2D200TRPF C1206C101J1GAC C1608C0G2A221J

C1608X7R1E334K C2012C0G2A472J 2220J2K00562KXT KHC201E225M76N0T00 1812J2K00332KXT CCR06CG153FSV

CDR14BP471CJUR CDR31BX103AKWR CDR33BX683AKUS CGA2B2C0G1H010C CGA2B2C0G1H040C CGA2B2C0G1H050C

CGA2B2C0G1H060D CGA2B2C0G1H070D CGA2B2C0G1H120J CGA2B2C0G1H151J CGA2B2C0G1H1R5C CGA2B2C0G1H2R2C

CGA2B2C0G1H390J CGA2B2C0G1H391J CGA2B2C0G1H3R3C CGA2B2C0G1H680J CGA2B2C0G1H6R8D CGA2B2C0G1H820J