


# X6S Dielectric, KGM Series

## General Specifications



### FEATURES

- Offered in a complete range of products for both general and specialized applications and designed to meet a wide variety of needs.
- We have a worldwide network in order to supply our global customer bases quickly and efficiently.
- All of our products are highly reliable due to their monolithic structure of high-purity and superfine uniform ceramics and their integral internal electrodes.
- By combining superior manufacturing technology and materials with high dielectric constants, we produce extremely compact components with exceptional specifications.
- Our stringent quality control in every phase of production from material procurement to shipping ensures consistent manufacturing and superior quality.

### DIELECTRIC CHARACTERISTICS

- Temperature Range: -55 to + 105°C
- Standard Temperature: 25°C
- ΔC Max: ±22%

### HOW TO ORDER

|                                       |  |                            |                        |  |  |  |                              |
|---------------------------------------|--|----------------------------|------------------------|--|--|--|------------------------------|
| <b>KGM</b>                            | <b>05</b>  | <b>H</b>                   | <b>S6</b>              | <b>0G</b>  | <b>106</b>   | <b>M</b>   | <b>N</b>                     |
| General Purpose<br>Tin/ Nickel Finish | Size<br>03 = 0201<br>05 = 0402<br>15 = 0603<br>21 = 0805 | Thickness<br>See Cap Chart | Dielectric<br>S6 = X6S | Voltage<br>0E = 2.5V<br>0G = 4.0V<br>0J = 6.3V<br>1A = 10V<br>1C = 16V<br>1E = 25V | Capacitance<br>Code Code (in pF)<br>2 Significant Digits<br>+Number of zeros<br>eg. 10µF = 106<br>10nF = 103<br>47pF = 470 | Capacitance<br>Tolerance<br>K = ±10%<br>M = ±20% | Packaging<br>See Table Below |



### PACKAGING CODES


| Code | EIA (inch) | IEC(mm) | 7" Paper | 7" Embossed | 13" Paper | 13" Embossed |
|------|------------|---------|----------|-------------|-----------|--------------|
| 03   | 0201       | 0603    | H        |             | N         |              |
| 05   | 0402       | 1005    | H        |             | N         |              |
| 15   | 0603       | 1608    | T        |             | M         |              |
| 21   | 0805       | 2012    |          | U           |           | L            |

\*Note: The thickness determines if packaging is paper or embossed.

### CAPACITANCE RANGE

| SIZE<br>Packaging | 0201                                   |   |     |    | 0402                                  |     |     |    |     | 0603                                  |   |     |    |    | 0805                                  |   |     |    |    |    |
|-------------------|--|---|-----|----|---------------------------------------|-----|-----|----|-----|---------------------------------------|---|-----|----|----|---------------------------------------|---|-----|----|----|----|
|                   | All Paper                              |   |     |    | All Paper                             |     |     |    |     | All Paper                             |   |     |    |    | All Embossed                          |   |     |    |    |    |
| (L) Length        | mm<br>0.60 ± 0.09<br>(0.024 ± 0.004)   |   |     |    | mm<br>1.00 ± 0.20<br>(0.040 ± 0.002)  |     |     |    |     | mm<br>1.60 ± 0.20<br>(0.063 ± 0.008)  |   |     |    |    | mm<br>2.01 ± 0.20<br>(0.079 ± 0.008)  |   |     |    |    |    |
| (W) Width         | mm<br>0.30 ± 0.09<br>(0.011 ± 0.004)   |   |     |    | mm<br>0.50 ± 0.20<br>(0.020 ± 0.008)  |     |     |    |     | mm<br>0.80 ± 0.20<br>(0.030 ± 0.008)  |   |     |    |    | mm<br>1.25 ± 0.20<br>(0.049 ± 0.008)  |   |     |    |    |    |
| (t) Terminal      | mm.<br>0.18 ± 0.005<br>(0.007 ± 0.002) |   |     |    | mm.<br>0.25 ± 0.10<br>(0.010 ± 0.004) |     |     |    |     | mm.<br>0.40 ± 0.20<br>(0.016 ± 0.008) |   |     |    |    | mm.<br>0.50 ± 0.25<br>(0.020 ± 0.010) |   |     |    |    |    |
| WVDC              | 2.5                                    | 4 | 6.3 | 10 | 4                                     | 6.3 | 10  | 16 | 25  | 2.5                                   | 4 | 6.3 | 10 | 16 | 25                                    | 4 | 6.3 | 10 | 16 | 25 |
| Cap (µF)          | 0.47                                   |   |     |    |                                       |     | A   | A  | A   |                                       |   |     |    |    | A                                     |   |     |    |    |    |
|                   | 1.0                                    | C | C   | C  |                                       |     | A   | A  | A   |                                       |   |     |    |    | A                                     |   |     |    |    |    |
|                   | 2.2                                    |   |     |    |                                       |     |     | A  |     |                                       |   |     |    |    |                                       |   |     |    |    |    |
|                   | 4.7                                    | D |     |    |                                       |     | B/C | C  |     |                                       |   | A   |    | C  |                                       |   |     |    |    |    |
|                   | 10                                     |   |     |    | H                                     | C   |     |    |     |                                       |   | C   | C  | C  | C                                     |   |     |    |    | F  |
|                   | 22                                     |   |     |    | D                                     |     |     |    |     |                                       |   | C   | C  | C  | C                                     |   |     |    |    |    |
|                   | 47                                     |   |     |    |                                       |     |     |    |     | C                                     | C |     |    |    |                                       | A | A   | A  | A  |    |
|                   | 100                                    |   |     |    |                                       |     |     |    |     |                                       |   |     |    |    |                                       |   |     |    |    |    |
| WVDC              | 2.5                                    | 4 | 6.3 | 10 | 4                                     | 6.3 | 10  | 16 | 6.3 | 2.5                                   | 4 | 6.3 | 10 | 16 | 25                                    | 4 | 6.3 | 10 | 16 | 25 |
| Size              | 0201                                   |   |     |    | 0402                                  |     |     |    |     | 0603                                  |   |     |    |    | 0805                                  |   |     |    |    |    |

| Case Size               | 0201 (KGM03) |      | 0402 (KGM05) |      |      |      |     | 0603 (KGM15) |      | 0805 (KGM21)   |      |
|-------------------------|--------------|------|--------------|------|------|------|-----|--------------|------|----------------|------|
| Thickness Letter        | C            | D    | A            | B    | C    | H    | D   | A            | C    | A              | F    |
| Max Thickness(mm)       | 0.39         | 0.55 | 0.55         | 0.65 | 0.70 | 0.75 | 0.8 | 0.90         | 1.00 | 1.45           | 1.52 |
| Carrier Tape            | PAPER        |      | PAPER        |      |      |      |     | PAPER        |      | EMB            |      |
| Packaging Code 7" reel  | H            | H    | H            | H    | H    | H    | H   | T            | T    | U              | U    |
| Packaging Code 13" reel | N            | N    | N            | N    | N    | N    | N   | M            | M    | L              | L    |
|                         | PAPER        |      |              |      |      |      |     |              |      | Embossed (EMB) |      |



# X6S Dielectric, KGM Series

## Specifications and Test Methods



| X6S Specification Limits    |  | X6S Specification Limits   | Measuring Conditions (Complies with JIS C5101 / IEC60384)  |
|-----------------------------|--|--|--|
| Operating Temperature Range |  | -55°C to +105°C  | Temperature Cycle Chamber  |
| Capacitance                 |  | Within specified tolerance   | Measure after heat treatment<br>Capacitance Frequency Volt<br>C<10μF<br>Frequency : 1kHz±10%<br>Volt : 1.0±0.2Vrms *0.5±0.2Vrms  |
| Dissipation Factor / Tanδ   |  |  | C>10μF<br>Frequency : 120Hz±10%<br>Volt : 0.5±0.2Vrms<br>The charge and discharge current of the capacitor must not exceed 50mA.   |
| Insulation Resistance       |  | Refer to <a href="https://spicat.kyocera-avx.com">https://spicat.kyocera-avx.com</a> for individual part number specification      | Apply the rated voltage for 1 minute, and measure it in normal temperature and humidity.<br>The charge and discharge current of the capacitor must not exceed 50mA.  |
| Dielectric Strength         |  | No breakdown or visual defects   | Charge device with 250% of rated voltage for 1-5 seconds, w/charge and discharge current limited to 50 mA (max)<br>* Note, Charge device with 150% rated voltage for 500V devices  |
| Bending Strength            |  | No significant damage with 1mm bending   | Glass epoxy PCB: Fulcrum spacing: 90mm, duration time 10 seconds.  |
| Solderability               |  |  | Soaking condition Sn-3Ag-0.5Cu 245±5°C 3±0.5 sec.  |
| Resistance to Solder Heat   | Appearance                                 | No problem observed  | Take the initial value after heat treatment.<br>Soak the sample in 260°C±5°C solder for 10±0.5 seconds and place in normal temperature and humidity, and measure after heat treatment.<br>(Pre-heating conditions)<br>Order      Temperature      Time<br>1          80 to 100°C          2 minutes<br>2          150 to 200°C          2 minutes<br>The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement. |
|                             | Capacitance Variation                      | ≤ ±7.5%  |  |
|                             | Dissipation Factor / Tanδ                  | Within specification   |  |
|                             | Insulation Resistance                      | Within specification   |  |
|                             | Withstanding Voltage / Dielectric Strength | Resist without problem   |  |
| Thermal Shock               | Appearance                                 | No visual defects  | Take the initial value after heat treatment.<br>(Cycle)<br>Room temperature (3 min.)→<br>Lowest operation temperature (30 min.)→<br>Room temperature (3 min.)→<br>Highest operation temperature (30 min.)<br>After 5 cycles, measure after heat treatment.<br>The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.  |
|                             | Capacitance Variation                      | ≤ ±7.5%  |  |
|                             | Dissipation Factor                         | Within specification   |  |
|                             | Insulation Resistance                      | Within specification   |  |
|                             | Withstanding Voltage / Dielectric Strength | Resist without problem   |  |
| Load Life                   | Appearance                                 | No visual defects  | Take the initial value after heat treatment.<br>After applying *1.5 the rated voltage at the highest operation temperature for 1000+12/-0 hours, and measure the sample after heat treatment in normal temperature and humidity.<br>The charge and discharge current of the capacitor must not exceed 50mA for IR measurement.<br>*Apply 1.0 times when the rated voltage is 4V or less. Applied voltages for respective products are indicated in the chart below.      |
|                             | Capacitance Variation                      | ≤ ±12.5%   |  |
|                             | Dissipation Factor / Tanδ                  | ≤ Initial Value x 2.0 (See Above)  |  |
|                             | Insulation Resistance                      | Over 1000MΩ or 50MΩ · μF, whichever is less. *Exceptions Listed Below  |  |
| Load Humidity               | Appearance                                 | No visual defects  | Take the initial value after heat treatment.<br>After applying rated voltage for 500+12/-0 hours in the condition of 40°C±2°C and 90 to 95%RH, and place in normal temperature and humidity, then measure the sample after heat treatment.<br>The charge and discharge current of the capacitor must not exceed 50mA for IR measurement.   |
|                             | Capacitance Variation                      | ≤ ±12.5%   |  |
|                             | Dissipation Factor / Tanδ                  | Within specification   |  |
|                             | Insulation Resistance                      | Over 1000MΩ or 50MΩ · μF, whichever is less. *Exceptions Listed Below  |  |
| Appearance                  |  |  | Microscope   |
| Termination Strength        |  |  | Apply a sideward force of 500g (5N) to a PCB-mounted sample. Note : 2N for 0201 size, and 1N for 01005 size.   |
| Vibration                   | Appearance                                 | No problem observed  | Take the initial value after heat treatment.<br>Vibration frequency: 10 to 55 (Hz)<br>Amplitude: 1.5mm<br>Sweeping condition: 10→55→10Hz/ 1 minute in X, Y and Z directions: 2 hours each, 6 hours in total, and place in normal temperature and humidity, then measure the sample after heat treatment  |
|                             | Capacitance                                | Within tolerance   |  |
|                             | Tanδ                                       | Within tolerance   |  |
| Heat treatment              |  | Expose sample in the temperature of 150+0/-10°C for 1 hour and leave the sample in normal temperature and humidity for 24±2 hours. |  |

Voltage to be applied in the High Temperature Load (Applied voltage is the multiple of the rated voltage)

| Rated Voltage |      |  |
|---------------|------|--|
| ×1.0          | 2.5V | KGM03DS60E475  |
|               | 4V   | KGM03CS60G105, KGM05DS60G226, KGM15CS60G226, KGM21AS60G476                               |
|               | 6.3V | KGM03CS60J105, KGM05BS60J475, KGM05CS60J106, KGM15CS60J226                               |
|               | 10V  | KGM03CS61A105, KGM05AS61A474, KGM05AS61A105, KGM05CS61A475, KGM15CS61A226, KGM21AS61A226 |
|               | 16V  | KGM05AS61C474, KGM05AS61C225, KGM15CS61C106, KGM21AS61C226                               |
|               | 25V  | KGM05AS61E105  |

Load Life / Load Humidity > Insulation Resistance: Over 10MΩ · μF

|    |    |  |
|----|----|--|
| S6 | 03 | KGM03DS60E475, KGM03CS60G105, KGM03CS60J105, KGM03CS61A105   |
|    | 05 | KGM05DS60G226, KGM05CS60J475, KGM05BS60J475, KGM05CS60J106, KGM05AS61A474, KGM05AS61A105, KGM05CS61A475, KGM05AS61C474, KGM05AS61C225, KGM05AS61E105 |
|    | 15 | KGM15CS60G226M, KGM15CS60J226, KGM15CS61A106, KGM15CS61A226, KGM15CS61C106   |
|    | 21 | KGM21AS60G476, KGM21AS60J226, KGM21AS61A226, KGM21AS61C226   |

## X-ON Electronics

Largest Supplier of Electrical and Electronic Components

*Click to view similar products for [Multilayer Ceramic Capacitors MLCC - SMD/SMT category:](#)*

*Click to view products by [Kyocera AVX manufacturer:](#)*

Other Similar products are found below :

[M39014/02-1218V](#) [M39014/02-1225V](#) [M39014/02-1301](#) [M39014/22-0631](#) [M39014/22-0808](#) [NIN-FC2R7JTRF](#) [C1608C0G2A221J](#)  
[C1608X7R1E334K](#) [C2012C0G2A472J](#) [CL10C0R8BB8ANNC](#) [C1005X5R0G225M](#) [C3216C0G2J272J](#) [726632-1](#) [CGA3E2X8R1H223K](#)  
[CDR35BX474AKUR\M500](#) [C1608X8R1H473K](#) [M39014/01-1554](#) [4327 030 36981](#) [CDR06BX474AMSP\M](#) [CDR31BP330BJMS\M](#)  
[M39014/220214](#) [CHP1-100-8202-G-LF674A](#) [502R29N330JV3E-](#) [0603B103J500NT](#) [1206B103K501NT](#) [0402N820J101CT](#)  
[1206N221J202CT](#) [0805N330J102CT](#) [1206N220J501CT](#) [1206N151J500CT](#) [1206N103J101CT](#) [0603B152K201CT](#) [RF18N5R0B500CT](#)  
[0603B472K201CT](#) [0805B272K101CT](#) [0603N1R0C251CT](#) [0805B153K201CT](#) [1210B333K101CT](#) [CC0100JRNPO8BN100](#)  
[CC0100JRNPO6BN101](#) [CC0402JRNPO9BN301](#) [CC0805KKX7R0BB105](#) [AC0805KKX7R6BB475](#) [CC0805KKX7R7BB824](#)  
[CQ0402DRNPO9BN5R6](#) [AF0100FR-07200KL](#) [CC0603DRNPO9BN5R1](#) [CC0805GKNPO9BN472](#) [CC1206JKX7R9BB474](#)  
[CC1206JRX7R8BB474](#)