## **Automotive Grade Cylindrical SuperCapacitors**





The new series of cylindrical electrochemical double-layer capacitors offers automotive grade, qualified by AEC-Q200, solutions with high capacitance and very low ESR. Used by themselves or in conjunction with primary or secondary batteries, they provide extended back up time, longer battery life, and provide instantaneous power pulses as needed. Offers great solutions to Hold-Up, Energy Harvesting, and Pulse Power Applications.

#### **FEATURES**

- Vdc 3.0V
- Cap values from 10F 100F
- High pulse power capability
- Low leakage current
- Pass AEC-Q200

#### **APPLICATIONS**

- · eLatch (Safety, Normal operation)
- eCall (Safety)
- · Motor Stabilization
- eVideo
- Power backup
- · Camera flash systems
- · Energy harvesting

- · GSM/GSR pulse applications
- UPS/Industrial
- · Wireless alarms
- Remote metering
- Scanners
- Toys and games

#### **HOW TO ORDER**







length in mm





107

Capacitance Code 1st two digits represent significant figures 3rd digit represents multiplier (number of zeros to follow)



Tolerance S = +30%/-10%



**Lead Format** R = Radial





## **QUALITY INSPECTION**

Parts are tested for Life Cycle, high load life, temperature temperature characteristics, vibration resistance, and humidity characteristics. See page 2 for more information.

#### **TERMINATION**

These SuperCapacitors are compatible with hand soldering and wave soldering processes, so long as appropriate precautions are followed. See page 4 for more information.

#### **OPERATING TEMPERATURE**

-40°C to +65°C @ 3.0V

-40°C to +85°C with appropriate derating





For RoHS compliant products, please select correct termination style.



# **Automotive Grade Cylindrical SuperCapacitors**

### **RATINGS & PART NUMBER REFERENCE**

Part Number	Diameter (mm)	Length (mm)	Rated Capacitance (F)	Capacitance Tolerance	Rated Voltage (V)	Rated Temperature (°C)	DCL Max @ 72 Hrs (μA)	ESR Max @ 1000 Hz (mΩ)	ESR Max @ DC (mΩ)	Peak Current (A)	Power Density (W/kg)	Max Energy (Wh)	Energy Density (Wh/kg)
Radial Lead													
SCCV60E107SRBQ	18	60	100	+30%/-10%	3.0*	65/85*	260	15	18	53.57	2904	0.1250	6.05

<sup>\*</sup>with appropriate voltage derating operating temperature can be extended to  $85^{\circ}\text{C}$ 


## **QUALIFICATION TEST SUMMARY**


Test	Test Method	Parameter	Limits
Life Cycle	Capacitors are cycled between rated voltage and half-rated voltage under constant current at +25°C for 500,000 cycles	Capacitance ESR Appearance	≤30% of spec value ≤200% of spec value No remarkable defects
High Temperature Load Life	Temperature: +85°C Voltage: Rated Voltage Test Duration: 1,000 hours	Capacitance ESR Appearance	≤30% of spec value ≤200% of spec value No remarkable defects
Storage Temperature Characteristics	Storage Duration: 2 years No Load Temperature: +35°C	Capacitance ESR Appearance	≤30% of spec value ≤200% of spec value No remarkable defects
Vibration Resistance	MIL-STD-202G Method 204/213	Capacitance ESR Appearance	≤30% of spec value ≤200% of spec value No remarkable defects






## **QUALITY AND RELIABILITY**












#### **MECHANICAL SPECIFICATIONS**

#### **RADIAL LEAD TYPE 1F - 100F**



Cap (F)	D (mm)	L (mm)	P (mm)	d (mm)
100	18	60	8	0.8

#### SOLDERING RECOMMENDATIONS

When soldering SuperCapacitors to a PCB, the temperature & time that the body of the SuperCapacitor sees during soldering can have a negative effect on performance. We advise following these guidelines:

- Do not immerse the SuperCapacitors in solder. Only the leads should come in contact with the solder.
- Ensure that the body of the SuperCapacitor is never in contact with the molten solder, the PCB or other components during soldering.
- Excessive temperatures or excessive temperature cycling during soldering may cause the safety vent to burst or the case to shrink or crack, potentially damaging the PCB or other components, and significantly reduce the life of the capacitor.

PRECAUTION: For all products with shrink wrap sleeves, washing in any type of cleaning agent is prohibited. During all soldering processes, it's recommended to protect the shrink wrap from any kind of liquid (including but not limited to: water, strong acid, strong alkali, strong oxidizing solutions, and strong solvents) to avoid the risk of damage, cracking, and fading of the outer shrink wrap.

#### HAND SOLDERING

Keep distance between the SuperCapacitor body and the tip of the soldering iron and the tip should never touch the body of the capacitor. Contact between SuperCapacitor body and soldering iron will cause extensive damage to the SuperCapacitor, and change its electrical properties. It is recommended that the soldering iron temperature should be less than 350°C, and contact time should be limited to less than 4 seconds. Too much exposure to terminal heat during soldering can cause heat to transfer to the body of the SuperCapacitor, potentially damaging the electrical properties of the SuperCapacitor.

#### WAVE SOLDERING/ SELECTIVE WAVE SOLDERING

Only use wave soldering or selective wave soldering on Radial type SuperCapacitors. The PCB should be preheated only from the bottom and for less than 60 seconds, with temperature at, or below, 100°C on the top side of the board for PCBs equal to or greater than 0.8 mm thick.

Wave Soldering					
Solder Temperature (°C)	Suggested Solder Time (s)	Maximum Solder Time (s)			
220	7	9			
240	7	9			
250	5	7			
260	3	5			

Selective Wave Soldering					
Solder Temperature (°C)	Suggested Solder Time (s)	Maximum Solder Time (s)			
290	2	4			




## **Automotive Grade Cylindrical SuperCapacitors**

#### **TEST METHODS**

#### **IEC CAPACITANCE TEST METHOD**

Procedure:

Charge module under constant current to rated voltage at room temperature, then hold 10 minutes on charge under constant voltage. After 10 minutes, discharge under constant current (as shown in chart below), recording voltage at V1, V2, and time intervals at t1 and t2. Use the capacitance formula to determine cap value.



I - Discharge Current, 4 × C × V<sub>R</sub> (mA)

V<sub>p</sub> - Rated Voltage (V)

V<sub>1</sub> - Initial Test Voltage, 80% Of V<sub>p</sub> (V)

V2 - Final Test Voltage, 40% Of V2 (V)

t, - Initial Test Time (s)

T<sub>2</sub> - Final Test Time (s)

$$C = \frac{I \times (t_2 - t_1)}{V1 - V2}$$

## DC ESR MEASUREMENT

A six-step  $\mathsf{ESR}_{\mathtt{DC}}$  test method is illustrated to the right and carried out as follows:

Rest 10 Seconds

Charge under constant current (I<sub>1</sub>) to rated voltage (V<sub>R</sub>)

Rest 5 seconds

Rest 10 seconds, record V<sub>3</sub> and t<sub>4</sub>

Discharge under constant current (I2) to half rated voltage, Record I2, V4, And t5


\* Rest 2 seconds, record V $_5$  And t $_6$  Repeat steps 1-6 recording I, V, And t accordingly, finally discharging to below 0.1V under constant current (I<sub>2</sub>).

Formulas to calculate:

Two cycle discharge capacitances:  $C_{deh1} = I_2 \times \frac{(t_5 - t_4)}{V_3 - V_4}$ ;  $C_{deh2} = I_2 \times \frac{(t_{11} - t_{10})}{(V_9 - V_{10})}$ 

Discharge capacitance:  $C_{dch} = \frac{(C_{dch1} + C_{dch2})}{2}$ 

Two cycle discharge DC ESR:  $ESR_{dch1} = \frac{(V_s - V_4)}{I_2}$ ;  $ESR_{dch2} = \frac{(V_{11} - V_{10})}{I_2}$ Discharge DC ESR:  $ESR_{dch} = \frac{(ESR_{dch1} + ESR_{dch2})}{2}$ 



Note: I<sub>1</sub> = I<sub>2</sub> = 75mA/F, the rated capacitance in the chart means discharge capacitance, and DC ESR (ESR<sub>DC</sub>) means discharge DC resistance.



## **Automotive Grade Cylindrical SuperCapacitors**

TEST METHODS (continued)

#### **MAXIMUM CONTINUOUS CURRENT**

• This is the maximum current when temperature rise of the supercapacitor during its operation is less than 15°C

#### **MAXIMUM PEAK CURRENT**

· This is the maximum current during 1 second time interval (dt)

#### POWER DENSITY

• Power Density =  $(0.12*V^2 / R_{DC})$  / mass

#### **ENERGY DENSITY**

Energy Density = (½ CV²) / (3600\*mass)

#### **POLARITY AND REVERSE VOLTAGE**

For product consistency and optimum performance, it is recommended that the capacitor be connected with polarity indicated. Reversing polarity could result in permanent damage to the circuit including much higher leakage current for a short duration of time and the life time of the supercapacitors will be reduced.

#### LIFE TIME AND TEMPERATURE PERFORMANCE

The life of a supercapacitor is impacted by a combination of operating voltage and the operating temperature according to the following Time to Failure equation:

$$t \propto V^n \times e^{\left(\frac{-Q}{kT}\right)}$$


where V is the operating voltage, Q is the activation energy in electron volts (eV), k is the Boltzmann constant in eV, and T is the operating temperature in Kelvin (K). Typical values for the voltage exponent, n, is between 2.5-3.5, and Q is between 1.0-1.2 eV in the normal operating temperature range of -40° to 65°C.

The industry standard for supercapacitor end of life is when the equivalent series resistance, ESR, increases to 200% of the specified value and the capacitance drops by 30% from specified value. Typically a supercapacitor shows an initial "iump" in the ESR value and then levels off. If the supercapacitors are exposed to excessive temperatures the ESR will show a continuous degradation (increase). In the extreme case, if the temperature or voltage are substantially higher than the rated specifications, this could result in the part venting and the product showing a faster degradation of capacitance and ESR, which may be many times the specified value.





# Expected Lifetime at Various Voltages SCC Series



## **Automotive Grade Cylindrical SuperCapacitors**



#### SAFETY RECOMMENDATIONS

#### WARNINGS

- · To Avoid Short Circuit, after usage or test, SuperCapacitor voltage needs to discharge to ≤ 0.1V
- Do not Apply Overvoltage, Reverse Charge, Burn or Heat Higher than 150°C, explosion-proof valve may break open
- Do not Press, Damage or disassemble the SuperCapacitor, housing could heat to high temperature causing Burns
- If you observe Overheating or Burning Smell from the capacitor disconnect Power immediately, and do not touch

#### **EMERGENCY APPLICATIONS**

If Housing is Leaking:

- Skin Contact: Use soap and water thoroughly to wash the area of the skin
- Eye Contact: Flush with flowing water or saline, and immediately seek medical treatment
- · Ingestion: Immediately wash with water and seek medical treatment

#### **TRANSPORTATION**

Not subjected to US DOT or IATA regulations UN3499, <10Wh, Non-Hazardous Goods International shipping description - "Electronic Products - Capacitor"

#### REGULATORY

- UL 810A
- · RoHS Compliant
- · REACH Compliant
- · Halogen free according to IEC 61249-2-21: 2003 and IPC/JEDEC-J-STD-709

#### **STORAGE**

Capacitors may be stored within the temperature range of -40°C to +70°C with humidity < 60%. Lower storage temperature is preferred as it extends the shelf life of the capacitor. Product over one year and within two years of the date code, we recommend recharging the product at the beginning of use for at least 24 hours.

Optimum storage conditions are as follows:

- 25°C and RH ≤ 60% without voltage applied
- · Not in direct sunlight
- Not in direct contact with water, salt oil or other chemicals
- Not in direct contact with corrosive materials, acids, alkalis, or toxic gases
- Not in dusty environments
- Not in environments with shock and vibration conditions

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Supercapacitors / Ultracapacitors category:

Click to view products by Kyocera AVX manufacturer:

Other Similar products are found below:

BZ12GA154ZHB BZ195B273ZNBDM C-TEC1225 P KR-5R5C105H-R SCCY73B407SLBLE MAL223551014E3 MAL223551007E3

MAL223551001E3 CPM3225A-2K iMOD054V062P3L-11A SCCS30B126SRB HSL0814-3R8106-R SC5V5Z255M DB5U207M30045HA

DRE10/2.5 DRL106S0TI25RRDAP DRL226S0TK25RR 106DCN2R7M SCCR20B335SRB SCCT30B156SRB SCCU30B306MRB

SCMR14C474MRBA0 SCMR14C474MSBA0 SCMR22C155MRBA0 SCMR22C155MSBA0 SCMS22C255MRBA0 SCMT22C505MRBA0

SCMT32C755MRBA0 DRL475S0TG20RRDAP FT0H225ZF SCCV40B506MRB NEXCW224Z3.5V10.7X5.5TRF GW209F TV1020
3R0605-R TV1245-3R0346-R SCCX50B207VSB PAS0815LS2R5105 MAL222091006E3 MAL222091008E3 SCCY62B307VSB

SCMR18C105MSBA0 EEC-HL0E107 EEC-HL0E506 SCMR18D105MRBB0 MAL219691154E3 HVZ0E107NF-LT MAL219632224E3

HVZ0E106NF MAL219691125E3 MAL219691225E3