

Tflex[™] 700 Series Thermal Gap Filler



HIGHEST THERMAL CONDUCTIVITY COMPLIANT GAP FILLER

Tflex™ 700 is a 5 W/mK soft gap filler thermal interface material with great thermal performance and high compliancy. The soft interface pad conforms to component topography, resulting in little or no stress on the components and mating chassis or parts.

Unique silicone and ceramic filler technology allows a combination of high compliancy and high thermal performance. Tflex™ 700 is stable from -45°C thru 200°C and meets UL 94V0 flame rating. Naturally tacky, it requires no additional adhesive coating which inhibits thermal performance.

FEATURES AND BENEFITS

- Thermal conductivity 5.0 W/mK
- · Highly compliant
- Low thermal resistance even at low pressure
- Available in thicknesses from 0.020" thru 0.200" (0.5mm thru 5.0mm)
- Naturally tacky for adhesion during assembly and transport

APPLICATIONS

- Cooling components to chassis, frame or other mating components
- Mass storage devices
- Heat pipe thermal solutions for notebook computers
- · Automotive engine control
- Telecommunication hardware
- LED solid state lighting
- Power electronics
- · Flat panel displays
- Audio and video components
- Computer servers and other IT infrastructure
- GPS navigation and other portable devices

 Farnell Description :
 Laird-PN:

 Tflex 720 9x9in, thickness = 0.5 mm
 A15196-02

 Tflex 740 9x9in, thickness = 1.0 mm
 A15896-04

 Tflex 780 9x9in, thickness = 2.0 mm
 A15796-26

 Tflex 7160 9x9in, thickness = 4.0 mm
 A15896-31

 Tflex 7200 9x9in, thickness = 5.0 mm
 A15796-28

Americas: +1.800.843.4556 Europe: +49.8031.24600 Asia: +86.755.2714.116

Tflex[™] 700 Series Thermal Gap Filler

	Tflex™ 700	TEST METHOD
Construction	Filled Silicone Sheet	N/A
Color	Dark Grey	Visual
Thermal Conductivity (W/mK)	5.0	Hot Disk™
Hardness (Shore 00)	66; 3	ASTM D2240
Specific Gravity	1.73	Helium Pyncometer
Thickness Range	0.020"200" (0.5 - 5.0mm)	
Thickness Tolerance	±10%	
UL Flammability Rating	94 V0	File E180840
Temperature Range	-45°C to 200°C	See reliability report
Volume Resistivity (ohm-cm)	1 x 10 ¹³	ASTM D257
Outgassing TML	1.0%	ASTM E595
Outgassing CVCM	0.13%	ASTM E595

STANDARD THICKNESSES

Standard thickness 0.020'' (0.5mm) through 0.200'' (5.0mm) available in 0.010'' (0.25mm) increments.


MATERIAL NAME AND THICKNESS

Tflex™ - indicates elastomeric gap filler product line.

7XXX - indicates Tflex™ 700 product line and thickness in mils (0.001-inches).

-DC1 - one side tacky; default is both sides tacky.

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.



X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Thermal Interface Products category:

Click to view products by Laird manufacturer:

Other Similar products are found below:

7721-9PPS FGN80-2 PFM-172-60 A-40 9601-7 5300AC 1.500G 017177 08133 TVQF-1225-07S TP0001 4860 V6516C A17653-20 A17536-07 A17775-05 A17633-03 TA-1.75 30195 3223-07AC-34 3223-07AC-51 V6516A U021041-32-U1 A17752-05 MC32680 7952MP (610MM X 914 MM) 7717-46NG VC-106-70-3 AL-225-175 A12780-01 A17084-07 A15295-13 70-841-031 2403289 2403290 A16820-27 2190548 TCF 2000 AF 01884.9-00 SC100-W40 SC1000-W1SS SC80-W2B 30190 30198 MC-099/127 CS-054/088 CS-116/138 CS-138/210 CS-143/188 CS-B-01 CS-C