

# 85785 Nickel/Copper Fabric Tape



### **NI/CU POLYESTER CONDUCTIVE FABRIC TAPE**

Laird's Conductive Fabric Tape 85785 is composed of metallized (nickel/copper) polyester based fabric and conductive pressure sensitive adhesive (PSA). The fabric layer offers excellent performance for EMI/RFI shielding and electrical grounding, while the adhesive layer makes it convenient to apply on most metal or plastic surfaces. This relatively stiff fabric tape is ideal for die cut and hole punched applications.

### FEATURES **PROHS**

- RoHS compliant
- Halogen-free per IEC-61249-2-21 standard
- Low surface resistivity of  $< 0.04 \ \Omega/\Box$  provides excellent conductivity
- Shielding effectiveness of >75 dB across a wide spectrum of frequencies

#### **MARKETS**



- Cabinet applications
  - LCD and Plasma TV
  - Medical equipment
  - Servers
  - Printers
  - Laptop computers

USA: +1.866.928.8181 Europe: +49.0.8031.2460.0 Asia: +86.755.2714.1166




# 85785 Nickel/Copper Fabric Tape

ltem	Unit	Value	Test Method
Thickness	mm	$0.12 \pm 0.02$	-
Peel Adhesion	Kgf / 25 mm	>1.1	PSTC 101*
Shear Adhesion			
at R.T.	Hrs	>72	PSTC 107#
at 80°C	Hrs	>5	PSTC 107#
Tensile Strength	Kgf / 25 mm	>12	
Operation Temperature	°C	0-80	
Surface Resistivity (Fabric Side)	Ω/□	<0.04	ASTM F390
Z-axial Resistance	Ω	<0.04	
Shielding Effectiveness+			ASTM D4935
at 100 MHz	dB	75	
at 1GHz	dB	80	
Package Dimensions	М	W: 5 mm to 1000 mm L: Standard Length of 20 M	
Shelf Life (Under 23°C/65% R.H.)		Six Months	

<sup>\*:</sup>Test Method A, dwell time 30 min. #:Contact area 25 mm by 25 mm +:Typical value

### **COMPOSITION OF PRODUCT**



### **APPLICATION TECHNIQUES**

- 1. Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact and improves bond strength.
- 2. To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified.
- 3. The temperature of tape application is recommended 21°C to 38°C.
- 4. Not designed for cable wrapping or applications requiring high shear adhesion. Please contact your Laird Sales representative for a more suitable product.

### **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for EMI Gaskets, Sheets, Absorbers & Shielding category:

Click to view products by Laird Connectivity manufacturer:

Other Similar products are found below:

8101010140 8563-0090-89 1194-7.7X10 1245-34"X18YD 1267 1345-3/8x18yrd 1554907-1 2320002000 2320014700 SG293037DS

ST005PCN50 55005107 38M4040AA0606 46J5N02020.NN00 1125-8X10 1126X1" 1170-3/4X18YDS 1170-7.7x10 1183-12"X18YD 6
34T-BD-0.315 SG125187D-24 SG125250R-24 SG187375R-24 SG284050DS 8402010540 KIT TECH CLIP 10-40450-28S 1245 1267
1/2"x18yd 46J8501020.NN00 1170-1/4"x18yd AL-36FR-1x54.5 3013310A 1194X1" 3020604 3021302 3031313 260709 3021310 6
34UT-070-BD-16 303076048 46J5N03020.NN00 30206025 30395641 3030403 3690103020 HNY-LT15CU4241 46X7503020.NN00

46W5E02520.NN00 302095032