

Tputty™ 502 SeriesThermal Gap Filler



PRODUCT DESCRIPTION

Tputty[™] 502 is best suited for applications where large tolerance differences create the need for compression of the interface material beyond 50% of its original thickness.

Tputty™ 502 will ensure low pressures on the components being cooled. In conjunction with outstanding compression characteristics, Tputty™ 502 has a high thermal conductivity, resulting in very low thermal resistance. Tputty™ 502 is naturally tacky and requires no additional adhesive coating that can inhibit thermal performance.

FEATURES AND BENEFITS

- 3 W/mK thermal conductivity
- Soft and ultra high compressibility for low stress applications
- Fiberglass layer for reinforcement and better handling capabilities
- Low Dielectric Constant
- Environmentally friendly solution that meets regulatory requirements including RoHS and REACH

SPECIFICATIONS

| TYPICAL PROPERTIES | VALUE | TEST METHOD |
|------------------------------|--|-----------------------|
| Construction & Composition | Reinforced boron nitride filled silicone sheet | N/A |
| Color | White | Visual |
| Thickness Range | 0.50mm (0.020") 5.0mm (0.20") | N/A |
| Thickness Tolerance | +/- 10% | N/A |
| Thermal Conductivity (W/mK) | 3.0 | ASTM D5470 |
| Density (g/cc) | 1.37 | Helium Pycnometer |
| Hardness (Shore 00) | 14 | ASTM D2240 |
| Outgassing TML (weight %) | 0.11 | ASTM E595 |
| Outgassing CVCM (weight %) | 0.06 | ASTM E595 |
| Temperature Range | -45°C to 200°C | Laird Test Method |
| Rth@ 40 mils, 10 psi | 0.49°C-in2/W | ASTM D5470 (Modified) |
| Dielectric Constant @ 10 GHz | 3.6 | ASTM D150 |
| UL Flammability Rating | V-0 | UL 94 |
| Volume Resistivity | 5 x 10 ¹³ ohm-cm | ASTM D257 |

Americas: +1.866.928.8181 Europe: +49.(0).8031.2460.0 Asia: +86.755.2714.1166 www.lairdtech.com



Tputty™ 502 SeriesThermal Gap Filler

AVAILABILITY

STANDARD SHEET SIZES

- 0.5mm (0.020") to 5.0mm (0.200") thick material available in 0.25mm (0.010") increments
- Available in standard sheet sizes of 18" x 18" and 9" x 9" or custom die cut parts

REINFORCEMENT

• Tputty 502 sheets are reinforced on both sides with fiberglass

BULK

Tputty™ 502 is available in bulk form in the following sizes: 100 cc Jar 500 cc Jar 1000 cc Jar

PART NUMBER SYSTEM

- Tputty™ indicates Laird elastomeric thermal gap filler product line. Tputty 502FG2,xxx indicates Tputty 502 product line with Fiberglass
 on both sides, thickness in mils (0.001")
- EXAMPLES: Tflex™ Tputty 502FG2,040= 0.040" thick Tputty™ 502 material

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Thermal Interface Products category:

Click to view products by Laird Connectivity manufacturer:

Other Similar products are found below:

7721-9PPS FGN80-2 PFM-172-60 A-40 174-9-230P 9601-7 5300AC 1.500G 08133 V6622C TVQF-1225-07S TP0001 4860 SC80-W2 V6516C A17536-04 A17713-06 A17713-05 A17653-05 A17690-06 A17689-04 A17775-03 A17690-05 A17653-02 A17689-02 A17690-06 A17775-05 A17775-06 A17690-08 A17690-02 A17689-06 A17653-06 A17690-12 A17653-03 A17536-02 A17689-03 A17536-10 A17752-13 A17752-04 A17752-07 A17634-12 19-36565-0001-1 A17752-09 22000-001A A17752-20 A17752-16 A17752-12 A17653-04 A17634-10 A17634-09 A17634-07