



## FOR EXCEPTIONALLY LOW THERMAL RESISTANCE

The Tpcm™ 580 Series is a high-performance thermal phase change material (PCM) designed to meet the thermal reliability and price requirements of high-end thermal applications. The Series is inherently tacky, flexible and exceptionally easy-to-use. The Tpcm 580 Series is available in four thicknesses: 0.003" (Tpcm 583), 0.005" (Tpcm 585), 0.008" (Tpcm 588), 0.010" (Tpcm 5810) and 0.016" (Tpcm 5816).

At temperatures above its transition temperature of 50°C (122°F), the Tpcm 580 Series begins to soften and flow, filling the microscopic irregularities of the components it comes into contact with. The result is an interface with minimal thermal contact resistance. Due to the gradual change in viscosity (softening), it minimizes migration (pump-out).

The Tpcm 580 Series can be supplied as cut parts in strips and rolls with top tabbed liners for easy application. The top tabbed liner can be removed immediately or provide a protective cover during shipping, and can be removed at assembly. It can also be supplied in sheets and custom die-cut configurations; and meets all environmental requirements including RoHS.

## FEATURES AND BENEFITS

- Low total thermal resistance (0.013°C-in<sup>2</sup>/W at 50 psi)
- Inherently tacky and easy-to-use – no adhesive required
- High reliability
- Meets all environmental requirements including RoHS
- Provides high value price / performance point

## APPLICATIONS

- Microprocessors
- Chipsets
- Graphic processing chips
- Custom ASICS

**global solutions: local support™**

Americas: +1.888.246.9050

Europe: +46.31.704.67.57

Asia: +86.755.2714.1166

CLV-customerservice@lairdtech.com

[www.lairdtech.com/thermal](http://www.lairdtech.com/thermal)

## SPECIFICATIONS

PROPERTIES	Tpcm™ 583	Tpcm™ 585	Tpcm™ 588	Tpcm™ 5810	Tpcm™ 5816
Construction & composition	Non-reinforced film				
Color	Gray				
Thickness	0.003" (0.076 mm)	0.005" (0.127 mm)	0.008" (0.2 mm)	0.010" (0.25 mm)	0.016" (0.406 mm)
Density	2.87 g/cc				
Operating temperature range	-40°C to 125°C (-40°F to 257°F)				
Phase change softening temperature	50°C (122°F)				
Thermal resistance					
10 psi	0.019°C-in <sup>2</sup> /W (0.12°C-cm <sup>2</sup> /W)	0.020°C-in <sup>2</sup> /W (0.13°C-cm <sup>2</sup> /W)	0.020°C-in <sup>2</sup> /W (0.13°C-cm <sup>2</sup> /W)	0.020°C-in <sup>2</sup> /W (0.13°C-cm <sup>2</sup> /W)	0.025°C-in <sup>2</sup> /W (0.16°C-cm <sup>2</sup> /W)
20 psi	0.016°C-in <sup>2</sup> /W (0.10°C-cm <sup>2</sup> /W)	0.016°C-in <sup>2</sup> /W (0.10°C-cm <sup>2</sup> /W)	0.016°C-in <sup>2</sup> /W (0.10°C-cm <sup>2</sup> /W)	0.016°C-in <sup>2</sup> /W (0.10°C-cm <sup>2</sup> /W)	0.016°C-in <sup>2</sup> /W (0.10°C-cm <sup>2</sup> /W)
50 psi	0.013°C-in <sup>2</sup> /W (0.08°C-cm <sup>2</sup> /W)	0.013°C-in <sup>2</sup> /W (0.08°C-cm <sup>2</sup> /W)	0.013°C-in <sup>2</sup> /W (0.08°C-cm <sup>2</sup> /W)	0.013°C-in <sup>2</sup> /W (0.08°C-cm <sup>2</sup> /W)	0.013°C-in <sup>2</sup> /W (0.08°C-cm <sup>2</sup> /W)
Thermal conductivity	3.8 W/mK				
Volume resistivity	3.0 x 10 <sup>12</sup> ohm-cm				

## STANDARD PACKAGING

- Sheets:** 9" x 9" (228.6 mm x 228.6 mm)  
18" x 18" (457.2 mm x 457.2 mm)
- Cut Parts:** On strip with top tabbed liner  
Individual cut through

**global solutions: local support™**

Americas: +1.888.246.9050

Europe: +46.31.704.67.57

Asia: +86.755.2714.1166

THR-DS-TPCM580 1112

CLV-customerservice@lairdtech.com

[www.lairdtech.com/thermal](http://www.lairdtech.com/thermal)

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user, since Laird Technologies and its agents cannot be aware of all potential uses. Laird Technologies makes no warranties as to the fitness, merchantability or suitability of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2012 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trade marks or registered trade marks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights. Document A16819-00 Rev A

## X-ON Electronics

Largest Supplier of Electrical and Electronic Components

*Click to view similar products for [Thermal Interface Products](#) category:*

*Click to view products by [Laird Connectivity](#) manufacturer:*

Other Similar products are found below :

[7721-9PPS](#) [FGN80-2](#) [PFM-172-60](#) [A-40](#) [174-9-230P](#) [9601-7](#) [5300AC](#) [1.500G](#) [08133](#) [V6622C](#) [TVQF-1225-07S](#) [TP0001](#) [4860](#) [SC80-W2](#)  
[V6516C](#) [A17536-04](#) [A17713-06](#) [A17713-05](#) [A17653-05](#) [A17690-06](#) [A17689-04](#) [A17775-03](#) [A17690-05](#) [A17653-02](#) [A17689-02](#) [A17690-04](#) [A17775-05](#) [A17775-06](#) [A17690-08](#) [A17690-02](#) [A17689-06](#) [A17653-06](#) [A17690-12](#) [A17653-03](#) [A17536-02](#) [A17689-03](#) [A17536-10](#)  
[A17752-13](#) [A17752-04](#) [A17752-07](#) [A17634-12](#) [19-36565-0001-1](#) [A17752-09](#) [22000-001A](#) [A17752-20](#) [A17752-16](#) [A17752-12](#) [A17653-04](#)  
[A17634-10](#) [A17634-09](#) [A17634-07](#)