





# High-Loss, Non-Rigid, Magnetically Loaded Stock

#### **HIGH-LOSS NON-RIGID ABSORBER**

Eccosorb MFS is a high-loss stock based on silicone. This product was developed to overcome the physical limitations of rigid high-loss absorbers. Being flexible, Eccosorb MFS can be fitted to compound curves. It has low outgassing properties for space applications.



#### **FEATURES AND BENEFITS**

- Flexible structure for improved fit
- Low outgassing for space applications
- · Good adhesion to metals during to cycling due to elastomeric properties

#### **MARKETS**

- · Commercial Telecom
- · Security and Defense

#### **SPECIFICATIONS**

TYPICAL PROPERTIES	ECCOSORB MFS
Frequency Range	1 – 18 GHz
Service Temperature °C (°F)	<160 (< 320)
Density g/cc	4.15 – 4.3
Hardness, Shore A	>70
Volume Resistivity ohm-cm	10 <sup>10</sup>
Thermal Expansion per °C	63 x 10 <sup>-6</sup>
Thermal Conductivity W/mK	0.865
Water Absorption % 24 Hours	<0.1
Dielectric Strength volts/mil	>10

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

### **APPLICATIONS**

- Eccosorb MFS is engineered for terminations, loads, attenuators in microwave circuits, and in waveguides and transmission systems.
- It can be bonded to low-expansion-coefficient ceramics, such as sintered ferrites.

#### **AVAILABILITY**

- Eccosorb MFS is available in two types, Eccosorb® MFS-117 and Eccosorb® MFS-124
- Sheets: 30.5cm x 30.5cm (12" x 12") in thicknesses of 0.32cm (1/8"), 0.64cm (1/4"), 1.27cm (1/2") & 2.54cm (1.0")
- Bars: 30.5cm long (12") in squares of 0.64, 1.27, 2.54 cm (1/4, 1/2, 1.0").
- It can be supplied with a Pressure Sensitive Adhesive (PSA).
- Available in other thicknesses, sizes, and customer specified shapes upon request

## **INSTRUCTION FOR USE**

• Can be cut with a sharp knife, sawed, sanded, and ground to form pyramids, cones and other machines parts. Magnetic holding devices can be used for machine operations.

Americas: +1.866.928.8181 Europe: +49.(0)8031.2460.0 Asia: +86.755.2714.1166



### **TEMPERATURE CYCLING**

Many rigid materials cannot be bonded to metal surfaces and then temperature cycled. Temperature changes break this bond. This is due to the difference in the thermal expansion coefficient between the metal and the load material. Since Eccosorb MFS is a true elastomer, it deforms slightly to accommodate dimensional changes. In addition, a pyramid or wedge of Eccosorb MFS can be bonded over a large area to a waveguide wall to improve heat dissipation.

## **Typical Electrical Properties**

	GHz	10 <sup>-7</sup>	<b>10</b> -6	<b>10</b> -5	10-4	<b>10</b> -3	10 <sup>-2</sup>	10 <sup>-1</sup>	1.0	3.0	8.6	10.0	18.0
MFS-117	K'	195	158	120	85	62	48	38	28	22.9	21.4	21	20.6
	$tan \; \delta_d$	0.18	0.21	0.23	0.24	0.22	0.18	0.12	0.09	0.06	0.02	0.02	0.02
	K"	35	33	28	20	14	8.6	4.6	2.5	1.4	0.42	0.42	0.41
	M'	5	5	5	5	5	5	4.8	4.1	3.4	1.2	1.1	1
	$tan \; \delta_m$	0	0	0	0	0	0	0.1	0.2	0.39	1.36	1.5	2
	Μ"	0	0	0	0	0	0	0.48	0.82	1.33	1.63	1.7	2
	dB/cm	0	0	0	0	0	0.03	0.27	2.8	11	46	56	119
	dB/in	0	0	0	0	0	0.08	0.69	7.1	28	117	142	302
	IZI/Z <sub>0</sub>	0.16	0.18	0.2	0.24	0.28	0.32	0.36	0.39	0.4	0.3	0.31	0.33
MFS-124	K'	260	205	145	95	70	52	40	32	25.8	23.8	23.6	23
	$tan \; \delta_d$	0.4	0.39	0.36	0.31	0.26	0.2	0.14	0.08	0.07	0.05	0.03	0.04
	K"	104	80	52	29	18	1	5.6	2.6	1.8	1.19	0.71	0.92
	М'	7	6.9	6.8	6.7	6.6	6.3	6	5	3.8	2.5	1.5	1
	$tan \; \delta_m$	0	0	0	0	0	0	0.2	0.45	0.69	1.1	1.4	2.5
	М"	0	0	0	0	0	0	1.2	2.3	2.62	2.75	2.1	2.5
	dB/cm	0	0	0	0	0	0.03	0.48	6.5	20	63	67	149
	dB/in	0	0	0	0	0	0.08	1.2	16.51	50	160	170	378
	IZI/Z <sub>0</sub>	0.16	0.18	0.21	0.26	0.3	0.34	0.39	0.42	0.42	0.39	0.33	0.34

<sup>\*</sup>Note: Attenuation is a theoretical property calculated from the Complex Permittivity and Complex Permeability of a lossy material and is strictly a means of comparing one absorbing material to another. The attenuation properties are not an indication of how the material will perform inside a microwave device. The frequencies of use recommended for Eccosorb® MFS-117 & Eccosorb® MFS-124 in the Typical Properties Table of this bulletin are based on application experience at Laird.

## **Typical Electrical Properties Legend**

K'	Real part of the permittivity (dielectric constant)
$tan \; \delta_d$	Dielectric loss tangent
K"	Imaginary part of the permittivity (loss)
M'	Real part of the magnetic permeability
$tan\;\delta_m$	Magnetic loss tangent
М"	Imaginary part of the magnetic permeability (loss)
dB/cm	Attenuation per unit distance
dB/in	Attenuation per unit distance
IZI/Z <sub>0</sub>	Normalized impedance magnitude ratio

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for EMI Gaskets, Sheets, Absorbers & Shielding category:

Click to view products by Laird Performance Materials manufacturer:

Other Similar products are found below:

23-76FSC-SN-24 2-1616323-1 4-1616259-0 3013350A 46J8501020.NN00 3013310A 3013325A 3013308A 3020604 55005106 3021302 3031313 67SLH050050025PI00 3021310 0137131400 6-34UT-070-BD-16 303076048 46J5N03020.NN00 30206025 260737 30395641 3030403 3690103020 HNY-LT15CU4241 46X7503020.NN00 46X7501020.NN00 46W5E02520.NN00 46W5E01520.NN00 302095032 30207032 30210005 46J5N02520.NN00 3021213 3020804 3021004 74273711 74273704 33403 3031210 3031008 3031004 3030903 30308055 303076016 303045018 303035015 3029564 3025602 3023502 3022303