



LOSSY, FLEXIBLE FOAM ABSORBER

Eccosorb LS is the most widely known, used, and recommended polyurethane foam absorber. Eccosorb LS obtains its microwave properties via impregnation with a carbon black dispersion and is therefore electrically conductive. It is a very low cost solution for many applications over the thinner, more expensive rubber absorbers.

FEATURES AND BENEFITS

- Flexible, foam material
- High loss, low density
- Very low cost

MARKETS

- Commercial Telecom
- Test Boxes
- Security and Defense

SPECIFICATIONS

TYPICAL PROPERTIES	ECCOSORB LS
Max. Service Temperature °C (°F)	90 (194)
Frequency Range	≥ 1 GHz

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

	Attenuation (dB/cm)		Relative Impedance (Z /Z ₀)	
	3 GHz	10 GHz	3 GHz	10 GHz
LS-14	1.0	1.7	0.83	0.89
LS-16	1.5	2.3	0.78	0.87
LS-18	3.2	4.7	0.69	0.82
LS-20	4.2	7.0	0.61	0.78
LS-22	7.4	14.9	0.55	0.74
LS-24	11	24	0.25	0.44
LS-26	16	34	0.18	0.31
LS-28	20	40	0.16	0.27
LS-30	24	46	0.13	0.22

APPLICATIONS


- Eccosorb LS is used to lower cavity Q's in RF amplifiers, oscillators, cabinets containing microwave devices, computer housings, LNB's and isolation of antennas by insertion loss.
- Eccosorb LS is also used to reduce surface currents on radiating elements and outer ground-plane type surfaces.
- Reflectivity of an object (metal or otherwise) can be reduced somewhat by applying one or more layers of Eccosorb LS to its surface.

AVAILABILITY

- Standard sheets are 610mm x 610mm (24"x24").
- Standard thicknesses are 3.2 mm (1/8"), 6.4 mm (1/4"), 9.5 mm (3/8"), 12.7 mm (1/2"), 19.1 mm (3/4").
- All Eccosorb LS types can be delivered in special sizes or customer specified configurations upon request. This includes die-cut and kiss cut parts to reduce installation labor by allowing quick assembly.
- Usually Eccosorb LS is supplied with a pressure sensitive adhesive.
- Upon special request, Eccosorb LS can be supplied with an anti-dust coating to prevent carbon fallout.
- It can also be supplied, upon request, with a coating to prevent moisture uptake in high humidity to moderately wet environments.

INSTRUCTIONS FOR USE

- For optimal performance, Eccosorb LS should be bonded to a metallic surface.
- To obtain a strong bond, the surface should be thoroughly cleaned with a degreasing solvent.
- It can be securely bonded to itself or to other materials such as metal, wood and common plastic composites. Our specific Eccostock® foam adhesive is recommended or the self-adhesive version can be used.
- The material can be easily cut with a sharp knife, scissors or die.



X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [EMI Gaskets, Sheets, Absorbers & Shielding](#) *category:*

Click to view products by [Laird Performance Materials](#) *manufacturer:*

Other Similar products are found below :

[23-76FSC-SN-24](#) [2-1616323-1](#) [4-1616259-0](#) [3013350A](#) [46J8501020.NN00](#) [3013310A](#) [3013325A](#) [3013308A](#) [3020604](#) [55005106](#) [3021302](#)
[3031313](#) [67SLH050050025PI00](#) [3021310](#) [0137131400](#) [6-34UT-070-BD-16](#) [303076048](#) [46J5N03020.NN00](#) [30206025](#) [260737](#) [30395641](#)
[3030403](#) [3690103020](#) [HNY-LT15CU4241](#) [46X7503020.NN00](#) [46X7501020.NN00](#) [46W5E02520.NN00](#) [46W5E01520.NN00](#) [302095032](#)
[30207032](#) [30210005](#) [46J5N02520.NN00](#) [3021213](#) [3020804](#) [3021004](#) [74273711](#) [74273704](#) [33403](#) [3031210](#) [3031008](#) [3031004](#) [3030903](#)
[30308055](#) [303076016](#) [303045018](#) [303035015](#) [3029564](#) [3025602](#) [3023502](#) [3022303](#)