

### PRODUCT DESCRIPTION

Laird Tputty™ 508 is a single part dispensable material designed with automation and vertical stability in mind. Laird has leveraged its knowledge of thermally conductive fillers and resin systems to develop a single part dispensable that demonstrates reliability in a variety of application orientations.

Tputty™ 508 is ideal for applications that can benefit from automation, and allows minimization of SKUs in applications with gap variability. In addition to providing application flexibility and variable gap adaptation, Tputty™ 508 will exert minimum stress on your component while maintaining interface contact to maximize thermal transfer. Combined with Laird's global technical support and global footprint, deploying Tputty™ 508 is easier than ever.

### FEATURES AND BENEFITS

- RoHS Compliant
- Complete Dispensing Solution Options Available
- 3.7 W/mK
- Demonstrated thermal cycling stability
- Low outgassing per ASTM E595
- Available in cartridges (75cc, 180cc, 360cc, 600cc) and pails (1 gallon and 5 gallon)

Packaging Size	Fill Volume	Fill Weight
<b>75cc (2.5 oz)</b>	56cc	177g
<b>180cc (6 oz)</b>	159cc	503g
<b>360cc (12 oz)</b>	326cc	1030g
<b>600cc (20 oz)</b>	601cc	1900g
<b>1 gallon</b>	4110cc	13kg
<b>5 gallon</b>	6320cc	20kg

### SPECIFICATIONS

PROPERTY	TYPICAL VALUE	METHOD
<b>Construction</b>	Ceramic filled silicone dispensable	N/A
<b>Color</b>	Green	Visual
<b>Thermal Conductivity (w/mK)</b>	3.7	Hot Disk
<b>Flow Rate (75cc taper tip, 0.125" orifice, 40 psi)</b>	50 g/min	Laird Test Method – A16724-00
<b>Density (g/cc)</b>	3.2	Helium Pycnometer
<b>Flammability</b>	V-0	UL 94
<b>Temperature Range</b>	-40 to 150°C	Laird Test Method
<b>Outgassing TML (weight %)</b>	0.04	ASTM E595
<b>Outgassing CVCM (weight %)</b>	0.01	ASTM E595
<b>Dielectric Breakdown</b>	>3000 VAC	ASTM D149
<b>Dielectric Constant @ 1MHz</b>	8.62	ASTM D150
<b>Minimum Bond line Thickness</b>	0.09 mm (0.0036")	Laird Test Method -A16112-00
<b>Volume Resistivity (ohm-cm)</b>	10 <sup>13</sup>	ASTM D257

Americas: +1.866.928.8181  
Europe: +44.(0).8031.2460.0  
Asia: +86.755.2714.1166

## X-ON Electronics

Largest Supplier of Electrical and Electronic Components

*Click to view similar products for [Thermal Interface Products](#) category:*

*Click to view products by [Laird Performance Materials](#) manufacturer:*

Other Similar products are found below :

[7721-9PPS](#) [FGN80-2](#) [PFM-172-60](#) [A-40](#) [174-9-230P](#) [9601-7](#) [5300AC](#) [1.500G](#) [08133](#) [V6622C](#) [TVQF-1225-07S](#) [TP0001](#) [4860](#) [SC80-W2](#)  
[V6516C](#) [A17713-06](#) [A17713-05](#) [A17653-05](#) [A17690-06](#) [A17775-03](#) [A17690-05](#) [A17653-02](#) [A17689-02](#) [A17690-04](#) [A17775-05](#) [A17775-](#)  
[06](#) [A17690-08](#) [A17690-02](#) [A17689-06](#) [A17653-06](#) [A17690-12](#) [A17653-03](#) [A17536-02](#) [A17689-03](#) [A17536-10](#) [A17752-13](#) [A17752-04](#)  
[A17752-07](#) [A17634-12](#) [19-36565-0001-1](#) [A17752-09](#) [22000-001A](#) [A17752-20](#) [A17752-16](#) [A17752-12](#) [A17653-04](#) [A17634-10](#) [A17634-09](#)  
[A17634-07](#) [A17633-20](#) [A17633-07](#)