



PRODUCT DESCRIPTION

Laird Tputty[™] 607 is a high thermally conductive single part dispensable material designed with automation and vertical stability in mind. Laird has leveraged its knowledge of thermally conductive fillers and resin systems to develop a single part dispensable that demonstrates reliability in a variety of application orientations.

Tputty[™] 607 is ideal for applications that can benefit from automation and allows minimization of SKUs in applications with gap variability. In addition to providing application flexibility and variable gap adaptation, Tputty[™] 607 will exert minimal stress on your component while maintaining interface contact to maximize thermal transfer. Combined with Laird's global technical support and global footprint, deploying Tputty[™] 607 is easier than ever.

When it is time to integrate Tputty[™] 607 into your production environment, Laird can work with your existing dispensing partner or provide recommendations for a dispensing equipment provider.

FEATURES AND BENEFITS

- RoHS Compliant
- Complete Dispensing Solution Options Available
- 6.4 W/mK
- Demonstrated thermal cycling stability
- Low outgassing per ASTM E595
- Available in cartridges (75cc, 180cc, 360cc, 600cc) and pails (1 gallon and 5 gallon)

Packaging Size	Fill Volume	Fill Weight
75cc (2.5 oz)	56cc	193g
180cc (6 oz)	159cc	549g
360cc (12 oz)	326cc	1242g
600cc (20 oz)	601cc	2070g
1 gallon	3768cc	14kg
5 gallon	5797cc	20kg

Americas: +1.866.928.8181
Europe: +44.(0).8031.2460.0
Asia: +86.755.2714.1166

www.lairdtech.com

THR-DS-Tputty 607 12-11-18

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2013 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights.

SPECIFICATIONS

PROPERTY	TYPICAL VALUE	METHOD
Construction	Ceramic filled silicone dispensable	N/A
Color	Blue	Visual
Thermal Conductivity (W/mK)	6.4	Hot Disk
Flow Rate (75cc taper tip, 0.125" orifice, 90 psi)	60 g/min	Laird Test Method – A16724-00
Density (g/cc)	3.45	Helium Pycnometer
Flammability	V-0	UL 94
Temperature Range	-40 to 150°C	Laird Test Method
Outgassing TML (weight %)	0.204	ASTM E595
Outgassing CVCN (weight %)	0.01	ASTM E595
Dielectric Breakdown	>6000 VAC (at 40 mil)	ASTM D149
Dielectric Constant @ 1MHz	15.0	ASTM D150
Minimum Bond line Thickness	0.150 mm (0.006")	Laird Test Method - A16112-00
Volume Resistivity (ohm-cm)	10 ¹³	ASTM D257

Americas: +1.866.928.8181
 Europe: +44.(0).8031.2460.0
 Asia: +86.755.2714.1166

www.lairdtech.com

THR-DS-Tputty 607 12-11-18

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2013 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [Thermal Interface Products](#) category:

Click to view products by [Laird Performance Materials](#) manufacturer:

Other Similar products are found below :

[7721-9PPS](#) [FGN80-2](#) [PFM-172-60](#) [A-40](#) [174-9-230P](#) [9601-7](#) [5300AC](#) [1.500G](#) [08133](#) [V6622C](#) [TVQF-1225-07S](#) [TP0001](#) [4860](#) [SC80-W2](#)
[V6516C](#) [A17536-04](#) [A17713-06](#) [A17713-05](#) [A17653-05](#) [A17690-06](#) [A17689-04](#) [A17775-03](#) [A17690-05](#) [A17653-02](#) [A17689-02](#) [A17690-04](#) [A17775-05](#) [A17775-06](#) [A17690-08](#) [A17690-02](#) [A17689-06](#) [A17653-06](#) [A17690-12](#) [A17653-03](#) [A17536-02](#) [A17689-03](#) [A17536-10](#)
[A17752-13](#) [A17752-04](#) [A17752-07](#) [A17634-12](#) [19-36565-0001-1](#) [A17752-09](#) [22000-001A](#) [A17752-20](#) [A17752-16](#) [A17752-12](#) [A17653-04](#)
[A17634-10](#) [A17634-09](#) [A17634-07](#)