

## MATERIAL SPECIFICATIONS FOR BS2775:1987

\*\*\*\*\*

PROPERTY	NATURAL RUBBER	CHOLOROPRENE	SILICONE
COLOUR	RED	GREY/BLACK	TRANSLUCENT
HARDNESS (IRHD)	46-55	46-55	46-55
TENSILE STRENGTH (MP) MIN	10	10	6
ELONGATION AT BREAK	400	350	300
COMPRESSION SET (% MAX 70 DEG C	30	30	-40 AT 150C
CHANGES IN PROPERTIES AFTER ACCELERATED AGEING PROPERTY			
CHANGE IN HARDNESS (IRHD)	-0 +5	-0 +10	-0 +10
CHANGE IN TENSILE STRENGTH % MAX	-25	-15	-25
CHANGE IN ELONGATION AT BREAK (%)	-25	-30	-30

ADDITIONAL INFORMATION:

THE ABOVE CONFORMS TO FDA-177 -2600 RUBBER ARTICLES INTENDED FOR REPEATED USE.

## **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

*Click to view similar products for [ley holdings](#) manufacturer:*

Other Similar products are found below :

[Ley Holdings](#)