

PRODUCT SPECIFICATION

Rechargeable Lithium Ion Battery

Model : INR18650 M36T 12.50Wh

Revision History

| Revision | Date | Originator | Description |
|----------|------------|----------------|-------------------------------------|
| 0 | 2017-05-26 | Kim, Yong-Hoon | Draft |
| 1 | 2017-10-18 | Kim, Yong-Hoon | Add contents of General Information |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |

Contents

| | |
|---|-----------|
| Contents | 3 |
| 1. General Information | 4 |
| 1.1 Scope | |
| 1.2 Product Classification | |
| 1.3 Model Name | |
| 2. Nominal Specification | 4 |
| 2.1 Energy | |
| 2.2 Nominal Voltage | |
| 2.3 Nominal Shipping SOC | |
| 2.4 Standard Charge | |
| 2.5 Max. Charge Voltage | |
| 2.6 Max. Charge Current | |
| 2.7 Standard Discharge | |
| 2.8 Max. Pulse Discharge Power | |
| 2.9 Max. Discharge Current | |
| 2.10 Weight | |
| 2.11 Storage Temperature (for shipping state) | |
| 3. Appearance and Dimension | 5 |
| 3.1 Appearance | |
| 3.2 Dimension | |
| 4. Performance Specification | 6 |
| 4.1 Measuring Equipment | |
| 4.2 Standard Test Condition | |
| 4.3 Electrical Specification | |
| 4.4 Environmental Specification | |
| 4.5 Mechanical Specification | |
| 4.6 Safety Specification | |
| 5. Caution | 10 |
| 5.1 Cautions for Use and Handling | |
| 5.2 Prohibitions | |
| 5.3 Caution for the battery and the pack | |
| 6. Exclusion of Liability | 13 |

1. General Information

1.1 Scope

This product specification defines the requirements of the rechargeable lithium ion battery to be supplied to the Customer by LG Chem.

1.2 Application : Electric Vehicle

1.3 Product classification : Cylindrical rechargeable lithium ion battery

1.4 Model name : INR18650 M36T

2. Nominal Specification

| Item | Condition / Note | Specification |
|--|--|------------------------------------|
| 2.1 Energy | Std. charge / discharge | Nominal 12.50Wh Minimum 12.10Wh |
| 2.2 Nominal Voltage | Average | 3.63V |
| 2.3 Nominal Shipping SOC | | 30% |
| 2.4 Standard Charge (Refer to 4.2.1) | Constant current Constant voltage End current(Cut off) | 0.3C (1,000mA) 4.2V 50mA |
| 2.5 Max. Charge Voltage | | 4.20 ± 0.05V |
| 2.6 Max. Charge Current | 0 ~ 24°C | 0.3C (1,000mA) |
| | 24 ~ 50°C | 0.7C (2,330mA) |
| 2.7 Standard Discharge (Refer to 4.2.2) | Constant current End voltage(Cut off) | 0.2C (670mA) 2.50V |
| 2.8 Max. Pulse Discharge Power | Pulse Power(10sec), 24 °C ± 2 °C | ≤ 80W (SOC 80%) |
| 2.9 Max. Discharge Current | -30 ~ -20°C | 0.2C(670mA) |
| | -20 ~ 5°C | 0.3C(1,000mA) |
| | 5 ~ 45°C | 1.5C(5,000mA) |
| | 45 ~ 60°C | 1.5C(5,000mA) |
| 2.10 Weight | With Tube | 48.2 ± 1.0 g |
| 2.11 Storage Temperature (for shipping state) | 1 day | -40°C |
| | 1 month | -20 ~ 60°C |
| | 3 months | -20 ~ 45°C |
| | 1 year | -20 ~ 20°C |

3. Appearance and Dimension

3.1 Appearance


There shall be no such defects as deep scratch, crack, rust, discoloration or leakage, which may adversely affect the commercial value of the cell.

3.2 Dimension

Diameter : ≤ 18.51 mm

Diameter is defined as the largest data value measured on the "A" area of a cylindrical cell

Height : ≤ 65.60 mm



4. Performance Specification

4.1 Measuring Equipment

| Item | Maker | Accuracy | Resolution |
|------------------|------------------------|--|--|
| Cycler | ETH (BATESTER) | Voltage : $\pm 0.02\%$ Current : $\pm 0.05\%$ | Voltage : $\pm 1\text{mV}$ Current : $\pm 1\text{mA}$ |
| Electronic scale | AND (HR-200) | $\pm 0.3\text{mg}$ | 4 digits (0.1mg) |
| Vernier Calipers | Mitsutoyo (500-182-20) | $\pm 0.02\text{mm}$ | 2 digits (0.01mm) |

4.2 Standard test condition

4.2.1 Standard Charge

Unless otherwise specified, "Standard Charge" shall consist of charging at constant current of 0.3C. The cell shall then be charged at constant voltage of 4.20V while tapering the charge current. Charging shall be terminated when the charging current has tapered to 50mA. For test purposes, charging shall be performed at $24^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

4.2.2 Standard Discharge

"Standard Discharge" shall consist of discharging at a constant current of 0.2C to 2.50V. Discharging is to be performed at $24^{\circ}\text{C} \pm 2^{\circ}\text{C}$ unless otherwise noted (such as capacity versus temperature).

4.2.3 Charge / discharge condition (I)

Cells shall be charged at constant current of 0.3C to 4.10V with end current of 1/20C. Cells shall be discharged at constant current of 0.5C to 2.85V. Cells are to rest 10 minutes after charge and 20 minutes after discharge at $24^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

4.3 Electrical Specification

| Item | Condition | Specification |
|--------------------------------|--|--|
| 4.3.1 Initial AC Impedance | Cell shall be measured at 1kHz after charge per 4.2.1. | $\leq 30 \text{ m}\Omega$, without PTC |
| 4.3.2 Initial DC Resistance | Cell shall be charged per 4.2.1 and discharged to the SOC (states of charge) 50%. Measurement of internal impedance under DC loads at constant current of 0.5C for 30 sec at $24 \text{ }^\circ\text{C} \pm 2 \text{ }^\circ\text{C}$. | $36 \pm 6 \text{ m}\Omega$, without PTC |
| 4.3.3 Initial Energy | Cells shall be charged per 4.2.1 and discharged per 4.2.2 within 1h after full charge. | $\geq 12.10 \text{ Wh}$ |
| 4.3.4 Cycle Life | Cells shall be charged and discharged per 4.2.3 for 1000 cycles. A cycle is defined as one charge and one discharge. 1001st discharge energy shall be measured per 4.2.1 and 4.2.2. | $\geq 80\%$ (of Wh_{\min} in 2.1) |

4.4 Environmental specification.

| Item | Condition | | Specification |
|---|--|------------------------------|---|
| 4.4.1 Storage Characteristics | Cells shall be charged per 4.2.1 and stored in a temperature-controlled environment at 24°C ± 2°C for 30 days. After storage, cells shall be discharged per 4.2.2 to obtain the remaining energy*. | | Energy remaining rate ≥ 90% (Wh _{min} in 2.1) |
| 4.4.2 High Temperature Storage Test | Cells shall be charged per 4.2.1 and stored in a temperature-controlled environment at 60°C for 1 week. After storage, cells shall be discharged per 4.2.2 and cycled per 4.2.3 for 3 cycles to obtain recovered energy**. | | No leakage, Energy recovery rate ≥ 80% |
| 4.4.3 Thermal Shock Test | 65°C (8h) ← 3hrs → -20°C (8h) for 8 cycles with cells charged per 4.2.1 After test, cells are discharged per 4.2.2 and cycled per 4.2.3 for 3 cycles to obtain recovered energy. | | No leakage Energy recovery rate ≥ 80% |
| 4.4.4 Temperature Dependency of Capacity | Cells shall be charged per 4.2.1 at 24°C ± 2°C and discharged per 4.2.2 at the following temperatures. | | |
| | Charge | Discharge | Energy |
| | 24°C | -10°C 0°C 24°C 60°C | 70% of Wh _{ini} 80% of Wh _{ini} 100% of Wh _{ini} 95% of Wh _{ini} |

* Remaining Energy : After storage, cells shall be discharged with Std. condition(4.2.2) to measure the remaining capacity.

** Recovery Energy : After storage, cells shall be discharged with fast discharge condition(4.2.3), and then cells shall be charged with std. charge condition(4.2.1), and then discharged with Std. condition(4.2.2). This charge / discharge cycle shall be repeated three times to measure the recovery capacity.

4.5 Mechanical Specification

| Item | Condition | Specification |
|-------------------------|---|-------------------------------------|
| 4.5.1 Drop Test | Cells charged per 4.2.1 are dropped onto an wooden floor from 1.0 meter height for 1 cycle, 2 drops from each cell terminal and 1drop from the side of cell can (Total number of drops = 3). | No leakage No temperature rising |
| 4.5.2 Vibration Test | Cells charged per 4.2.1 are vibrated for 90 minutes per each of the three mutually perpendicular axis (x, y, z) with total excursion of 0.8mm, frequency of 10Hz to 55Hz and sweep of 1Hz change per minute | No leakage |

4.6 Safety Specification

| Item | Condition | Specification |
|--|--|-----------------------|
| 4.6.1 Overcharge Test | Cells are discharged per 4.2.2, then charged at constant current of 3 times the max. charge condition and constant voltage of 4.2V while tapering the charge current. Charging is continued for 7 hours. | : No explode, No fire |
| 4.6.2 External Short - Circuiting Test | Cells are charged per 4.2.1, and the positive and negative terminal is connected by a 100m Ω -wire for 1 hour. | : No explode, No fire |
| 4.6.3 Over-discharge* Test | Cells are discharged at constant current of 0.2C to 250% of the minimum capacity. | : No explode, No fire |
| 4.6.4 Heating Test | Cells are charged per 4.2.1 and heated in a circulating air oven at a rate of 5°C per minute to 130°C. At 130°C, oven is to remain for 10 minutes before test is discontinued. | : No explode, No fire |

*Over-discharge : Cell must not be recharged after dropping down below 1.0V and must be recharged with low C-rate less than 0.3C if it experienced an over-discharge above 1.0V.

5. Caution

Warning for using the lithium ion rechargeable battery. Mishandling of the battery may cause heat, fire and deterioration in performance. Be sure to observe the following.

5.1 Cautions for Use and Handling

- When using the application equipped with the battery, refer to the user's manual before usage.
- Please read the specific charger manual before charging.
- Charge time should not be longer than specified in the manual.
- When the cell is not charged after long exposure to the charger, discontinue charging.
- Battery must be charged at operating temperature range 0 ~ 45°C.
- Battery must be discharged at operating temperature range -20 ~ 60°C.
- Please check the positive(+) and negative(-) direction before packing.
- When a lead plate or wire is connected to the cell for packing, check out insulation not to short-circuit.
- Battery must be stored separately.
- Battery must be stored in a dry area with low temperature for long-term storage.
- Do not place the battery in direct sunlight or heat.
- Do not use the battery in high static energy environment where the protection device can be damaged.
- When rust or smell is detected on first use, please return the product to the seller immediately.
- The battery must be away from children or pets
- When cell life span shortens after long usage, please exchange to new cells.
- Do insulate between the metal plate and cell or other components not to make a electrical short.
- When use cells for an assembly of module or pack, the "first-in, first-out" (FIFO) principle should be applied
- The cells should be handled and used in Pack/System manufacturing companies only.
- The cells should be sold only to Battery Pack Maker(s) or System Integrator(s). The cells should not be handled by individual consumers and should not be sold to individual consumers by individual markets. (especially, the cells are strictly prohibited to be used for any kinds of E-cigarette devices).
- Be sure to request and confirm the most current product specifications in advance which explain the specifications in detail, before the final stage of your design, purchasing or use for any application.

5.2 Prohibitions

- Do not use different charger. Do not use cigarette jacks (in cars) for charging.
- Do not charge with constant current more than maximum charge current.
- Do not disassemble or reconstruct the battery.
- Do not remove the tube and washer the battery.
- Do not pierce a hole in the battery with sharp things. (such as nail, knife, pencil, drill)

-
- Do not use with other batteries or cells.
 - Do not solder on battery directly.
 - Do not press the battery with overload in manufacturing process, especially ultrasonic welding.
 - Do not use old and new cells together for packing.
 - Do not expose the battery to high heat. (such as fire)
 - Do not put the battery into a microwave or high pressure container.
 - Do not use the battery reversed.
 - Do not connect positive(+) and negative(-) with conductive materials (such as metal, wire)
 - Do not allow the battery to be immersed in or wetted with water or sea-water.

5.3 Caution for the battery and the pack

Pack shall meet under condition to maintain battery safety and last long performance of the lithium rechargeable cells.

5.3.1 Installing the battery into the pack

- . The cell should be inspected visually before battery assembly into the pack.
- . Damaged cell should not be used. (damaged surface, can-distortion, electrolyte-smell)
- . Different Lot Number cells should not be packaged into the same pack.
- . Different types of cells, or same types but different cell maker's should not be used together.

5.3.2 Design of battery pack

- . The battery pack should not be connected easily to any charger other than the dedicated charger.
- . The battery pack has function not to cause external short cut easily.
- . The design of battery pack and its structure should be reviewed physically, mechanically and electrically not to cause cell imbalance.
- . The battery pack for multiple cells should be designed to monitor the voltage of each bank.

5.3.3 Charge

- . Charging method is Constant Current-Constant Voltage (CC/CV).
- . Charging should be operating under maximum charge voltage and current which is specified in the product specification. (Article. 2.4, 2.5)
- . The battery should be charged under operating temperature specified in the product specification. (Article. 2.9)

5.3.4 Discharge

- . Discharging method is Constant Current (CC).

(In case of using the battery for mobile equipment, discharging mode could be Constant Power.)

- Discharging should be operating under maximum discharge current which is specified in the product specification. (Article. 2.7)
- Discharging should be done by cut off voltage which is specified in the product specification. (Article. 2.6)
- The battery should be discharged under operating temperature specified in the product specification. (Article. 2.9)

5.3.5 Protection Circuit

- When battery packs for any applications are assembled with cells, following functions must be designed into the battery packs and/or in the charger or charging adapter. The detailed levels, values, conditions for each following functions should be referring to the contents specified in this Product Specification. If one or more than one function is/are to be omitted, the Packer Company (and/or System integration company) must be informing to LG Chem's or to LG Chem's sales Agent company. Without informing to LGC, LGC will not be liable for any field quality issues happened due to exclusion of following functions.

- (1) Over voltage protection circuit
- (2) Under voltage protection circuit
- (3) Over Charge current protection circuit
- (4) Over Discharge current protection circuit
- (5) Short circuit protection
- (6) Over Temperature protection circuit
- (7) 2nd over voltage protection
- (8) FET failure protection (in case FET is out of order)
- (9) Cell imbalance protection circuit (only for battery packs assembled with more than one cell)
- (10) Cell Voltage balancing function (only for battery packs assembled with more than one cell)

6. Exclusion of Liability

The warranty shall not cover defects caused by normal wear and tear, inadequate maintenance, handling, storager faulty repair, modification to the battery or pack by a third party other than LGC or LGC's agent approved by LGC, Failure to observe the product specification provided herein or improper use of installation, including but not limited to, the following:

- Damage during transport or storage
- Incorrect installation of battery into pack or maintenance
- Use of battery or pack in inappropriate environment
- Improper, inadequate, or incorrect charge, discharge or production circuit other than stipulated herein
- Incorrect use or inappropriate use

- Insufficient ventilation
- Ignoring applicable safety warnings and instructions
- Altering of attempted repairs by unauthorized personnel
- In case of force majeure (Ex. Lightning, Storm, Flood, fire, Earthquake, Etc)

There are no warranties – Implied or express – Other than those stipulated herein. LG chem. Shall not be liable for any consequential or indirect damages arising of in connection with the product specification, battery or pack.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [Battery Packs](#) category:

Click to view products by [LG](#) manufacturer:

Other Similar products are found below :

[2280309-1](#) [R101-B](#) [4114 210 501](#) [4120 210 501](#) [4600 726 406](#) [4610 726 406](#) [312G-U1](#) [55615703012](#) [3LR12](#) [4103 210 392](#) [4103 210 394](#)
[4106 210 392](#) [4106 210 394](#) [4223 210 501](#) [4606 726 406](#) [4607 726 406](#) [ZA13](#) [LR03/AAA/MN2400\(K4\)](#) [LR03 MAXELL S4](#) [LR1130](#)
[MAXELL B10](#) [LR14-MN1400-C K2](#) [LR1/910A](#) [LR41 MAXELL B10](#) [LR43](#) [LR43 MAXELL B10](#) [LR6 MAXELL S4](#) [11012](#) [E23A](#) [E90](#)
[625302](#) [625304](#) [637871](#) [638006](#) [6LF22/9V/MN1604\(K1\)C&B](#) [6LF22/9V/MN1604 PLUS](#) [6LR61](#) [SR626SW MAXELL](#) [SR920SW](#)
[MAXELL](#) [7K67 J](#) [55615303059](#) [GP14A S2](#) [GP15E](#) [GP1604GLF-2UE1](#) [GP 1604 ULTRA PLUS](#) [23733](#) [10 ET](#) [675 ET](#) [11A B5](#) [A544](#) [A76-](#)
[U10](#)