

4901



Sn99 No-Clean Solder Wire

4901 is a solder wire for electronics. It uses a high-purity eutectic Sn99.3/Cu0.7 alloy, with a no-clean, synthetically refined, splatter-proof resin flux core. Sn99 solder is a great lead-free alternative to leaded solders. It is a suitable and less costly replacement for SAC305.

It achieves a consistent solder and flux percentage due to our state-of-the-art extrusion wire-drawing machine, which continuously monitors the wire to prevent voids and ensure consistency,



Features & Benefits

- Eutectic alloy (liquidus=solidus temperature)
- Alloy exceeds J-STD-006C and meets ASTM B 32 purity requirements
- Flux meets J-STD-004B
- Resin spreads like rosin-activated flux
- Virtually non-splattering
- Non-corrosive and non-conductive
- Halide-free
- Suitable for Use in Food Facilities as a Non-Food Chemical—Canadian and NFS recognition letters available on request

Available Packaging

Cat. No.	Packaging	Gauge	Diameter	Net Wt.
4901-112G	Spool	21	0.032"	112 g
4901-227G	Spool	21	0.032"	227 g
4901-454G	Spool	21	0.032"	454 g

Contact Information

MG Chemicals, 1210 Corporate Drive
Burlington, Ontario, Canada L7L 5R6

Email: support@mgchemicals.com

Phone: North America: +(1)800-340-0772

International: +(1) 905-331-1396

Europe: +(44)1663 362888

Properties

Flux Classification	RELO
Flux Type	Resin
Flux Activity	Low
Copper Mirror	No removal
Corrosion Test	Pass
Electromigration	Pass
Silver Chromate—Cl ⁻ + Br ⁻	Pass
Flux Residue Dryness	Pass
Acid Number (mgKOH/g sample)	190–210
Softening Point of Flux Extract	24 °C
Solder Spread	130 mm ²
Splitting of Flux-Cored Wire Solder	0.30 %
Halides (by weight)	<0.05 %
Post Reflow Flux Residue	55 %
Surface Insulation Resistance (SIR)	2.3 x 10 ¹¹ Ω
Bellcore (Telecordia)	6.1 x 10 ¹¹ Ω

Storage and Handling

Store refrigerated between 18–25 °C away from direct heat or sunlight.

Disclaimer

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [Solder](#) category:

Click to view products by [MG Chemicals](#) manufacturer:

Other Similar products are found below :

[600YSY](#) [701-2758](#) [707-1746](#) [707-1748](#) [707-1811](#) [707-1813](#) [707-1831](#) [707-1840](#) [707-1850](#) [707-1852](#) [13-217-3-01](#) [P10695](#) [SN63WRAP3-.022-1-LB](#) [24-6040-0007](#) [DAC-061](#) [701-2089](#) [707-0285](#) [707-0366](#) [707-0441-26](#) [707-1774](#) [707-1810](#) [24-6337-9727](#) [601Y](#) [24-9574-7619](#)
[24-4060-2437](#) [14-6040-0125](#) [04-0595-0000](#) [V5S35\[42G\]217](#) [V8B45\[60G\]138](#) [V5B45\[42G\]138](#) [V3B45\[20G\]138](#) [XGS20\[20G\]158](#) [5901003](#)
[631960](#) [SW02-10](#) [S2626-O-T](#) [8055](#) [5760140](#) [TRWR-204](#) [1152](#) [EC2002M-1](#) [WPT17](#) [WS6016](#) [760-2028](#) [8001115](#) [8001073](#) [8001495](#)
[ART.AGT-030](#) [389289](#) [54068](#)