8331



Silver Conductive Epoxy Adhesive

8331 is an electrically conductive, silver-filled 2-part epoxy adhesive. It is smooth, non-sagging, thixotropic, and bonds well to a wide variety of substrates.

This product allows for quick, cold-soldering repairs. It can also be used as a solder replacement for bonding heat-sensitive electronic components, or for making conductive connections where soldering is not an option, such as when bonding to glass, soft metals, or plastics.

8331 has been formulated to be economical. For a higher fill that maximizes conductivity, use 8330. For a longer working time, use 8331S.

Features and Benefits

- Creates strong permanent electrical connections
- Cures at room temperature
- · Excellent adhesion to many substrates
- Room temperature storage
- · Long shelf life

Available Packaging

Cat. No.	Packaging	Net Vol.	Net Wt.
8331-14G	2 Syringe kit	6 mL	14.4 g
8331-50ML	2 Jar kit	50 mL	120 g
8331-200ML	2 Can kit	200 mL	482 g

Contact Information

MG Chemicals, 1210 Corporate Drive Burlington, Ontario, Canada L7L 5R6

Email: support@mgchemicals.com

Phone: North America: +(1)800-340-0772

International: +(1) 905-331-1396 Europe: +(44)1663 362888



Cured Properties

Resistivity	7.0 x 10 ⁻³ Ω·cm
Hardness	73 D
Tensile Strength	13 N/mm ²
Compressive Strength	39 N/mm ²
Lap Shear (stainless steel)	3.8 N/mm ²
(aluminum)	5.5 N/mm ²
Water Absorption	0.04 %
Outgassing @ 125 °C for 24 h	6.3 %
Glass Transition Temperature (T _g)	50 °C
CTE Prior T _g	54 ppm/°C
CTE After T _g	169 ppm/°C
Thermal Conductivity @ 25 °C	1.4 W/(m·K)
Service Temperature Range	-55–150 °C

Usage Parameters

Working Time	10 min
Service Cure	5 h @ 22 °C
Mix Ratio by Volume	1:1
Mix Ratio by Weight	1.2:1

Uncured Properties

Mixed Density	2.29 g/mL
Shelf Life	3 y
Viscosity @ 25 °C	(A) 1 000 Pa·s
	(B) 15 000 Pa·s

8331



Application Instructions

Read the product SDS before using this product (downloadable at www.mgchemicals.com).

Recommended Preparation

Clean the substrate with Isopropyl Alcohol, MG #824, so the surface is free of oils, dust, and other residues.

Syringe

- **1.** Twist and remove the cap from the syringe. Do not discard cap.
- 2. Measure 1 part by volume of A.
- 3. Measure 1 part by volume of B.
- **4.** Dispense material on a mixing surface or container, and thoroughly mix parts A and B together.
- 5. To stop the flow, pull back on the plunger.
- **6.** Clean nozzle to prevent contamination and material buildup.
- 7. Replace the cap on the syringe.

Can or Jar

- **1.** Stir each part individually to re-incorporate material that may have separated.
- 2. Measure 1.2 part by weight of A.
- 3. Measure 1 part by weight of B.
- **4.** Thoroughly mix parts A and B together.
- **5.** Apply adhesive to the application area.

Cure Instructions

Allow to cure at room temperature for 24 hours, or cure the adhesive in an oven at one of these time/temperature options:

- 15 min @ 65 °C
- 7 min @ 125 °C

Storage and Handling

Store between 16 and 27 °C in a dry area, away from sunlight (see SDS). To maximize shelf life, recap product firmly when not in use.

Disclaimer

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Chemicals category:

Click to view products by MG Chemicals manufacturer:

Other Similar products are found below:

DP-605NS 3045-QT 3125-9S 5200-WHITE-3OZ 3748-Q-58"x8" FO-25DT Polygun-LT S1009-KIT-A-CS8606 DP100-200ML 1743-2FP

152-KA-NC VERSIL406 826-450G 3789-Q 9729 9223 9945 7000000275 1601 8330-19G 842AR-15ML 841AR-150ML 842AR-P

843WB-15ML 8462-85ML 4354-1L 838AR-P 838AR-15ML 419D-P-BK 419D-P-GR 419D-P-WH 8MT-450 8MT-25 832HD-25ML

8616-25ML 832FX-450ML 834ATH-375ML 832HD-400ML 8617-1P 843AR-340G 9310-300ML 847-1P 4228-225ML 419D-55ML

8800-375ML 8810-375ML 8820-2.55L 419E-340G 842UR-12ML 419D-1L