8351



No-Clean Halogen-Free Flux

8351 is a organic liquid solder flux with low activity. It has a low solids content that leaves virtually no residue. Solder joints appear shiny after soldering, even without cleaning.

This halogen free flux is the best soldering flux for wave soldering and surface mount assembly. It may be applied by spray or foam, or by wave fluxing. It is also re-flowable in air or nitrogen.

In liquid format, we also offer rosin-based flux, lead-free no-clean flux, and lead-free water soluble flux.

For paste flux, visit MG Chemicals' 8341 and 8342.

Features & Benefits

- · Halogen-free flux
- · Excellent wettability
- Can be used with both lead-free and leaded alloys
- Rosin/resin-free
- Meets J-STD-004B
- RoHS-compliant

Available Packaging

Cat. No.	Packaging	Net Vol.	Net Wt.
8351-125ML	Bottle	125 mL	101 g
8351-1L	Bottle	1 L	809 g
8351-4L	Jug	4 L	3.23 kg
8351-20L	Pail	20 L	16.1 g

Contact Information

MG Chemicals, 1210 Corporate Drive Burlington, Ontario, Canada L7L 5R6

Email: support@mgchemicals.com


Phone: North America: +(1)800-340-0772 International: +(1) 905-331-1396 Europe: +(44)1663 362888



Properties

Flux Classification	ORL0
Flux Type	Organic
Flux Activity	Low
Copper Mirror	Pass
Cleaning Requirements	Recommended
Acid Number (mgKOH/g sample)	14–16
Halides (by weight)	<0.5 %
Suface Insulation Resistance (SIR)	2.1 x 10 ⁹ Ω

Typical Lead-Free Wave Solder Profile



8351



Application Instructions

Read the product SDS before using this product (downloadable at www.mgchemicals.com).

- **1.** Apply flux on the surface by dip, spray, foam, or brush application.
- **2.** Clean residue with MG 413B, 413C, 4140, 4050A, or 4140A flux removers.

Wave Solder Operating Parameters

Amount of Flux: Foam Spray		µg/in² solids µg/in² solids
Foam Fluxing Parameters: Foam Stone Pore Size Flux Level Above Stone Chimney Opening Air Pressure	10–13	mm
Top Side Preheat Temp.	85–110	°C
Bottom Side Preheat Temp.	35	°C
Conveyor-speed	1.2–2.8	m/min
Contact Time in Solder	2.5-4.5	S
Solder Pot Temp. Sn96.5/Ag3.5 Sn95/Ag5 Sn99.3/Cu0.7 SnAgCu Sn95/Sb5	260–276 280–296 265–276 271–276 280–296	ວ° ວ° ວ°

Foam Flux

- The foam fluxer should be provided with the compressed air
- Flux tank must be always full
- Surface of the flux should be 0.5–1" above the top of the flux aerator or flux stone
- Adjust pressure to optimize foam height with a fine uniform foam head
- After fluxing, use an air knife to remove excess flux from the machine

To check for uniformity of spray flux coating, run a tempered glass plate provided by the machine manufactuer through the flux and preheat zones. Ensure to inspect the glass before the wave zone.

Storage and Handling

Store between 18 and 27 °C in a dry area, away from sunlight (see SDS).

Disclaimer

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Soldering Flux category:

Click to view products by MG Chemicals manufacturer:

Other Similar products are found below :

 8351-1L
 8351-125ML
 051-0001
 051-0002
 051-0003
 051-0007
 051-0008
 053-1002
 053-1003
 8342-50G
 ART.AGT

 088
 270WR
 ART.AGT-089
 ART.AGT-094
 ART.AGT-179
 CW8100
 CW8400
 SSS500ML
 63-0000-0186
 63-0000-0951
 63-0000-0977
 63

 0000-1544
 83-1000-0186
 83-1000-0951
 83-1097-2331
 8341-10ML
 835-100ML
 SF-02
 CW8700
 FL22W
 SMD291SNL50T3

 SMD291AX50T3
 CQ2LF
 CQ4LF
 CW8500
 CQ4LF-0.5
 CQ4LF-1.0
 SMD291
 SMD29175G
 SMD291AX
 SMD291AX10

 SMD291AX250T3
 SMD291NL
 SMD291ST2CC6
 SMD291ST8CC
 SMD4300TF
 SMD291AX
 SMD291AX
 SMD291AX