

Threadlocker High Strength, Wicking 8704 Technical Data Sheet

Description

The 8704 *Threadlocker, High Strength, Wicking* has an anaerobic formulation designed to secure and seal fasteners. Due to its low viscosity and high capillary action, it easily penetrates porous metals, moulds, and castings. It prevents loosening caused by vibrations, shock, expansion and contraction. The threadlocker is resistant to heat, corrosion, water, gases, oils, hydrocarbons, and many chemicals.

Applications & Usages

The 8704 is used to secure and seal hydraulic line fittings, housing screws, machinery keys, and many types of nuts and bolts.

Benefits and Features

- Meets MIL S-46163, Type III, Grade R
- Ideal for post application to pre-assembled fasteners
- Penetrates threads by capillary action
- One drop prevents loosening and ensures a secure hold
- Prevent corrosion, seal threads, improve torque control, and reduce galling
- Reduces friction allowing controlled torque during assembly

Usage Parameters

Properties	Value
Fixture Time ^{a)}	10 to 30 min
Full Cure @22 °C [72 °F]	8 h
Bolt Range	For preassembled fasteners
Shelf Life	3 у

a) Time at which the fixture strength of bonded substrate is 0.1 N/mm².

Principal Components

Name	CAS Number
polyglycol dimethacrylate	25852-47-5
aromatic dimethacrylate	24448-20-2
2-hydroxyethyl methacrylate	868-77-9
cumene hydroperoxide	80-15-9

Temperature Ranges

Value
-54 to 176 °C
[-65 to 350 °F] 8 to 28 °C [46 to 82 °F]



Threadlocker High Strength, Wicking 8704 Technical Data Sheet

8704-Liquid

Properties of Cured 8704

Physical Properties	Method	Value
Composition		Dimethacrylate ester
Color	Visual	Green
Mechanical Property		Value
Torque		17/31 N·m [150/275 lbf·in] ^{a)}
Thermal Properties		Value
Coefficient of Thermal Expansion (CTE)	ASTM D696	80 x 10 ⁻⁶ 1/K
Thermal Conductivity	ASTM C177	0.1 W/(m·K)
Specific Heat		0.3 J/(g·K)
Environmental Resistance		Value
Hot Strength	ISO 10964 (Modified)	
% retrained strength @25 °C [77 °F]	"	100%
@100 °C [212 °F]	н	100%
@120 °C [248 °F]	н	85%
@150 °C [302 °F]	"	65%
Heat Aging ^{b)}	"	
% retrained strength @120 °C [248 °F]	"	45%
@150 °C [302 °F]	n	15%
Chemical/Solvent Resistance ^{c)}		Value
% Retained Strength		
50/50 Water/Glycol @87 °C [187 °F]		90%
Unleaded gasoline @22 °C [72 °F]		90%
Motor oil @125 °C [257 °F]		50%
Brake fluid @22 °C [72 °F]		85%
Acetone @22 °C [72 °F]		85%

a) Breakaway/prevailing torque

b) Specimens aged for 2 000 hours and tested at room temperature

c) Specimens immersed for 1 000 hours and tested at room temperature

Properties of Uncured 8704

Physical Properties	Value
Viscosity	12 cP [11 mm ² /s]
Specific Gravity	1.08 g/mL
Flash Point	93 °C [200 °F]
Boiling Point	≥149 °C [≥300 °F]
Odor	Mild
VOC (Volatile Organic Compound)	13 g/L



Storage

Store between 8 to 28 °C [46 to 82 °F] in dry area. Store in well-ventilated area. Keep container tightly closed.

Health, Safety, and Environmental Awareness

Please see the 8704 **Safety Data Sheet** (SDS) for greater details on transportation, storage, handling and other security guidelines.

Environmental Impact: Avoid release to the environment.

Health and Safety: The solvents in 8704 can cause respiratory track irritation, serious eye irritation, skin irritation, and an allergic skin reaction.

Do not breathe vapors. Wear safety glasses or goggles and disposable gloves to avoid exposures.

HMIS® RATING

HEALTH:	* 1
FLAMMABILITY:	1
PHYSICAL HAZARD:	1
PERSONAL PROTECTION:	



Approximate HMIS and NFPA Risk Ratings Legend: 0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

Application Instructions

Follow the procedure below for best results.

To apply the threadlocker

- 1. Shake well before use.
- 2. Ensure the surface is clean of oil, dust, water, solvents, and other contaminants and let the surface dry fully.
- 3. Remove cap and cut nozzle tip.
- 4. Apply to thread and wipe off excess.
- 5. Fixture time is 10 to 30 minutes. Allow full cure in 8 hours.

ATTENTION! Not recommended for use on plastics. Compatibility check should be performed prior application.

NOTE: Optimal use on close fitting flanged parts gaps up to 0.05 mm. Flanges should be tightened as soon as possible after assembly to avoid shimming.



Packaging and Supporting Products

Cat. No.	Packaging	Net Volume		Net Weight		Packaging Weight	
8704-10ML	Bottle	10 mL	0.33 fl oz	10.8 g	0.38 oz	0.04 kg	0.09 lb

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at <u>www.mgchemicals.com</u>.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA) +(1) 905-331-1396 (International) Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address:	Manufacturing & Support 1210 Corporate Drive Burlington, Ontario, Canada L7L 5R6	Head Office 9347–193rd Street Surrey, British Columbia, Canada V4N 4E7
	L/L 5R6	V4N 4E7

Warranty

M.G. Chemicals Ltd. warranties this product for 12 months from the date of purchase by the end user. *M.G. Chemicals Ltd.* makes no claims as to shelf life of this product for the warranty. The liability of *M.G. Chemicals Ltd.* whether based on its warranty, contracts, or otherwise shall in no case include incidental or consequential damage.

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Chemicals category:

Click to view products by MG Chemicals manufacturer:

Other Similar products are found below :

DP-605NS 3045-QT 3125-9S 5200-WHITE-3OZ 3748-Q-58"x8" FO-25DT Polygun-LT S1009-KIT-A-CS8606 DP100-200ML 1743-2FP 152-KA-NC VERSIL406 826-450G 3789-Q 9729 9223 9945 7000000275 1601 8330-19G 842AR-15ML 841AR-150ML 842AR-P 843WB-15ML 8462-85ML 4354-1L 838AR-P 838AR-15ML 419D-P-BK 419D-P-GR 419D-P-WH 8MT-450 8MT-25 832HD-25ML 8616-25ML 832FX-450ML 834ATH-375ML 832HD-400ML 8617-1P 843AR-340G 843ER-800ML 9310-300ML 847-1P 4228-225ML 419D-55ML 8800-375ML 8810-375ML 8820-2.55L 419E-340G 842UR-12ML