


DATA SHEE

Product Number: 115-47-308-41-001000



Description: DIP Dual In Line Socket Low Profile Solder Tail DIP Open Frame Through Hole Plating Code:

Shell Plating: 200 μ" Tin (matte finish) over 100 u" Nickel

Inner Contact Plating:

Gold Flash Packaging:

Packaged in Tubes

# Of Pins	A	В	С	Qty. per Tube	Mill-Max Part Number	RoHS Compliant
8	0.4	0.3	0.4	50	115-47-308-41-001000	RoHS 2002/ISEC

CONTACT:

Contact Used: #30, Standard 4 Finger Contact

Current Rating = 3 Amps

BERYLLIUM COPPER ALLOY 172 (UNS C17200) per ASTM B 194

Properties of BERYLLIUM COPPER:

- Chemical composition: Cu 98.1%, Be 1.9%
- Temper as stamped: TD01
- Properties after heat treatment (TH01):
- Hardness: 36-43 Rockwell C
- Mechanical Life: 1000 Cycles Min.
- Density: .298 lbs/in3
- Electrical Conductivity: 22% IACS*
- Resistance: 10 miliohms Max
- Operating Temperature: -55°C/+125°C
- Melting point: 980°C/865°C (liquidus/solidus)
- Stress Relaxation†: 96% of stress remains after 1,000 hours @ 100 °C; 70% of stress remains after 1,000 hours @ 200 °C

†Since BeCu loses its spring properties over time at high temperatures; it is rated for continuous use up to 150°C. For applications up to 300°C, Mill-Max offers many contacts in Beryllium Nickel. Contact Tech Support for more info.

LOOSE PIN:

Pin Used: 0501 (Brass Alloy)

^{*}International Annealed Copper Standard, i.e. as a % of pure copper.

BRASS ALLOY 360 per ASTM B 16, or 385 per ASTM B455

Properties of BRASS ALLOY 360 ASTM B 16:

Chemical composition: Cu 63% (max), Pb 3.7% (max)†, Fe .35% (max), Zn remainder

Temper as machined: H02/H04
Yield Strength: 25-45 ksi
Tensile strength: 57-80 ksi

Hardness as machined: 80-90 Rockwell B
Electrical conductivity: 26% IACS*

Melting point: 1000°C/840°C (liquidus/solidus)

Properties of BRASS ALLOY 385 ASTM B 455:

• Chemical composition: Cu 60% (max), Pb 3.5% (max)†, Fe .35% (max), Zn remainder

Temper as machined: H02/H04Yield Strength: 16 ksi(min)

Tensile strength: 48 ksi(min)

• Hardness as machined: 80-90 Rockwell B

Electrical conductivity: 28% IACS*

• Melting point: 1000°C/840°C (liquidus/solidus)

After machining, brass parts are often annealed (softened) for subsequent bending, swaging or crimping. A partial anneal down to 60 ± 10 RB is recommended for 90° bends, a full anneal down to 35 ± 15 RB is recommended for pins or terminals that are swaged (riveted) to a circuit board or crimped to a wire.

†RoHS-2 directive 2011/65/EU, exemption 6c allows up to 4% lead as an alloy agent in copper.

*International Annealed Copper Standard, i.e. as a % of pure copper.

INSULATOR INFORMATION:

PCT Polyester, (Thermx CG933, black)

High Temperature

Properties of PCT Polyester:

Brand: ThermxGrade: CG-933

• Rated voltage: 100 VRMS/150 VDC

• Insulation resistance: 10,000 Megaohms min.

• Material Heat Deflection Temp (per ASTM D 648): 529°F (276°C) @ 66 psi

• Dielectric strength: 1000 VRMS min. (700 VRMS min. for series 117 Shrink DIP)

Note: Materials above 446°F (230°C) are considered suitable for "eutectic" reflow soldering, above 500°F (260°C) for "lead-free" reflow soldering.

Certificate of Compliance:

This is to Certify that the product described above is manufactured to Mill-Max quality standards in accordance with all applicable specifications and drawing. Mill-Max certifies this product to be free from defects of materials and workmanship.

This Certificate of Compliance covers the following requirements:

- Dimensional (all features verified to be within tolerances described on the applicable drawing).
- Raw Material (materials and properties verified to be as described on the applicable drawing).
- Plating (platings as required, thickness verified, and performance including solderability per mil-standard).
- Performance (insertion extraction or other force requirements as described on the applicable drawing).

Compliance Statement for RoHS and RoHS-2, on the restriction of the use of certain hazardous substances in electrical and electronic equipment, for Mill-Max products.

- 1. Directive 2015/863/EU of 31 March 2015 amending Annex II to Directive 2011/65/EU of the European Parliament and of the Council as regards the list of restricted substances.
- 2. Directive 2011/65/EU of the European Parliament and of the Council of 8 June 2011 on the restriction of the use of certain hazardous substances in electrical and electronic equipment (recast)
- 3. Directive 2002/95/EC of the European Parliament and of the Council of January 27 2003 on the restriction of the use of certain hazardous substances in electrical and electronic equipment.

In reference to the directives described above, Mill-Max Mfg.Corp. certifies that its product labeled as RoHS and RoHS-2 are compliant to the above directives with exemption 6c, (copper alloy containing up to 4 % lead by weight). No warranty or liability of indemnification is expressed or implied with this information.

Compliance Statement for Registration, Evaluation, Authorization and Restriction of Chemicals (REACH)

Reference:

- 1. Regulation EC No 1907/2006 of the European Parliament and of the Council of 18 December 2006, concerning the Registration, Evaluation, Authorization and Restriction of Chemicals (REACH)
- 2. ECHA, Candidate list of Substances of Very High Concern (SVHC) http://echa.europa.eu/reach_en.asp

Mill-Max is aware of the regulation and the SVHC list the EU published (referenced above). Mill-Max does not produce or sell any of the listed substances in their homogeneous form. These substances are not intentionally added during the manufacturing of any Mill-Max products. To our knowledge, our products do not contain the substances described on the ECHA SVHC list. Testing is not performed for materials and substances that were not intentionally added. No warranty, liability of indemnification is expressed or implied with this information. Mill-Max maintains surveillance of the ECHA website to obtain the latest information and periodically reviews the SVHC list for changes and additions.

Compliance Statement for DRC Conflict Free products.

Reference:

Dodd-Frank Wall Street Reform and Consumer Protection Act, Section 1502, reporting requirements for users of conflict minerals.

"Conflict minerals," are Columbite-tantalite (coltan), cassiterite, gold, wolframite, or their derivatives; or any other mineral or its derivatives determined by the Secretary of State to be financing conflict in the Democratic Republic of the Congo (DRC) or an adjoining country. Metals derived from these minerals are tin, tantalum, tungsten, and gold. By this definition, the only minerals of concern that may be found in Mill-Max products are tin and gold.

Mill-Max Mfg.Corp. hereby certifies that its products are manufactured with tin and gold that is derived from material that is considered DRC Conflict Free. Mill-Max provides this assurance as a result of a due diligence process that includes traceability to the source and in some cases the identification of recycled and scrap materials included in the subject material.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for IC & Component Sockets category:

Click to view products by Mill-Max manufacturer:

Other Similar products are found below:

0066-3-17-15-30-14-02-0 670 672 673 694-13-640-00-672-000 712-93-120-41-001000 714-93-104-31-018000 8059-4G1-LF 807-22-001-10-001101 807-22-001-10-006101 807-22-001-30-011101 807-22-001-30-012101 807-22-001-30-013101 807-22-001-30-014101 8-1437531-4 8150-6P10 833-93-034-10-001000 851-41-006-10-001000 851-43-008-20-001000 851-43-014-20-001000 851-93-006-20-001000 851-93-006-20-001000 851-93-010-20-001000 853-43-020-10-001000 86.010.0053.0 116-43-308-41-007000 PX-68LCC 121-13-318-41-001000 121-13-320-41-001000 123-43-314-41-801000 123-43-420-41-001000 123-87-320-41-001101 122-13-316-41-001000 123-13-624-41-001000 123-43-306-41-001000 12-3513-11 123-91-320-41-001000 126-43-310-41-002000 AKSUN 37V-T 1437503-9 1437504-1 146-44-308-41-013000 APO-320-G-T 146-43-308-41-012000 160-10-308-00-001000 160-40-320-00-001000 214-99-306-01-670800 232-1270-02-0602 2-382761-4 2-5331677-4