Chip Monolithic Ceramic Capacitor for Automotive limited to Conductive Glue Mounting GCG32EC71E226KE01_ (1210, X7S:EIA, 22uF, DC25V)

_: packaging code Reference Sheet

1.Scope

This product specification is applied to Chip Monolithic Ceramic Capacitor limited to Conductive Glue Mounting Type used for Automotive Electronic equipment with conductive glue mounting.

2.MURATA Part NO. System

(Ex.)	GCG	32	Е	C7	1E	226	K	E01	L
		(1)L/W Dimensions	(2)T Dimensions	(3)Temperature Characteristics	(4)Rated Voltage	(5)Nominal Capacitance	(6)Capacitance Tolerance	(7)Murata's Control Code	(8)Packaging Cod

3. Type & Dimensions



(Unit:mm)

1

(1)-1 L	(1)-2 W (2) T		е	g
3.2±0.4	2.5±0.3	2.5±0.3	0.3 min.	1.0 min.

4.Rated value

Tillated Value						
· / ·	e Characteristics ode):X7S(EIA)	(4) Rated	(5) Nominal	(6) Capacitance	Specifications and Test Methods	
Temp. coeff or Cap. Change	Temp. Range (Ref.Temp.)	Voltage	Capacitance	Tolerance	(Operating Temp. Range)	
-22 to 22 %	-55 to 125 °C (25 °C)	DC 25 V	22 uF	±10 %	-55 to 125 °C	

5.Package

	on donage								
mark	(8) Packaging	Packaging Unit							
L	φ180mm Reel EMBOSSED W8P4	1000 pcs./Reel							
K	φ330mm Reel EMBOSSED W8P4	4000 pcs./Reel							

Product specifications in this catalog are as of Apr.14,2016,and are subject to change or obsolescence without notice. Please consult the approval sheet before ordering.

Please read rating and !Cautions first.

No	AEC-Q200 T	est Item	Specification.	AEC-Q200 Test Method				
1	Pre-and Post-Stress Electrical Test			-				
	High Temperature Exposure (Storage)	Appearance	The measured and observed characteristics should satisfy the specifications in the following table. No marking defects	Fix the capacitor to the supporting jig in the same manner and under the same conditions as No.16. Set the capacitor for 1000±12 hours at 150±3°C. Set for				
		Capacitance Change Dissipation Factor	C7: Within ±12.5% C7: 0.2max	24±2 hours at room temperature, then measure.				
	Insulation Resistance		More than 2,000MΩ or 50 Ω∙ F (Whichever is smaller)					
3	Temperature Cycling	Appearance Capacitance	The measured and observed characteristics should satisfy the specifications in the following table. No marking defects C7: Within ±10.0%	Fix the capacitor to the supporting jig in the same manner and under the same conditions as No.16.Perform the 1000 cycles test according to the four heat treatments listed in the following table. Set for 24±2 hours at room temperature, then measure				
		Change Dissipation	C7: 0.1max	Step 1 2 3 4				
		Factor		Temp. (°C) -55+0/-3 Room Temp. 125+3/-0 Room Temp.				
		Insulation Resistance	100Ω ·F min.	Time (min.) 15±3 1 15±3 1				
				 Initial measurement for high dielectric constant type Perform a heat treatment at 150+0/-10 °C for one hour and then set for 24±2 hours at room temperature. Perform the initial measurement. 				
4	Destructive Physical Analysis		No defects or abnormalities	Per EIA-469				
5	Moisture Resistance		The measured and observed characteristics should satisfy the specifications in the following table.	Fix the capacitor to the supporting jig in the same manner and under the same conditions as No.16.				
		Appearance	No marking defects	Apply the 24-hour heat (25 to 65°C) and humidity (80 to 98%) treatment shown below, 10 consecutive times.				
		Capacitance Change	C7: Within ±12.5%	Set for 24±2 hours at room temperature, then measure. Temperature Humidity Humidity				
		Dissipation Factor	C7: 0.2max	Humidity 80~98% Humidity 80~98% Humidity 90~98% 90~9				
		Insulation Resistance	More than 2,000M Ω or 50 Ω • F (Whichever is smaller)	30 25 20 15 10 15 10 17 11 11 11 11 11 11 11 11 11 11 11 11				
				Perform a heat treatment at 150+0/–10°C for one hour and then let sit for 24±2 hours at room temperature, then measure.				
6	Biased Humidity		The measured and observed characteristics should satisfy the specifications in the following table.	Fix the capacitor to the supporting jig in the same manner and under the same conditions as No.16.				
		Appearance	No marking defects	Apply the rated voltage and 1.3+0.2/-0vdc (add 6.8kΩ resister)				
		Capacitance Change	C7: Within ±12.5%	at 85±3°C and 80 to 85% humidity for 1000±12 hours. Remove and set for 24±2 hours at room temperature, then measure.				
		Dissipation Factor	C7: 0.2 max	The charge/discharge current is less than 50mA.				
		Insulation	More than 1,000M Ω or 25 Ω · F	Measurement after test for high dielectric constant type Perform a heat treatment at 150+0/–10°C for one hour and then let				
		Resistance	(Whichever is smaller)	sit for 24±2 hours at room temperature, then measure.				

JEMCGS-04728 2

■AEC-Q200 Murata Standard Specification and Test Methods

No	AEC-Q20	00 Test Item	Specification.	AEC-Q200 Test Method
7	Operational Life		The measured and observed characteristics should satisfy the specifications in the following table.	Fix the capacitor to the supporting jig in the same manner and under the same conditions as No.16.
		Appearance	No marking defects	Apply 150% of the rated voltage for 1000±12 hours at 125±3°C.
		Capacitance	C7: Within ±12.5%	Set for 24±2 hours at room temperature, then measure.
		Change		The charge/discharge current is less than 50mA.
		Dissipation	C7: 0.2max	Initial measurement for high dielectric constant type
		Factor		Perform a heat treatment at 150+0/-10°C for one hour and then set
				for 24±2 hours at room temperature.
				Perform the initial measurement.
	Insulation			Measurement after test for high dielectric constant type
			More than 1,000M Ω or 25 Ω • F	Perform a heat treatment at 150+0/–10°C for one hour and then let
		Resistance	(Whichever is smaller)	sit for 24±2 hours at room temperature, then measure.
8	External Visual	L	No defects or abnormalities	Visual inspection
9	Physical Dimer	sion	Within the specified dimensions	Using calipers
10	Resistance to	Appearance	No marking defects	Per MIL-STD-202 Method 215
	Solvents	Capacitance	Within the specified tolerance	Solvent 1: 1 part (by volume) of isopropyl alcohol
		Change		3 parts (by volume) of mineral spirits
		Dissipation	C7: 0.1max	Solvent 2 : Terpene defluxer
		Factor		Solvent 3 : 42 parts (by volume) of water
		actor		
				1part (by volume) of propylene glycol monomethyl ether 1 part (by volume) of monoethanolamine
		Insulation	100Ω • F min.	, part (b) round) of moneculariolarisis
		Resistance		
11	Mechanical	Appearance	No marking defects	Fix the capacitor to the test jig in the same manner and under the
	Shock	Capacitance	Within the specified tolerance	same conditions as No.16.
		Change		Three shocks in each direction should be applied along 3 mutually
		Dissipation	C7: 0.1max	perpendicular axes of the test specimen (18 shocks).
		Factor		The specified test pulse should be Half-sine and should have a
				duration :0.5ms, peak value:1500g and velocity change: 4.7m/s.
		Insulation	100Ω · F min.	
		Resistance		
12	Vibration	Appearance	No defects or abnormalities	Fix the capacitor to the test jig in the same manner and under the
		Capacitance	Within the specified tolerance	same conditions as No.16.
		Change		Solder the capacitor to the test jig (glass epoxy board) in the same
		Dissipation	C7: 0.1max	manner and under the same conditions as (19). The capacitor
		Factor		should be subjected to a simple harmonic motion having a total
		1		amplitude of 1.5mm, the frequency being varied uniformly between
		1		the approximate limits of 10 and 2000Hz. The frequency range, from
		Insulation	1000 - E min	10 to 2000Hz and return to 10Hz, should be traversed in
			100Ω • F min.	
		Resistance		approximately 20 minutes. This motion should be applied for 12 items in each 3 mutually perpendicular directions (total of 36 times).
		1		

JEMCGS-04728 3

■ AEC-Q200 Murata Standard Specification and Test Methods

No AEC-Q	200 Test Item	Specification.			AEC-Q200 Tes	t Method	
13 Thermal Sh	ock	The measured and observed characteristics shall satisfy the specifications in the following table.	Fix the capacitor to the supporting jig in the same manner and under the same conditions as No.16. Perform the 300 cycles according to				
	Appearance	No marking defects	under the same conditions as No.16. Perform the 300 cycles according the two heat treatments listed in the following table (Maximum				
	Capacitance	C7: Within ±10.0%				• '	
		C7. Within £10.0%			conds). Set for 24±	2 nours at room	
	Change		temper	ature, then me	easure		
	Dissipation	C7: 0.1max		Step	1	2	
	Factor			Temp.(°C)	-55+0/-3	125+3/-0	
	Insulation	100Ω • F min.		Time (min.)	15±3	15±3	
	Resistance		Perform for 24±	n a heat treatn	m temperature.	constant type C for one hour and then set	
14 ESD	Appearance	No marking defects	Per AE	C-Q200-002			
	Capacitance Within the specified tolerance Change						
	Dissipation Factor	C7: 0.1max					
	Insulation Resistance	100Ω • F min.					
15 Electrical	Appearance	No defects or abnormalities	Visual	Visual inspection.			
Chatacteri-	Capacitance	Within the specified tolerance	The capacitance/Q/D.F. should be measured at 25°C at the				
zation	Change		frequency and voltage shown in the table.				
	Dissipation	C7: 0.1max		.,			
	Factor	O7. C. TINEA	Fr	Item (C equency 1:		nin. (10μF < C) (0μF) (Hz 120±24Hz	
				1.0		1 34 50 15	
	Insulation	100Ω · F min.				sured with a DC voltage not	
	Resistance			-	otage at 25°C and	150°C within 1 minute of	
	25 ℃		chargir	ng.			
	Insulation	1Ω •F min.					
	Resistance						
	125°C						
	Dielectric Strength	No failure	No failure should be observed when 250% of the rated voltage applied between the terminations for 1 to 5 seconds, provide charge/ discharge current is less than 50mA.				

muRata ■AEC-Q200 Murata Standard Specification and Test Methods

No	AEC-Q200	Test Item	Specification.	AEC-Q200 Test Method
16	Terminal Strength	Appearance Capacitance Change Dissipation Factor Insulation Resistance	No marking defects Within specified tolerance C7: 0.1max 100Ω • F min.	Mount the capacitor on the test jig in Fig.1 using a conductive glue (HEREAUS*PC3000*). The conductive glue is hardened at 140°C for 30minites. Then apply *shear tension in parallel with the test jig for 60sec. *Show in the table 1 Type Share Tension GCG15 2. 0N GCG18 2. 7N GCG21 4. 9N GCG31 6. 9N GCG31 6. 9N GCG32 12. 6N Table. 1
17	7 Beam Load Test		Destruction value should be exceed following one. < Chip L dimension : 2.5mm max. > Chip thickness > 0.5mm rank : 20N Chip thickness ≤ 0.5mm rank : 8N < Chip L dimension : 3.2mm max. > Chip thickness < 1.25mm rank : 15N	Type
			Chip thickness < 1.25mm rank : 15N Chip thickness ≧ 1.25mm rank : 54.5N	< Chip Length : 3.2mm min. > Chip Length : 3.2mm min. > Lip Control of the stress Load : 0.5mm / sec.

JEMCGS-04728 5

■AEC-Q200 Murata Standard Specification and Test Methods

No	AEC-Q200 Test Item		AEC-Q200 Test Item Specification.		AEC-Q200 Test Method			
18	Capacitance Temperature Characteristics	Capacitance Change	C7 : Within ±22% (-55°C to +125°C)	each spec The rang value ove within the • Initial m Perform a and then	cified te es of ca er the te e specif neasure heat tr set for 2	change should be measure mperature stage. apacitance change compare emperature ranges shown in ited ranges. ment for high dielectric conceatment at 150+0/-10°C for 24±2 hours at room temperat I measurement. Temperature.(°C) 25±2 -55±3 25±2 125±3 25±2	nd with the above 25°C the table should be stant type.	

JEMCGS-04728 6


- 1.Tape Carrier Packaging(Packaging Code:D/E/W/F/L/J/K)
- 1.1 Minimum Quantity(pcs./reel)

			φ180mm reel	φ330m	nm reel	
Ty	/pe	Papei	^r Tape	Plastic Tape	Paper Tape	Plastic Tape
		Code:D/E	Code:W	Code:L	Code:J/ F	Code:K
GCG15	5	10000	20000		50000	
00013	٥	(W8P2)	(W8P1)		(W8P2)	
GCG18	8	4000			10000	
	6	4000			10000	
GCG21	9	4000			10000	
	В			3000		10000
GCG31	M			3000		10000
GCG31	С			2000		6000
GCG32	D			1000		4000
GCG32	E			1000		4000


1.2 Dimensions of Tape

(1)GCG15(W8P2 CODE:D/E/J/F) <Paper Tape>

(in:mm)










(in:mm)




	Туре		Dimer Tolerand	nsions ce(Chip)	TDimensions	Α	В	t
			L	W	(Chip)			
	GCG18	8	±0.2	±0.1	0.8±0.1	1.05±0.10	1.85±0.10	
	GCG21	6 +03		±0.3 ±0.2		1.55±0.15	2.30±0.15	1.1max.
	GCG21	9	±0.3	±0.2	0.85±0.1	1.55 ±0.15	2.30 = 0.13	


(4)GCG21/31/32 <Plastic Tape>



Type		Dimensions Tolerance(Chip)		T Dimensions	А	В	t
		L	W	(Chip)			
GCG21	В	±0.3	±0.2	1.25±0.2	1.45±0.20	2.25±0.20	2.0 max.
GCG31	М	±0.3	±0.3 ±0.3	1.15±0.2	1.90±0.20	3.50±0.20	1.7 max.
GCG31	O			1.6±0.3			2.5 max.
GCG32	D			2.0±0.3	2 00 ± 0 20	3.50±0.20	3.0 max.
GCG32	Е	±0.4	±0.3	2.5±0.3	2.80±0.20	3.50 ± 0.20	3.7 max.




- 1.3 Tapes for capacitors are wound clockwise shown in Fig.3. (The sprocket holes are to the right as the tape is pulled toward the user.)
- 1.4 Part of the leader and part of the vacant section are attached as follows.



- 1.5 Accumulate pitch: 10 of sprocket holes pitch = 40±0.3mm
- 1.6 Chip in the tape is enclosed by top tape and bottom tape as shown in Fig.1.
- 1.7 The top tape and base tape are not attached at the end of the tape for a minimum of 5 pitches.
- 1.8 There are no jointing for top tape and bottom tape.
- 1.9 There are no fuzz in the cavity.
- 1.10 Break down force of top tape : 5N min.

 Break down force of bottom tape : 5N min. (Only a bottom tape existence)
- 1.11 Reel is made by resin and appeaser and dimension is shown in Fig 2.

 There are possibly to change the material and dimension due to some impairment.
- 1.12 Peeling off force: 0.1N to 0.6N in the direction as shown below.



1.13 Label that show the customer parts number, our parts number, our company name, inspection number and quantity, will be put in outside of reel.

■Limitation of Applications

Please contact us before using our products for the applications listed below which require especially high reliability for the prevention of defects which might directly cause damage to the third party's life, body or property.

- ①Aircraft equipment ②Aerospace equipment ③Undersea equipment ④Power plant control equipment
- ⑤Medical equipment ⑥Transportation equipment(vehicles,trains,ships,etc.) ⑦Traffic signal equipment
- (1) Application of similar complexity and/or reliability requirements to the applications listed in the above.

■ Storage and Operation condition


- 1. If store the chip monolithic ceramic capacitors in an atmosphere consisting of high temperature or humidity, sulfur or chlorine gases, contaminants attach to the surface of external electrode, and bondability with conductive glue may deteriorate. Do not store the capacitors in an atmosphere consisting of corrosive gas (e.g., hydrogen sulfide, sulfur dioxide, chlorine, ammoria gas, etc.). Storage environment must be at room temperature of +5°C to +40°C and a relative humidity of 20% to 70%, and use the product within six months. In case of packaging, do not open the last wrappend, polyethylene bag, till just before using. After unpacking, immediately reseal, or store in a desiccator containing a desiccant.
- 2. Due to moisture condensation caused by rapid humidity changes, or the photochemical change caused by direct sunlight on the terminal electrodes and/or the resin/epoxy coatings, the bondability with conductive glue and electrical performance may deteriorate. Do not store capacitors under direct sunlight or in high humidity conditions.
- 3. This product is chip monolithic ceramic capacitor limited to conductive glue mounting. Do not apply mounting method other than conductive glue. Flow or reflow soldering can result in a lack of adhesive strength on the outer electrode by poor wettability, which may result in chips breaking loose from the PCB.

■ Rating


1.Temperature Dependent Characteristics

- 1. The electrical characteristics of the capacitor can change with temperature.
- 1-1. For capacitors having larger temperature dependency, the capacitance may change with temperature changes. The following actions are recommended in order to ensure suitable capacitance values.
 - (1) Select a suitable capacitance for the operating temperature range.
 - (2) The capacitance may change within the rated temperature. When you use a high dielectric constant type capacitor in a circuit that needs a tight (narrow) capacitance tolerance (e.g., a time-constant circuit), please carefully consider the temperature characteristics, and carefully confirm the various characteristics in actual use conditions and the actual system.

[Example of Temperature Caracteristics X7R(R7)] Sample: 0.1µF, Rated Voltage 50VDC



[Example of Temperature Characteristics X5R(R6)] Sample: 22µF, Rated Voltage 4VDC




2.Measurement of Capacitance

- 1. Measure capacitance with the voltage and frequency specified in the product specifications.
- 1-1. The output voltage of the measuring equipment may decrease occasionally when capacitance is high. Please confirm whether a prescribed measured voltage is impressed to the capacitor.
- 1-2. The capacitance values of high dielectric constant type capacitors change depending on the AC voltage applied. Please consider the AC voltage characteristics when selecting a capacitor to be used in a AC circuit.

3.Applied Voltage

- 1. Do not apply a voltage to the capacitor that exceeds the rated voltage as called out in the specifications.
- 1-1. Applied voltage between the terminals of a capacitor shall be less than or equal to the rated voltage.
 - (1) When AC voltage is superimposed on DC voltage, the zero-to-peak voltage shall not exceed the rated DC voltage. When AC voltage or pulse voltage is applied, the peak-to-peak voltage shall not exceed the rated DC voltage.
 - (2) Abnormal voltages (surge voltage, static electricity, pulse voltage, etc.) shall not exceed the rated DC voltage.



(E: Maximum possible applied voltage.)

1-2. Influence of over voltage

Over voltage that is applied to the capacitor may result in an electrical short circuit caused by the breakdown of the internal dielectric layers.


The time duration until breakdown depends on the applied voltage and the ambient temperature.

4. Type of Applied Voltage and Self-heating Temperature

- 1. Confirm the operating conditions to make sure that no large current is flowing into the capacitor due to the continuous application of an AC voltage or pulse voltage.
 - When a DC rated voltage product is used in an AC voltage circuit or a pulse voltage circuit, the AC current or pulse current will flow into the capacitor; therefore check the self-heating condition.
 - Please confirm the surface temperature of the capacitor so that the temperature remains within the upper limits of the operating temperature, including the rise in temperature due to self-heating. When the capacitor is used with a high-frequency voltage or pulse voltage, heat may be generated by dielectric loss.

<Applicable to Rated Voltage of less than 100VDC>


1-1. The load should be contained to the level such that when measuring at atmospheric temperature of 25°C, the product's self-heating remains below 20°C and the surface temperature of the capacitor in the actual circuit remains within the maximum operating temperature.



5. DC Voltage and AC Voltage Characteristic

- The capacitance value of a high dielectric constant type capacitor changes depending on the DC voltage applied. Please consider the DC voltage characteristics when a capacitor is selected for use in a DC circuit.
- 1-1. The capacitance of ceramic capacitors may change sharply depending on the applied voltage. (See figure) Please confirm the following in order to secure the capacitance.
- (1) Determine whether the capacitance change caused by the applied voltage is within the allowed range.
- (2) In the DC voltage characteristics, the rate of capacitance change becomes larger as voltage increases, even if the applied voltage is below the rated voltage. When a high dielectric constant type capacitor is used in a circuit that requires a tight (narrow) capacitance tolerance (e.g., a time constant circuit), please carefully consider the voltage characteristics, and confirm the various characteristics in the actual operating conditions of the system.
- The capacitance values of high dielectric constant type capacitors changes depending on the AC voltage applied.
 Please consider the AC voltage characteristics when selecting a capacitor to be used in a AC circuit.






6. Capacitance Aging

1. The high dielectric constant type capacitors have an Aging characteristic in which the capacitance value decreases with the passage of time. When you use a high dielectric constant type capacitors in a circuit that needs a tight (narrow) capacitance tolerance (e.g., a time-constant circuit), please carefully consider the characteristics of these capacitors, such as their aging, voltage, and temperature characteristics. In addition, check capacitors using your actual appliances at the intended environment and operating conditions.


[Example of Change Over Time (Aging characteristics)]




7.Vibration and Shock

- 1. Please confirm the kind of vibration and/or shock, its condition, and any generation of resonance.

 Please mount the capacitor so as not to generate resonance, and do not allow any impact on the terminals.
- Mechanical shock due to being dropped may cause damage or a crack in the dielectric material of the capacitor.
 Do not use a dropped capacitor because the quality and reliability may be deteriorated.
- 3. When printed circuit boards are piled up or handled, the corner of another printed circuit board should not be allowed to hit the capacitor in order to avoid a crack or other damage to the capacitor.






■ Mounting

1. Selection of Conductive Adhesive, Mounting Process, and Bonding Strength

1.The acuired bonding strength may change greatly depending on the conductive adhesive to be used. Be sure to confirming the desired performance can be acquired in the assumed monting process with the conductive adhesive to be used.

2. Maintenance of the Mounting (pick and place) Machine

- 1. Make sure that the following excessive forces are not applied to the capacitors.
- 1-1. In mounting the capacitors on the printed circuit board, any bending force against them shall be kept to a minimum to prevent them from any damage or cracking. Please take into account the following precautions and recommendations for use in your process.
 - (1) Adjust the lowest position of the pickup nozzle so as not to bend the printed circuit board.
 - (2) Adjust the nozzle pressure within a static load of 1N to 3N during mounting.



2.Dirt particles and dust accumulated between the suction nozzle and the cylinder inner wall prevent the nozzle from moving smoothly. This imposes greater force upon the chip during mounting, causing cracked chips. Also, the locating claw, when worn out, imposes uneven forces on the chip when positioning, causing cracked chips. The suction nozzle and the locating claw must be maintained, checked and replaced periodically.

3.Moisture proof

1.To prevent the silver electrode migration, keep parts under low moisture condition with resin coating and the equivalent.

4.Coating

- 1. A crack may be caused in the capacitor due to the stress of the thermal contraction of the resin during curing process. The stress is affected by the amount of resin and curing contraction. Select a resin with low curing contraction. The difference in the thermal expansion coefficient between a coating resin or a molding resin and the capacitor may cause the destruction and deterioration of the capacitor such as a crack or peeling, and lead to the deterioration of insulation resistance or dielectric breakdown.
 - Select a resin for which the thermal expansion coefficient is as close to that of the capacitor as possible. A silicone resin can be used as an under-coating to buffer against the stress.
- Select a resin that is less hygroscopic.
 Using hygroscopic resins under high humidity conditions may cause the deterioration of the insulation resistance of a capacitor. An epoxy resin can be used as a less hygroscopic resin.
- 3. The halogen system substance and organic acid are included in coating material, and a chip corrodes by the kind of Coating material. Do not use strong acid type.

Others

1. Under Operation of Equipment

- 1-1. Do not touch a capacitor directly with bare hands during operation in order to avoid the danger of an electric shock.
- 1-2. Do not allow the terminals of a capacitor to come in contact with any conductive objects (short-circuit). Do not expose a capacitor to a conductive liquid, inducing any acid or alkali solutions.
- 1-3. Confirm the environment in which the equipment will operate is under the specified conditions.
 - Do not use the equipment under the following environments.
 - (1) Being spattered with water or oil.
 - (2) Being exposed to direct sunlight.
 - (3) Being exposed to ozone, ultraviolet rays, or radiation.
 - (4) Being exposed to toxic gas (e.g., hydrogen sulfide, sulfur dioxide, chlorine, ammonia gas etc.)
 - (5) Any vibrations or mechanical shocks exceeding the specified limits.
 - (6) Moisture condensing environments.
- 1-4. Use damp proof countermeasures if using under any conditions that can cause condensation.

2. Others

2-1. In an Emergency

- (1) If the equipment should generate smoke, fire, or smell, immediately turn off or unplug the equipment.

 If the equipment is not turned off or unplugged, the hazards may be worsened by supplying continuous power.
- (2) In this type of situation, do not allow face and hands to come in contact with the capacitor or burns may be caused by the capacitor's high temperature.

2-2. Disposal of waste

When capacitors are disposed of, they must be burned or buried by an industrial waste vendor with the appropriate licenses.

2-3. Circuit Design

(1) Addition of Fail Safe Function

Capacitors that are cracked by dropping or bending of the board may cause deterioration of the insulation resistance, and result in a short. If the circuit being used may cause an electrical shock, smoke or fire when a capacitor is shorted, be sure to install fail-safe functions, such as a fuse, to prevent secondary accidents.

(2) This series are not safety standard certified products.

2-4. Remarks

Failure to follow the cautions may result, worst case, in a short circuit and smoking when the product is used. The above notices are for standard applications and conditions. Contact us when the products are used in special mounting conditions.

Select optimum conditions for operation as they determine the reliability of the product after assembly.

The data herein are given in typical values, not guaranteed ratings.

Rating

1.Operating Temperature

- 1. The operating temperature limit depends on the capacitor.
- 1-1. Do not apply temperatures exceeding the maximum operating temperature. It is necessary to select a capacitor with a suitable rated temperature that will cover the operating temperature range. It is also necessary to consider the temperature distribution in equipment and the seasonal temperature variable factor.
- 1-2. Consider the self-heating factor of the capacitor

 The surface temperature of the capacitor shall not exceed the maximum operating temperature including self-heating.

2.Atmosphere Surroundings (gaseous and liquid)

- 1. Restriction on the operating environment of capacitors.
- 1-1. Capacitors, when used in the above, unsuitable, operating environments may deteriorate due to the corrosion of the terminations and the penetration of moisture into the capacitor.
- 1-2. The same phenomenon as the above may occur when the electrodes or terminals of the capacitor are subject to moisture condensation.
- 1-3. The deterioration of characteristics and insulation resistance due to the oxidization or corrosion of terminal electrodes may result in breakdown when the capacitor is exposed to corrosive or volatile gases or solvents for long periods of time.

3.Piezo-electric Phenomenon

 When using high dielectric constant type capacitors in AC or pulse circuits, the capacitor itself vibrates at specific frequencies and noise may be generated.
 Moreover, when the mechanical vibration or shock is added to capacitor, noise may occur.

Others

1.Transportation

- 1. The performance of a capacitor may be affected by the conditions during transportation.
- 1-1. The capacitors shall be protected against excessive temperature, humidity and mechanical force during transportation.
 - (1) Climatic condition
 - · low air temperature : -40°C
 - · change of temperature air/air : -25°C/+25°C
 - · low air pressure: 30 kPa
 - · change of air pressure : 6 kPa/min.
 - (2) Mechanical condition

Transportation shall be done in such a way that the boxes are not deformed and forces are not directly passed on to the inner packaging.

- 1-2. Do not apply excessive vibration, shock, or pressure to the capacitor.
 - (1) When excessive mechanical shock or pressure is applied to a capacitor, chipping or cracking may occur in the ceramic body of the capacitor.
 - (2) When the sharp edge of an air driver, tweezers, a chassis, etc. impacts strongly on the surface of the capacitor, the capacitor may crack and short-circuit.
- 1-3. Do not use a capacitor to which excessive shock was applied by dropping etc. A capacitor dropped accidentally during processing may be damaged.

2. Characteristics Evaluation in the Actual System

- 1. Evaluate the capacitor in the actual system,to confirm that there is no problem with the performance and specification values in a finished product before using.
- 2. Since a voltage dependency and temperature dependency exists in the capacitance of high dielectric type ceramic capacitors, the capacitance may change depending on the operating conditions in the actual system. Therefore, be sure to evaluate the various characteristics, such as the leakage current and noise absorptivity, which will affect the capacitance value of the capacitor.
- 3. In addition,voltages exceeding the predetermined surge may be applied to the capacitor by the inductance in the actual system. Evaluate the surge resistance in the actual system as required.

muRata

△ NOTE

- 1.Please make sure that your product has been evaluated in view of your specifications with our product being mounted to your product.
- 2. Your are requested not to use our product deviating from this product specification.
- 3.We consider it not appropriate to include any terms and conditions with regard to the business transaction in the product specifications, drawings or other technical documents. Therefore, if your technical documents as above include such terms and conditions such as warranty clause, product liability clause, or intellectual property infringement liability clause, they will be deemed to be invalid.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Multilayer Ceramic Capacitors MLCC - SMD/SMT category:

Click to view products by Murata manufacturer:

Other Similar products are found below:

D55342E07B523DR-T/R NCA1206X7R104K16TRPF NIN-FB391JTRF NIN-FC2R7JTRF NMC0402XPO220J50TRPF
NMC0402X5R105K6.3TRPF NMC0402X5R224K6.3TRPF NMC0402X7R103J25TRPF NMC0402X7R153K16TRPF
NMC0402X7R392K50TRPF NMC0603NPO1R8C50TRPF NMC0603NPO201J50TRPF NMC0603NPO330G50TRPF
NMC0603X5R475M6.3TRPF NMC0805NPO220J100TRPF NMC0805NPO270J50TRPF NMC0805NPO681F50TRPF
NMC0805NPO820J50TRPF NMC1206X7R102K50TRPF NMC1210Y5V105Z50TRPLPF NMC-L0402NPO7R0C50TRPF NMC-L0603NPO2R2B50TRPF NMC-P0805NPO221J500TRPLPF NMC-P1206X7R103K1KVTRPLPF NMC-Q0402NPO8R2D200TRPF
C1206C101J1GAC C1608C0G2A221J C1608X7R1E334K C2012C0G2A472J 2220J2K00562KXT KHC201E225M76N0T00
1812J2K00332KXT CCR06CG153FSV CDR14BP471CJUR CDR31BX103AKWR CDR33BX683AKUS CGA2B2C0G1H010C
CGA2B2C0G1H040C CGA2B2C0G1H050C CGA2B2C0G1H060D CGA2B2C0G1H070D CGA2B2C0G1H120J CGA2B2C0G1H151J
CGA2B2C0G1H1R5C CGA2B2C0G1H2R2C CGA2B2C0G1H390J CGA2B2C0G1H391J CGA2B2C0G1H3R3C CGA2B2C0G1H680J
CGA2B2C0G1H6R8D