

MT1000

Altera medical-grade, thin wall, semirigid, fluoropolymer heat-shrinkable tubing

Altera MT1000 heat-shrinkable tubing is tough, semirigid tubing with a very thin wall construction. It is especially suitable for applications requiring hightemperature performance, outstanding resistance to abrasion and cut-through, and excellent resistance to a variety of fluids. In polar media, such as aqueous systems and alcohols, property retention and dimensional stability are exceptional.

The translucent polyvinylidene fluoride material permits visual inspection of

covered components. Altera MT1000 tubing provides electrical insulation and strain relief for components that are exposed to high temperatures either during operation or during sterilization. With its thin-wall construction, Altera MT1000 tubing is ideal for applications that have clearance constraints.

Altera MT1000A tubing provides an inner layer of adhesive. During installation, the USP Class VI adhesive layer will reflow

around the substrate to provide sealing or blocking against fluids and other bioburden materials.

Altera MT1000 tubing may be sterilized by radiation, ethylene oxide, steam, and dry heat with no significant change in properties. It is fabricated from materials that meet the requirements of U.S. Pharmacopeia (USP) Class VI plastics (contact with injectables and body fluids or tissue).

Temperature rating

Full recovery temperature:	175°C	
Continuous operating temperature:	MT1000: -55°C to 155°C	MT1000A: -55°C to 125°C
Recommended maximum temperature for use as a primary insulator:	135°C	

Specifications*

Туре	Raychem	Material	Master File Number	
MT1000	MT1000 SCD	USP Class VI	MAF-444	
MT1000A	MT1000A SCD	USP Class VI	MAF-798	

When ordering, always specify latest issue.

Dimensions (millimeters/inches)



	Inside diameter		Wall thickness		Inside diameter		Wall thickness	
	D (min.)	d (max.)	W		D (min.)	d (max.)	W	
	Expanded	Recovered	Recovered		Expanded	Recovered	Recovered	
Size	as supplied	after heating	after heating**	Size	as supplied	after heating	after heating**	
3/64***	1.2 0.046	0.6 0.023	0.25 ± 0.05 0.010 ± 0.002	3/8	9.5 0.375	4.7 <i>0.187</i>	0.33 ± 0.05 0.013 ± 0.002	
1/16	1.6 0.063	0.8 0.031	0.25 ± 0.05 0.010 ± 0.002	1/2	12.7 0.500	6.4 0.250	0.33 ± 0.05 0.013 ± 0.002	
3/32	2.4 0.093	1.2 0.046	0.25 ± 0.05 0.010 ± 0.002	3/4***	19.1 <i>0.750</i>	9.5 <i>0.375</i>	0.43 ± 0.08 0.017 ± 0.003	
1/8	3.2 0.125	1.6 0.062	0.25 ± 0.05 0.010 ± 0.002	1***	25.4 1.000	12.7 0.500	0.48 ± 0.08 0.019 ± 0.003	
3/16	4.7 <i>0.187</i>	2.4 0.093	0.25 ± 0.05 0.010 ± 0.002	1 1/2***	38.1 <i>1.500</i>	19.1 <i>0.750</i>	0.51 ± 0.08 0.020 ± 0.003	
1/4	6.4 0.250	3.2 0.125	0.33 ± 0.05 0.013 ± 0.002					

Wall thickness will be less if tubing recovery is restricted during shrinkage. *Nonstandard size; available by special order only.

Ordering information

Colors	Standard	Translucent	
	Nonstandard	Black	
Size selection	e selection Always order the largest size that will shrink snugly over the component being covered.		
A variety of special order sizes are available.			
Standard packaging	4-foot lengths, double-bagged		
Ordering description	Specify product name, size, and color; for example, MT1000-1/8-0 (0=Black).		
	Specify MT1000A for adhesive-lined constructions in sizes 1/8" and larger only (special order).		

Specification values

	Property	Unit	Requirement	Method of test
Physical	Dimensions	mm <i>(inches)</i>	See reverse	ASTM D 2671
	Longitudinal change	percent	+0, -10	ASTM D 2671
	Tensile strength	psi <i>(Mpa)</i>	5000 <i>(34.5)</i> minimum	ASTM D 2671
	Ultimate elongation	percent	150 minimum	ASTM D 2671
	Secant modulus (expanded)	Psi <i>(Mpa)</i>	1 X 10 ⁵ <i>(690)</i> minimum	ASTM D 2671
	Heat resistance (168 hours at 250°C/482°F)			ASTM D 2671
	Followed by test for:			
	Ultimate Elongation	percent	50 minimum	ASTM D 2671
Electrical	Dielectric strength	volts/mil (volts/mm)		ASTM D 2671
	Sizes 3/64 through 1/2		800 <i>(31,500</i>) minimum	
	Sizes 3/4 through 1 1/2		600 <i>(23,600</i>) minimum	
	Dielectric withstand 3000 V, 60 Hz	seconds	60 minimum	ASTM D 2671
Chemical	Fluid resistance (24 hours at 23°C/ <i>73°F</i>) in: Isopropyl Alcohol 5% Saline Solution Cidex*†			ASTM D 2671
	Followed by tests for:			
	Dielectric strength	volts/mil (volts/mm)		ASTM D 2671
	Sizes 3/64 through 1/2		700 <i>(27,600</i>) minimum	
	Sizes 3/4 through 1 1/2		500 <i>(19,700</i>) minimum	
	Tensile strength	psi <i>(Mpa)</i>	5000 <i>(34.5)</i> minimum	ASTM D 2671
	Heavy metals analysis Cadmium Mercury Lead Bismuth Antimony	ppm	1 maximum (total of all metals)	USP XXII Physiochemical Tests - Plastics

Typical performance values

	Property	Unit	Performance	Method of Test
Electrical	Dielectric strength** volts/mil (volts/mm)			ASTM D 2671
	0.005″ < IWT ≤ 0.010″		1200 <i>(47,244)</i>	
	0.010" < IWT ≤ 0.015"		1000 <i>(39,370</i>)	
	$0.015'' < IWT \le 0.020''$		700 (27,559)	
Adhesive Properties	Ring and bell softening point	°C	165 ± 10	ASTM E 28
(MT1000A only)***	Adhesion to:			
	Polypropylene		Poor	
	HDPE		Poor	
	Polyurethane		Excellent	
	PVČ		Excellent	
	Steel		Excellent	

*Trademark of Johnson & Johnson Company **IWT = Installed wall thickness ***Not recommended for use on Teflon or silicone substrates. +Or equivalent dilute glutaraldehyde sterilizing solution.

Note: Consult the MT1000 SCD for specific details about test procedures.

Altera and Raychem are trademarks of Tyco Electronics Corporation. Teflon is a trademark of E.I. du Pont de Nemours and Company.

Users should independently evaluate the suitability of the product for their application.

Tyco Electronics Corporation 300 Constitution Drive Faraday Road 3816 Noborito, Tama-ku Asia Pacific Headquarters Dorcan, Swindon, SN3 5HH Menlo Park, CA 94025-1164 Kawasaki, Kanagawa 214-8533 26 Ang Mo Kio, Industrial Park 2 USA United Kingdom Japan Singapore 569507 Tel: (800) 926-2425 (US & Canada) Tel: +44 1793 528171 Tel: +81 44 900 5102 Tel: +65 4866 151 Tel: +1 (650) 361-3860 (All other countries)

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics Corporation makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Tyco Electronics Corporation's only obligations are those in the Standard Terms and Conditions of Sale for these products and in no case will Tyco Electronics Corporation be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use, or misuse of the product. Tyco Electronics Corporation's Specifications are subject to change without notice. In addition, Tyco Electronics Corporation reserves the right to make changes in materials or processing without notification to the Buyer which do not affect compliance with any applicable specification.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Heat Shrink Tubing and Sleeves category:

Click to view products by TE Connectivity manufacturer:

Other Similar products are found below :

 770-006S102
 5685710001
 CR8248-000
 CR9960-000
 603312-4
 607381P039
 611112-000
 617867N001
 6500750004
 CZ1420-000
 D-306-38

 770-007A303
 770-010Y106W1
 770-010Y706W1
 7771210001
 MFP-1/4"-Clear
 MFP-3/64"-Clear
 790-3012
 MFT-MT2000-NO.14-0-SP

 MHHT-4-15K2-G-104
 MIL-LT-1-1/2-4-SP
 MIL-LT-1-1/2-9-STK
 MIL-LT-1/2-2-STK
 MIL-LT-3/0-SP
 MIL-LT-3/32-0-SP
 MIL-LT-3/32-0-SP

 SP
 MIL-LT-3/4-6-SP
 MIL-LT-3/8-0-SP
 8159270001
 839602-000
 8423-6
 FP301-116-6"-Black
 FP301-1/2-48"-Black
 FP301-12-48"-Black-Hdr

 Hdr
 FP301-1/4-48"-Black
 FP301-1/4-48"-White-Hdr
 FP301-1-6"-Clear
 FP301-18-48"-Black-Hdr
 FP301-1/8-6"-Black
 FP301-18-6"-Black-Hdr

 Bulk
 FP301-316-48"-Blue-Hdr
 FP301-316-6"-Clear
 FP301-332-6"-Black
 912229N002
 120-126-16BL
 121-001-09
 121-018-32
 121-018-40

 121-123-1-1-32BTC
 121-123-1-1-40BTC
 121-123-1-1-40BTC
 120-126-16BL
 121-001-09
 121-018-32
 121-018-40