

# AN11689

## Recommendations for PCB assembly of DSN1006

Rev. 1 — 29 July 2015

Application note

### Document information

Info	Content
<b>Keywords</b>	DSN1006, DSN1006-2, DSN1006U-2, SOD993, SOD995, 0402 package size, reflow soldering, surface mount, solder paste, stencil aperture, Printed-Circuit Board (PCB), Solder Mask Defined (SMD), footprint, landing pattern, pick and place, Chip-Scale Package (CSP)
<b>Abstract</b>	<p>This application note provides guidelines for board assembly of the ultra-small DSN1006 (<math>1.0 \times 0.6 \text{ mm}^2</math>) chip-scale package. The main focus is on recommendations for reflow soldering.</p> <p>For general information about footprint design and reflow soldering see application note AN10365 (Surface mount reflow soldering description).</p>



## Revision history

Rev	Date	Description
1	20150729	Initial version

## Contact information

For more information, please visit: <http://www.nxp.com>

For sales office addresses, please send an email to: [salesaddresses@nxp.com](mailto:salesaddresses@nxp.com)

## 1. Introduction

Due to the trend of reduced dimensions and increased density of functionality in smartphones and other mobile devices, there is an increasing request from the industry for extremely small components. NXP supports this trend with the new DSN1006-2 (SOD993, symmetrical contacts) and DSN1006U-2 (SOD995, asymmetrical contacts) packages. They are ultra small surface-mount chip-scale diode packages with a size of only 1.0 mm × 0.6 mm × 0.27 mm (0402).

Due to the very small size of the component, NXP investigated the board assembly process intensively in order to offer board mounting recommendations.

This includes PCB mounting pads, stencil apertures, solder paste and board assembly process parameters.

Using the recommended dimensions for pads and stencil as described in this document will help to achieve:

- optimum stand-up height
- minimum tilt
- minimum rotation
- good board assembly process performance

While this application note helps minimizing any unexpected failures, following the advice in this document is not a guarantee for a perfect Surface-Mount Technology (SMT) assembly result. The results may differ depending on the machine capability, ambient conditions, material, etc.

## 2. DSN1006 (SOD993, SOD995): package details

DSN1006-2 (SOD993) and DSN1006U-2 (SOD995) are Discrete Silicon No-leads (DSN) packages. They feature tin (Sn) plated metal contacts under the package (bottom terminations) similar to Discrete Flat No-leads (DFN) style packages. The DSN-style package allows 100 % utilization of the package area for active silicon, offering a significant performance advantage per board area compared to products in plastic-molded packages.

Key Features:

- Ultra small and flat package (1.0 × 0.6 × 0.27 mm<sup>3</sup>)
- Sn-plated contacts for soldering on PCB
- Symmetrical contact pads for DSN1006-2 (SOD993)
- Asymmetrical contact pads for DSN1006U-2 (SOD995)


The visual appearance of DSN1006-2 (SOD993) is shown in [Figure 1](#) whereas [Figure 2](#) shows the package dimensions.

The visual appearance of DSN1006U-2 (SOD995) is shown in [Figure 3](#) whereas [Figure 4](#) shows the package dimensions.



Fig 1. DSN1006-2 (SOD993): visual appearance

DSN1006-2, leadless ultra small package; 2 terminals; body 1.0 x 0.6 x 0.27 mm SOD993



Dimensions (mm are the original dimensions)

Unit	A	A <sub>1</sub>	b	D	E	e <sub>1</sub>	L
mm	max	0.30	0.03	0.51	0.65	1.05	0.26
	nom					0.65	
	min	0.24		0.49	0.55	0.95	0.24

Note

1. The marking bar indicates the cathode.

sod993\_po


Outline version	References			European projection	Issue date
	IEC	JEDEC	JEITA		
SOD993					14-10-24 14-10-24

Fig 2. DSN1006-2 (SOD993): package dimensions



Fig 3. DSN1006U-2 (SOD995): visual appearance

DSN1006U-2, leadless ultra small package; 2 terminals; body 1.0 x 0.6 x 0.27 mm SOD995



Dimensions (mm are the original dimensions)

Unit	A	A <sub>1</sub>	b	D	E	e <sub>1</sub>	e <sub>2</sub>	L	L <sub>1</sub>
mm	max	0.30	0.03	0.51	0.65	1.05		0.26	0.41
	nom						0.325	0.25	
	min	0.24		0.49	0.55	0.95		0.24	0.39

Note

1. The marking bar indicates the cathode.

sod995\_po

Outline version	References			European projection	Issue date
	IEC	JEDEC	JEITA		
SOD995					14-12-09 15-05-29

Fig 4. DSN1006U-2 (SOD995): package dimensions

### 3. PCB solder pattern

#### 3.1 Solder pad design: general options

There are two types of solder pad / solder resist designs:


Solder Mask Defined (SMD) and Non-Solder Mask Defined (NSMD).

SMD is a method of designing the solder resist to partially overlap the copper (Cu) landing pattern on the PCB. NSMD designs have a gap between the solder resist and the Cu landing pattern on the PCB. These two types are described in more detail in the next chapter.

##### 3.1.1 SMD solder pad versus NSMD solder pad

If the solder mask extends onto the solder lands, the remaining solderable area is Solder Mask Defined (SMD). The effective solder pad is equal to the copper area that is not covered by the solder mask. This situation is illustrated in [Figure 5](#), left column. In case of an SMD pad, the copper will normally extend 75 μm down to 50 μm underneath the solder mask on all sides. In other words, the copper dimension is 0.1 mm to 0.15 mm larger than the solder mask dimension. These values may vary depending on the class of PCBs used. This allows tolerances in copper etching and solder mask placement during PCB production.

If the solder mask layer starts outside of the solder lands, and does not cover the copper, this is referred to as Non-Solder Mask Defined (NSMD). The effective solder pad is equal to the copper area. In case of an NSMD, the solder mask should be at least 50 μm away from the solder land on all sides. In other words, the solder mask dimension is 100 μm larger than the copper dimension. These values may vary depending on the class of PCBs used. The main requirement is that the solder mask is sufficiently far away from the copper, such that - with the given tolerances in solder mask application - it does not extend onto the copper. An NSMD footprint is shown in [Figure 5](#), right column.




### 3.2 Solder pad design for DSN1006 packages (SOD993, SOD995)


#### 3.2.1 Recommended reflow solder footprints

Based on the small dimensions of 1006 (0402) devices and the given tolerances for PCB manufacturing, it is recommended to use Non-Solder Mask Defined (NSMD) solder pads.

The DSN1006-2 (SOD993) solder footprint with dimensions and the solder footprint together with the package outline are shown in [Figure 6](#).



The DSN1006U-2 (SOD995) solder footprint with dimensions and the solder footprint together with the package outline are shown in [Figure 7](#).






## 4. Solder stencil

### 4.1 Stencil recommendations


Due to small apertures and pad dimensions, use a high-quality stainless-steel stencil manufactured by laser-cut and with electropolish or plasma coating.

The recommended stencil thickness is 100  $\mu\text{m}$  for the DSN1006 packages.

For the DSN1006-2 (SOD993) recommended NXP footprint (see [Section 3.2.1](#), [Figure 6](#)), the optimum stencil aperture is shown in [Figure 8](#).




For the DSN1006U-2 (SOD995) recommended NXP footprint (see [Section 3.2.1](#), [Figure 7](#)), the optimum stencil aperture is shown in [Figure 9](#).



### 4.2 Stencil aperture design

Area and aspect ratio are key design-guidelines for stencil apertures. The area ratio for a standard approach is > 0.66. Smaller values are possible with adequate process control. Of course, it depends on the manufacturing environment and other requirements of the manufacturer.

The aspect ratio should be > 1.5 which is less critical to fulfil. For explanation of area and aspect ratio, refer to [Figure 10](#).



**Table 1. Area and aspect ratio for stencil apertures as recommended**  
*Stencil thickness T = 100 μm*

NXP recommended footprint	Aperture size	Area ratio target > 0.62	Aspect ratio target > 1.5
DSN1006-2 (SOD993)	250 × 200 μm <sup>2</sup>	0.83	2.50
DSN1006U-2 (SOD995)	370 / 500 × 500 μm <sup>2</sup>	minimum 1.06	minimum 3.70

[Table 1](#) shows the values for aspect and area ratio of the optimum stencil apertures with a stencil thickness of 100 μm. It results in acceptable area ratios for the NXP footprint recommendations.

## 5. Solder paste

Besides stencil aperture and thickness, the used solder paste has a significant impact on the printing performance. As shown in [Table 2](#), solder pastes are available in different solder powder grain sizes.

**Table 2. Solder paste types**

Type	Powder grain size in $\mu\text{m}$			
	Less than 0.5 % larger than	10 % max. between	80 % max between	10 % max. less than
1	160	150-160	75-150	75
2	80	75-80	45-75	45
3	60	45-60	25-45	25
4	50	38-50	20-38	20
5	40	25-40	15-25	15
6	25	15-25	5-15	5
7	15	11-15	2-11	2

Use a solder paste type 4 and higher (smaller grain size) in combination with a stencil aperture thickness of 100  $\mu\text{m}$  for the DSN1006 (SOD993, SOD995) packages. As solder paste is sensitive to age, temperature, and humidity, follow the handling recommendations of the paste manufacturer.

## 6. Soldering process

For soldering of DSN1006 packages, following standard reflow processes and typical temperature profiles are suitable:

- Convection reflow under nitrogen atmosphere is preferred to improve the solder wetting.
- Convection reflow under air atmosphere also works, but solder joint surfaces are rough, flux residues often become darker and the soldering behavior may deteriorate.
- Vapor phase soldering is also possible.

A reflow solder profile for tin-silver-copper alloys, so-called SAC alloys (SnAg3.8Cu0.7) based on the IPC/JEDEC joint industry standard J-STD-020D is recommended. Refer to [Figure 11](#) and [Table 3](#).




Fig 11. Reflow solder profile based on IPC/JEDEC J-STD-020D

Table 3. Pb-free profile feature and specification based on IPC/JEDEC J-STD-020D

Profile feature	Values for Pb-free assembly
Average ramp-up rate ( $T_{smax}$ to $T_p$ )	3 °C/s maximum
Preheat	
Minimum temperature ( $T_{smin}$ )	150 °C
Maximum temperature ( $T_{smax}$ )	200 °C
Time ( $t_s$ ) from $T_{smin}$ to $T_{smax}$	60 s to 180 s
Liquidus temperature ( $T_L$ )	217 °C
Time ( $t_L$ ) maintained above $T_L$	60 s to 150 s
Peak/classification temperature ( $T_p$ )	260 °C
Time within 5 °C of actual peak temperature ( $t_p$ )	10 s to 30 s
Ramp-down rate	6 °C/s maximum
Time 25 °C to peak temperature ( $t_{25°C \text{ to peak}}$ )	8 minutes maximum

## 7. Handling recommendations


Besides the PCB and stencil design requirements, the ultra small size of the DSN1006 and as consequence the low weight of the component requires that some attention be paid to the pick and place (P&P) process. Electrostatic charge may cause problems during the pick and place (tape out) process. NXP has implemented preventive measures such as using a conductive plastic carrier tape (embossed tape).

For rework, use equipment suitable for the ultra small package size and for handling bare silicon devices. Manual handling with tweezers (e.g. for repair) is not recommended.


## 8. Summary

### 8.1 Recommended solder footprint and stencil aperture

The recommended solder footprint including stencil aperture are shown in [Figure 12](#) for DSN1006-2 (SOD993) and in [Figure 13](#) for DSN1006U-2 (SOD995).



SOD995



Recommended stencil thickness: 100 μm

Fig 13. DSN1006U-2 (SOD995): solder footprint and stencil aperture

## 8.2 Further recommendations

### 8.2.1 Stencil layout and solder paste

- Stencil thickness of 100 μm in combination with type 4 solder paste (refer to [Table 2](#)) is recommended.
- A stencil aperture dimension as shown in [Figure 8](#) and [Figure 12](#) is recommended for DSN1006-2 (SOD993).
- A stencil aperture dimension as shown in [Figure 9](#) and [Figure 13](#) is recommended for DSN1006U-2 (SOD995).
- To get best printing (and soldering) results, control the cleaning cycle of the stencil.

### 8.2.2 Solder pad design

- Non-Solder Mask Defined (NSMD) pads with a gap between Cu pad and solder resist of 50 μm are recommended.
- Conductor (Cu trace) between solder pads on PCB is not recommended.
- Do not connect solder pads by μ-via.
- Connection by Cu traces (lines) is preferred.

### 8.2.3 Soldering process

- Convection reflow under nitrogen atmosphere is preferred.
- Convection reflow under air atmosphere also works, but:
  - Using an unfavorable layout, products lean towards undefined tilting and rotation and solder joints tend to increase voiding.
  - Solder joint surfaces are rough, flux residues often become darker and the soldering behavior may deteriorate.
- Vapor phase soldering is also possible.

### 8.2.4 Handling recommendations

- Manual handling with tweezers (e.g. for repair) is not recommended.
- Keep control of thawing time of solder paste bundle to avoid too much humidity in paste.
- To prevent drying of flux in solder paste, maintain the relative humidity of shop floor at solder paste print until reflow to 40 % to 60 %.



## 9. Legal information

### 9.1 Definitions

**Draft** — The document is a draft version only. The content is still under internal review and subject to formal approval, which may result in modifications or additions. NXP Semiconductors does not give any representations or warranties as to the accuracy or completeness of information included herein and shall have no liability for the consequences of use of such information.

### 9.2 Disclaimers

**Limited warranty and liability** — Information in this document is believed to be accurate and reliable. However, NXP Semiconductors does not give any representations or warranties, expressed or implied, as to the accuracy or completeness of such information and shall have no liability for the consequences of use of such information. NXP Semiconductors takes no responsibility for the content in this document if provided by an information source outside of NXP Semiconductors.

In no event shall NXP Semiconductors be liable for any indirect, incidental, punitive, special or consequential damages (including - without limitation - lost profits, lost savings, business interruption, costs related to the removal or replacement of any products or rework charges) whether or not such damages are based on tort (including negligence), warranty, breach of contract or any other legal theory.

Notwithstanding any damages that customer might incur for any reason whatsoever, NXP Semiconductors' aggregate and cumulative liability towards customer for the products described herein shall be limited in accordance with the *Terms and conditions of commercial sale* of NXP Semiconductors.

**Right to make changes** — NXP Semiconductors reserves the right to make changes to information published in this document, including without limitation specifications and product descriptions, at any time and without notice. This document supersedes and replaces all information supplied prior to the publication hereof.

**Suitability for use** — NXP Semiconductors products are not designed, authorized or warranted to be suitable for use in life support, life-critical or safety-critical systems or equipment, nor in applications where failure or malfunction of an NXP Semiconductors product can reasonably be expected to result in personal injury, death or severe property or environmental damage. NXP Semiconductors and its suppliers accept no liability for inclusion and/or use of NXP Semiconductors products in such equipment or applications and therefore such inclusion and/or use is at the customer's own risk.

**Applications** — Applications that are described herein for any of these products are for illustrative purposes only. NXP Semiconductors makes no representation or warranty that such applications will be suitable for the specified use without further testing or modification.

Customers are responsible for the design and operation of their applications and products using NXP Semiconductors products, and NXP Semiconductors accepts no liability for any assistance with applications or customer product

design. It is customer's sole responsibility to determine whether the NXP Semiconductors product is suitable and fit for the customer's applications and products planned, as well as for the planned application and use of customer's third party customer(s). Customers should provide appropriate design and operating safeguards to minimize the risks associated with their applications and products.

NXP Semiconductors does not accept any liability related to any default, damage, costs or problem which is based on any weakness or default in the customer's applications or products, or the application or use by customer's third party customer(s). Customer is responsible for doing all necessary testing for the customer's applications and products using NXP Semiconductors products in order to avoid a default of the applications and the products or of the application or use by customer's third party customer(s). NXP does not accept any liability in this respect.

**Export control** — This document as well as the item(s) described herein may be subject to export control regulations. Export might require a prior authorization from competent authorities.

**Evaluation products** — This product is provided on an "as is" and "with all faults" basis for evaluation purposes only. NXP Semiconductors, its affiliates and their suppliers expressly disclaim all warranties, whether express, implied or statutory, including but not limited to the implied warranties of non-infringement, merchantability and fitness for a particular purpose. The entire risk as to the quality, or arising out of the use or performance, of this product remains with customer.

In no event shall NXP Semiconductors, its affiliates or their suppliers be liable to customer for any special, indirect, consequential, punitive or incidental damages (including without limitation damages for loss of business, business interruption, loss of use, loss of data or information, and the like) arising out of the use of or inability to use the product, whether or not based on tort (including negligence), strict liability, breach of contract, breach of warranty or any other theory, even if advised of the possibility of such damages.

Notwithstanding any damages that customer might incur for any reason whatsoever (including without limitation, all damages referenced above and all direct or general damages), the entire liability of NXP Semiconductors, its affiliates and their suppliers and customer's exclusive remedy for all of the foregoing shall be limited to actual damages incurred by customer based on reasonable reliance up to the greater of the amount actually paid by customer for the product or five dollars (US\$5.00). The foregoing limitations, exclusions and disclaimers shall apply to the maximum extent permitted by applicable law, even if any remedy fails of its essential purpose.

**Translations** — A non-English (translated) version of a document is for reference only. The English version shall prevail in case of any discrepancy between the translated and English versions.

### 9.3 Trademarks

Notice: All referenced brands, product names, service names and trademarks are the property of their respective owners.

## 10. Contents

<b>1</b>	<b>Introduction</b> .....	<b>3</b>
<b>2</b>	<b>DSN1006 (SOD993, SOD995): package details</b>	<b>3</b>
<b>3</b>	<b>PCB solder pattern</b> .....	<b>6</b>
3.1	Solder pad design: general options .....	6
3.1.1	SMD solder pad versus NSMD solder pad .....	6
3.2	Solder pad design for DSN1006 packages (SOD993, SOD995) .....	7
3.2.1	Recommended reflow solder footprints .....	7
<b>4</b>	<b>Solder stencil</b> .....	<b>9</b>
4.1	Stencil recommendations .....	9
4.2	Stencil aperture design .....	11
<b>5</b>	<b>Solder paste</b> .....	<b>12</b>
<b>6</b>	<b>Soldering process</b> .....	<b>12</b>
<b>7</b>	<b>Handling recommendations</b> .....	<b>13</b>
<b>8</b>	<b>Summary</b> .....	<b>14</b>
8.1	Recommended solder footprint and stencil aperture .....	14
8.2	Further recommendations .....	15
8.2.1	Stencil layout and solder paste .....	15
8.2.2	Solder pad design .....	15
8.2.3	Soldering process .....	16
8.2.4	Handling recommendations .....	16
<b>9</b>	<b>Legal information</b> .....	<b>17</b>
9.1	Definitions .....	17
9.2	Disclaimers .....	17
9.3	Trademarks .....	17
<b>10</b>	<b>Contents</b> .....	<b>18</b>

Please be aware that important notices concerning this document and the product(s) described herein, have been included in section 'Legal information'.

© NXP Semiconductors N.V. 2015.

All rights reserved.

For more information, please visit: <http://www.nxp.com>

For sales office addresses, please send an email to: [salesaddresses@nxp.com](mailto:salesaddresses@nxp.com)

Date of release: 29 July 2015

Document identifier: AN11689

## X-ON Electronics

Largest Supplier of Electrical and Electronic Components

*Click to view similar products for [nxp manufacturer:](#)*

Other Similar products are found below :

[MC13211R2](#) [PCA9518PW,112](#) [LFSTBEB865X](#) [MC33399PEFR2](#) [PCA9551PW,112](#) [MC34825EPR2](#) [CBTW28DD14AETJ](#) [PCF8583P](#)  
[MC68340AB16E](#) [MC8640DTVJ1250HE](#) [EVBCRTOUCH](#) [MC9S08PT8AVTG](#) [MC9S08SH32CTL](#) [MCF54415CMJ250](#) [MCIMX6Q-SDB](#)  
[MCIMX6SX-SDB](#) [74ALVC125BQ,115](#) [74HC4050N](#) [74HC4514N](#) [MK21FN1M0AVLQ12](#) [MKV30F128VFM10](#) [FRDM-K66F](#) [FRDM-](#)  
[KW40Z](#) [FRDM-MC-LVBLDC](#) [PESD18VF1BSFYL](#) [PMF63UNEX](#) [PSMN4R0-60YS,115](#) [HEF4028BPN](#) [RAPPID-567XFSW](#)  
[MPC565MVR56](#) [MPC574XG-176DS](#) [MPC8548VJAUJD](#) [MPC860PCVR66D4](#) [BCV61A,215](#) [BFU520XAR](#) [BT137-600E](#) [BT137S-600D.115](#)  
[BT138-600E.127](#) [BT139X-600.127](#) [BT258-600R.127](#) [BUK7628-100A118](#) [BUK765R0-100E.118](#) [P5020NSE7VNB](#) [S12ZVML12EVBLIN](#)  
[SCC2692AC1N40](#) [LPC1785FBD208K](#) [LPC2124FBD64/01](#) [LS1020ASN7KQB](#) [LS1020AXN7HNB](#) [LS1020AXN7KQB](#)