

Technical Data Sheet**Panduit GMH5 Film Lamination**

This specification is intended to outline the physical and chemical properties of *PANDUIT*'s GMH5 material and include the following printable material identifiers:

Printable Material Suffixes		
Y1T		

PRODUCT SPECIFICATIONS:

Description:	Material is RoHS compliant (European Union directive 2002/95/EC). GMH5 consists of a topcoated 2 mil polyester film laminated to a 5.0 mil polyester film. This material is halogen free.
Print Methods:	This material is recommended for thermal transfer printing.
Standard Colors:	White
Thickness:	8.0 +/- 0.5 mils
Service Temperature Range:	-10°F to 302°F (-23°C to 150°C)
Minimum Application Temperature:	50°F (10°C)
Storage Conditions:	Store at 70°F (21°C) and 50% Relative Humidity.

PROPERTIES:**PERFORMANCE:**

Tensile Strength:	MD: 140 +/- 14.0 lbs./inch width (PSTC-131) TD: 160 +/- 16.0 lbs./inch width (PSTC-131)
Elongation:	MD: 100% +/- 10% (PSTC-131) TD: 55% +/- 10% (PSTC-131)
UV Resistance:	*3000 hours no visual change observed (ASTM G154).
Humidity Resistance:	30 days at 100°F(37°C) and 95% R.H, no visible change observed
Abrasion Resistance:	CS-10 wheels/250 gm wt/50 cycles, no visible change observed

*3000 hours equates to 5 years of assimilated Outdoor UV exposure.

CHEMICAL/SOLVENT RESISTANCE:

The testing was conducted at room temperature. Samples were thermal transfer printed with Panduit RMR*BL/RMER*BL black ribbon on the Panduit TDP43MY/TDP43ME printer. Separate sets were conditioned for 24 hours before being immersed in the following solvents for a period of 1 hour and 24 hours. After the samples were removed from the immersed solvents, they were rubbed 10 times with a lint free gauze. Visual observations were noted for any smear or loss of legibility.

Technical Data Sheet**1 Hour Immersion**

Chemical/Solvent	Visual Observation for White Tag with RMR*BL, RMER*BL black ribbon
Jet Fuel	No change
Gasoline	Loss of print legibility
Methyl Ethyl Ketone	Loss of print legibility
1:1:1 TCE	No change
Trichloroethylene	Loss of print legibility
409 Cleaner	No change
Alpha Flux 200L	No change
Toluene	Loss of print density
3% Alconox	No change
10% Sodium Hydroxide	No change
10% Sulfuric Acid	No change
Degreaser	No change

24 Hours Immersion

Chemical/Solvent	Visual Observation for White Tag with RMR*BL, RMER*BL black ribbon
Isopropyl Alcohol	No change
Water 150F	No change
Salt Water	No change
SAE 30 Motor Oil	No change
Hydraulic Fluid	No change
Skydrol	Loss of print density
Methanol/Water	No change
Ethylene Glycol	No change
ASTM #3 Oil	No change

LIMITED WARRANTY

All *PANDUIT* Identification Solution Products (except for Software programs) are warranted to be free from defects in material and workmanship at the time of sale but our obligation under this warranty is limited to replacement of the product proved to be defective within 6 months from the date of sale, or in the case of printers, within 90 days from the date of sale. This warranty is void if the products or printers are modified, altered or misused in any way. Use of *PANDUIT* printers with any product other than the specified *PANDUIT* products for which the printer was designed constitutes misuse. Before using, the user shall determine the suitability of the product for its intended use and user assumes all risk and liability whatsoever in connection therewith. The foregoing may not be altered except by an agreement signed by officers or seller and manufacturer.

NEITHER *PANDUIT* OR SELLER SHALL BE LIABLE FOR ANY OTHER INJURY, LOSS OR DAMAGE, WHETHER DIRECT OR CONSEQUENTIAL, ARISING OUT OF THE USE OF, OR THE INABILITY TO USE THE PRODUCT OR THE PRINTER.

THIS WARRANTY IS MADE IN LIEU OF AND EXCLUDES ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS OF PARTICULAR USE ARE SPECIFICALLY EXCLUDED.

The information contained in this literature is based on our experience to date and is believed to be reliable. It is intended as a guide or use by persons having technical skill at their own discretion and risk. We do not guarantee favorable results or assume any liability in connection with its use. Dimensions contained herein are for reference purposes only. This publication is not to be taken as a license to operate under, or a recommendation to infringe any existing patents. This supersedes and voids all previous literature, etc.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [Wire Labels & Markers](#) category:

Click to view products by [Panduit](#) manufacturer:

Other Similar products are found below :

[89078GBEST](#) [89082GBESR](#) [89082GBEST](#) [PCL025-4](#) [5761-2SF](#) [58400](#) [586R734H02](#) [M1.040.0000.6](#) [CRS-CM5M](#) [CRS-M18M](#) [CS1836-000](#) [CS8626-000](#) [CU6337-000](#) [CU6342-000](#) [CU6343-000](#) [CWD01-0](#) [CWD012-0](#) [CWD012-7](#) [CWD015-3](#) [CWD015-7](#) [CWD02-0](#) [CWD02-3](#) [CWD02-4](#) [CWD02-6](#) [CWD02-8](#) [CWD02-A](#) [CWD02-D](#) [CWD02-H](#) [CWD02-K](#) [CWD02-L](#) [CWD02-M](#) [CWD02-P](#) [CWD02-Q](#) [CWD02-R](#) [CWD02-U](#) [CWD02-W](#) [CWD02-Y](#) [CWD03-+](#) [CWD03-0](#) [CWD03-P](#) [CWD06-0](#) [CWD06-8](#) [CWD06-9](#) [CWD06-L](#) [CWD06-N](#) [CWD09-0](#) [CWD09-5](#) [CWD09-7](#) [6806810001](#) [CZ2857-000](#)