**Technical Data Sheet** 

18900 Panduit Drive Tinley Park, IL 60487

Customer Service: 800-777-3300

TDS: Effective Date: Revision:

**GMNT** 16JUL12

# **High Temperature Marker Tag**

This specification is intended to outline the physical and chemical properties of *PANDUIT*'s GMNT material for identification purposes.

FPT	
FQT	
FQT-B	

## **PRODUCT SPECIFICATIONS:**

Description: Material is RoHS compliant (European Union directive

> 2002/95/EC). GMNT is a crosslinked, thermal transfer printable polyolefin. When printed using RMR\*BL, RMER4BL-A, and RMH\*BL thermal transfer ribbons it will also meet MIL-M-81531. This product has been tested for use as an identification marker for use in (Class 1E) harsh environments in various high

temperature power plants.

RMR\*BL, RMER4BL-A, RMH\*BL (recommended for best print Recommended Ribbons:

quality)

White **Standard Colors:** 

Thickness: 24 + / - 2 mils

Service Temperature Range: Minus 67F to 275F (Minus 55C to 135C)

Store at 70°F(21°C) and 50% Relative Humidity **Storage Conditions:** 

#### **PROPERTIES: PERFORMANCE:**

1500 psi minimum (ASTM D638) Tensile Strength:

200% minimum (ASTM D 638) **Elongation Ultimate:** 

500 volts/mil minimum (ASTM D876) Dielectric Strength:

Water Absorption: 0.5% maximum (ASTM D570)

Printability: Product meets print performance as per MIL-M-81531 Flammability: Product complies with the UL94-V2 flammability test

Specific Gravity: 1.35 max (ASTM 792)

The samples were tested in a QUV weather tester as per test procedure **QUV** Outdoor Durability:

ASTM G-154. Observations made at \*3000 hours exposure showed no

loss in legend or change in material.

Page 1 of 5 © 2007 PANDUIT Corp

18900 Panduit Drive Tinley Park, IL 60487

Customer Service: 800-777-3300

TDS: Effective Date: Revision:

**GMNT** 16JUL12 6

## **Technical Data Sheet**

#### **CHEMICAL/SOLVENT RESISTANCE:**

The testing was conducted at room temperature. Samples were thermal transfer printed with Panduit Resin ribbon on Panduit printer.

Chemical/Solvent	7 DAY IMMERSION	DIP TEST	RUB TEST
30% Sulfuric acid	1	1	1
10% Sulfuric acid	1	1	1
30% Hydrochloric	1	1	1
acid			
10% Hydrochloric	1	1	1
acid			
50% Sodium	2	1	1
Hydroxide			
10% Sodium	3	1	1
Hydroxide	2	2	2
Methyl Ethyl Ketone	3	3	3
Acetone	3	3	3
1:1:1 Trichloroethane	2	1	3
Isopropyl Alcohol	3	1	1
ASTM#3 Oil	1	1	1
SAE 30 Oil	1	1	1
Alconox	1	1	1
Toluene	2	1	3
Mineral Spirits	1	1	1
Glacial Acetic Acid	3	3	3
Diesel Fuel	1	1	1
10% Sodium	1	1	1
Chloride			
Water	1	1	1
Gasoline	1	1	1

1 = No change

2 = Slight failure in Legibility

3 = Failure in Legibility

7 Day Immersion – Immersed in reagent for 7 days

Dip Test -Five 10 minute dips in reagent followed by 30 minute recovery Rubbed sample for 1 minute with swab soaked in reagent **Rub Test -**

# **Marking Performance:**

MIL-M-81531: Print still legible after 20 eraser rubs with hard hand pressure.

Page 2 of 5 © 2007 PANDUIT Corp

<sup>\*3000</sup> hours equates to 5 years of assimilated outdoor UV exposure.

**Technical Data Sheet** 

18900 Panduit Drive Tinley Park, IL 60487

Customer Service: 800-777-3300

TDS: Effective Date: Revision:

**GMNT** 16JUL12 6

# **CHEMICAL/SOLVENT RESISTANCE:**

The testing was conducted at room temperature. Samples were thermal transfer printed with Panduit Hybrid ribbon on Panduit printer.

Chemical/Solvent	7 DAY IMMERSION	DIP TEST	RUB TEST
30% Sulfuric acid	1	1	1
10% Sulfuric acid	1	1	1
30% Hydrochloric	1	1	1
acid			
10% Hydrochloric	1	1	1
acid			
50% Sodium	2	1	1
Hydroxide			
10% Sodium	1	1	1
Hydroxide			
Methyl Ethyl Ketone	3	3	3
Acetone	3	3	3
1:1:1 Trichloroethane	3	1	3
Isopropyl Alcohol	3	1	3
ASTM#3 Oil	2	1	1
SAE 30 Oil	1	1	1
Alconox	1	1	1
Toluene	2	1	3
Mineral Spirits	3	1	2
Glacial Acetic Acid	3	3	3
Diesel Fuel	3	1	2
10% Sodium	1	1	1
Chloride			
Water	1	1	1
Gasoline	3	1	2

1 = No change

2 = Slight failure in Legibility

3 = Failure in Legibility

7 Day Immersion – Immersed in reagent for 7 days

Five 10 minute dips in reagent followed by 30 minute recovery Dip Test -Rubbed sample for 1 minute with swab soaked in reagent **Rub Test -**

# **Marking Performance:**

MIL-M-81531: Print still legible after 20 eraser rubs with hard hand pressure.

Page 3 of 5 © 2007 PANDUIT Corp

18900 Panduit Drive Tinley Park, IL 60487

Customer Service: 800-777-3300

TDS: Effective Date: Revision:

**GMNT** 16JUL12

## **Technical Data Sheet**

# High Temperature Plant (Class 1E) Harsh Environment Test Result Summary

GMNT marker tag has been tested for use as an identification marker for use in harsh environments in various high temperature power plants. Printed markers were subjected to radiation exposure, thermal aging and LOCA/MSLB environmental testing as shown in the three tables below. Test margins related to IEEE 323-2003 were used.

General Environmental Test Result Summary Table

General Environmental Test Result Summary Table		
Item	Normal	Accident
Service Life:	40 years	1 year
Temperature	140F (60C)	360F (182.2C) (peak)
Pressure	Atmospheric	57 psig (peak)
Relative Humidity	90%	100% (max)
Radiation	2.0E7 rads	2.0E8 rads (TID)
*Halogen Content		Not Applicable
Marker with (Print)		
(Thermal Print)	Fluorine < 1.0 ppm	
(Thermal Print)	Bromine < 1.0 ppm	
(Thermal Print)	Chlorine < 7.0 ppm	
(Thermal Print)	Iodine < 1.0 ppm	
Print Permanence	Print remained legible with	Thermal Print -No significant
	no change in print density	change
Physical Integrity	No significant change	Some warping and splitting but remained attached on wire

#### **Containment Spray Test Information Table**

Item	Short Term	Long Term
	(Injection Phase)	(Recirculation Phase)
Duration	4 hours	30 days
Temperature	60-360F (16-182C)	60-360F (16-182C)
Spray Density (gpm/ft^2.)	>0.62 (25.3 L/min/m <sup>2</sup> )	>0.62 (25.3 L/min/m <sup>2</sup> )
Chemical Composition		
Hydrazine ( $N_2H_{4}$ )	0-50 ppm	0-50 ppm
Boric Acid (H <sub>3</sub> BO <sub>3</sub> )	4,400 ppm	4,400 ppm
pН	4.0 - 10.0	7.0 - 8.5

LOCA /MSLB Combined Temperature/Pressure Test Information Table

TIME	Temperature	Pressure
Seconds	Deg F (Deg C)	PSIG (kPa)
0	120 (49)	0 (0)
10	300 (149)	57 (393)
50	360 (182)	57 (393)
250	360 (182)	57 (393)
270	275.3 (135.2)	57 (393)
1 X 10 <sup>3</sup>	275.3 (135.2)	57 (393)
1 X 10 <sup>4</sup>	230 (110)	46 (317)
1 X 10 <sup>5</sup>	190 (88)	20 (138)
1 X 10 <sup>6</sup>	150 (66)	10 (69)
2.592 X 10 <sup>6</sup> (30 days)	150 (66)	10 (69)
1.572 X 10 <sup>7</sup> (182 days)	142 (61)	10 (69)
3.15 X 10 <sup>7</sup> (365 days)	142 (61)	10 (69)

<sup>\*</sup>The chemical analysis method SM4110B (De-ionized Water Soluble Method) was performed to identify concentration of halogen ions in this material that could potentially leach onto materials such as stainless steel and promote corrosion, This chemical analysis does not identify the concentration of toxic gaseous effluents released by burning this material.

© 2007 PANDUIT Corp Page 4 of 5

**Technical Data Sheet** 

18900 Panduit Drive Tinley Park, IL 60487

Customer Service: 800-777-3300

TDS: Effective Date: Revision: GMNT 16JUL12 6

## LIMITED WARRANTY

All PANDUIT Identification Solution Products (except for Software programs) are warranted to be free from defects in material and workmanship at the time of sale but our obligation under this warranty is limited to replacement of the product proved to be defective within 6 months from the date of sale, or in the case of printers, within 90 days from the date of sale. This warranty is void if the products or printers are modified, altered or misused in any way. Use of PANDUIT printers with any product other than the specified PANDUIT products for which the printer was designed constitutes misuse. Before using, the user shall determine the suitability of the product for its intended use and user assumes all risk and liability whatsoever in connection therewith. The foregoing may not be altered except by an agreement signed by officers or seller and manufacturer.

NEITHER PANDUIT OR SELLER SHALL BE LIABLE FOR ANY OTHER INJURY, LOSS OR DAMAGE, WHETHER DIRECT OR CONSEQUENTIAL, ARISING OUT OF THE USE OF, OR THE INABILITY TO USE THE PRODUCT OR THE PRINTER.

THIS WARRANTY IS MADE IN LIEU OF AND EXCLUDES ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS OF PARTICULAR USE ARE SPECIFICALLY EXCLUDED.

The information contained in this literature is based on our experience to date and is believed to be reliable. It is intended as a guide or use by persons having technical skill at their own discretion and risk. We do not guarantee favorable results or assume any liability in connection with its use. Dimensions contained herein are for reference purposes only. This publication is not to be taken as a license to operate under, or a recommendation to infringe any existing patents. This supersedes and voids all previous literature, etc.

Page 5 of 5 © 2007 PANDUIT Corp

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Wire Labels & Markers category:

Click to view products by Panduit manufacturer:

Other Similar products are found below:

89078GBEST 89082GBESR 89082GBEST PCL025-4 5761-2SF 58400 586R734H02 M1.040.0000.6 CRS-CM5M CRS-M18M CS1836000 CS8626-000 CU6337-000 CU6342-000 CU6343-000 CWD01-0 CWD012-0 CWD012-7 CWD015-3 CWD015-7 CWD02-0 CWD023 CWD02-4 CWD02-6 CWD02-8 CWD02-A CWD02-D CWD02-H CWD02-K CWD02-L CWD02-M CWD02-P CWD02-Q CWD02-R
CWD02-U CWD02-W CWD02-Y CWD03-+ CWD03-0 CWD03-P CWD06-0 CWD06-8 CWD06-9 CWD06-L CWD06-N CWD09-0
CWD09-5 CWD09-7 6806810001 CZ2857-000