





ProLight PE8A-FFTE-WERGBVD 0.4W 4 in 1 RGBV Power LED Technical Datasheet Version: 1.1

ProLight Opto © PE8A Series

Features

·R, G, B, V four color in one Package
·Good color uniformity
·Lead free reflow soldering
·RoHS compliant
·No UV
·Moisture Sensitivity Level - JEDEC Level 5a

Main Applications

Indoor and Outdoor display
Outdoor Lighting for Amusement
Consumer Electronics

Introduction

•PE8A-FFTE-WERGBVD colorful series is a color changeable LED with maximum 4 color chips in one package. It's creating a small optical source for excellent optical control and efficient color mixing.


•PE8A-FFTE-WERGBVD colorful series is much suitable for the application of color- changing lighting , indoor and outdoor display , and entertainment lighting.

No. 89, Xiyuan Rd., Zhongli City, Taoyuan County 320, Taiwan (R.O.C.) Tel : +886-3-461-8618 Fax : +886-3-461-8677 www.prolightopto.com 2020/08 DS-1459

We Provide the Light to the world



Emitter Mechanical Dimensions



Notes:

- 1. The cathode side of the device is denoted by the chamfer on the part body.
- 2. Drawing not to scale.
- 3. All dimensions are in millimeters.
- 4. Unless otherwise indicated, tolerances are \pm 0.10mm.
- 5. Please do not bend the leads of the LED, otherwise it will damage the LED.
- 6. Please do not use a force of over 0.3kgf impact or pressure on the lens of the LED, otherwise it will cause a catastrophic failure.
- *The appearance and specifications of the product may be modified for improvement without notice.

We Provide the Light to the world



Intensity Characteristics, T_J = 25°C

Radiation Color Pattern		Part Number	Test Current (mA)	Luminous Int or Flux	• • •	CRI
		Emitter	(IIIA)	Min.	Тур.	Min.
Lambertian	Red		20	770 mcd	900 mcd	-
	Green		20	1550 mcd	1850 mcd	-
	Blue	PE8A-FFTE-WERGBVD	20	330 mcd	400 mcd	-
	Warm White		60	18 lm	20 lm	80

ProLight maintains a tolerance of ± 10% on intensity and flux measurements.

Electrical Characteristics, T_J = 25°C

Color	Toot Current (mA)	F	orward Voltage V _F (V)
Color	Test Current (mA)	Min.	Тур.	Max.
Red	20	1.90	2.20	2.50
Green	20	2.80	3.00	3.40
Blue	20	2.80	3.00	3.40
Warm White	60	2.90	3.15	3.50

• ProLight maintains a tolerance of ± 0.1V for Voltage measurements.

Optical Characteristics, T_J = 25°C

Color	Test Current		nant Wavelen or Temperatu	-	Total included Angle (degrees)	Viewing Angle (degrees)
COIDI	(mA)	Min.	Тур.	Max.	θ _{0.90V}	2 θ _{1/2}
Red	20	619 nm	622 nm	624 nm	160	115
Green	20	521 nm	524 nm	526 nm	160	115
Blue	20	465 nm	468 nm	470 nm	160	115
Warm White	60	2850 K	3050 K	3250 K	160	115

• ProLight maintains a tolerance of ± 1nm for dominant wavelength measurements.

• ProLight maintains a tolerance of ± 5% for CCT measurements.

We Provide the Light to the world



Absolute Maximum Ratings

Parameter	Red	Green	Blue	Warm White
DC Forward Current (mA)	20	20	20	60
Peak Pulsed Forward Current (mA)	30	30	30	90
ESD Sensitivity (HBM per MIL-STD-883E Method 3015.7)	(less than 1/10 duty cycle@1KHz) $> \pm 500V$			
LED Junction Temperature	105°C			
Operating Board Temperature at Maximum DC Forward Current	-40°C - 85°C			
Storage Temperature	-40°C - 85°C			
Allowable Reflow Cycles	2			
Reverse Voltage	Not designed to be driven in reverse bias			

We Provide the Light to the world



Photometric Luminous Intensity Bin Structure at 20mA

Color	Bin Code	Minimum Luminous Intensity (mcd)	Maximum Luminous Intensity (mcd)
Red	A	770	1000
	B	1000	1300
Green	A	1550	2000
	B	2000	2600
Blue	A	330	430
	B	430	560

• ProLight maintains a tolerance of ± 10% on Intensity measurements.

Photometric Luminous Flux Bin Structure at 60mA

Color	lor Bin Code Minimum Photometric Flux (Im)		Maximum Photometric Flux (Im)
Warm White	A B	18 23	23 29

• ProLight maintains a tolerance of \pm 10% on flux measurements.

Dominant Wavelength Bin Structure at 20mA

Color	Bin Code	Minimum Dominant Wavelength (nm)	Maximum Dominant Wavelength (nm)
Red	4	619	624
Green	1	521	526
Blue	2	465	470


ProLight maintains a tolerance of ± 1nm for dominant wavelength measurements.

We Provide the Light to the world



Color Bin at 60mA

Warm White Binning Structure Graphical Representation



Warm White Bin Structure

Bin Code	x	У	Typ. CCT (K)	Bin Code	x	У	Тур. ССТ (К)
	0.4240	0.3920			0.4299	0.4165	
NO	0.4320	0.4100	3050	N2	0.4431	0.4213	3150
INO	0.4450	0.4140	3030	000 INZ	0.4345	0.4033	5150
	0.4360	0.3960			0.4223	0.3990	
	0.4431	0.4213			0.4223	0.3990	
N1	0.4562	0.4260	2950	N3	0.4345	0.4033	3150
INI	0.4468	0.4077	2950	IN3	0.4260	0.3854	5150
	0.4345	0.4033			0.4147	0.3814	
	0.4345	0.4033					
N4	0.4468	0.4077	2950				
IN4	0.4373	0.3893	2950				
	0.4260	0.3854					

• Tolerance on each color bin (x, y) is ± 0.01

Note:

1. Although several bins are outlined, product availability in a particular bin varies by production run and by product performance. Not all bins are available in all colors.


2. ProLight **SmartBin** is working to make the color bin smarter, by selecting that intelligence is infused into major **N0** bin with minor N1-N4 bins and processes that make assembly easily

We Provide the Light to the world




Color Spectrum, T_J = 25°C

1. Blue > Green > Red



2. Warm White




We Provide the Light to the world



Light Output Characteristics

Relative Light Output vs. Junction Temperature




We Provide the Light to the world



Forward Current Characteristics, T_J = 25°C

1. Forward Voltage vs. Forward Current




No. 89, Xiyuan Rd., Zhongli City, Taoyuan County 320, Taiwan (R.O.C.) Tel : +886-3-461-8618 Fax : +886-3-461-8677 www.prolightopto.com

We Provide the Light to the world



Forward Current Characteristics, $T_J = 25^{\circ}C$

2. Forward Current vs. Normalized Relative Luminous Flux




No. 89, Xiyuan Rd., Zhongli City, Taoyuan County 320, Taiwan (R.O.C.) Tel : +886-3-461-8618 Fax : +886-3-461-8677 www.prolightopto.com

We Provide the Light to the world



Typical Representative Spatial Radiation Pattern

Lambertian Radiation Pattern



We Provide the Light to the world



Moisture Sensitivity Level - JEDEC Level 5a

			Soak Requirements			
Level	vel Floor Life		Standard		Accelerated Environment	
	Time	Conditions	Time (hours)	Conditions	Time (hours)	Conditions
50	24 hours	≤30°C /	48 +2/-0	30°C /	10 +0.5/-0	60°C /
5a	24 110UIS	60% RH	40 +2/-0	60% RH	10 +0.5/-0	60% RH


- The standard soak time includes a default value of 24 hours for semiconductor manufature's exposure time (MET) between bake and bag and includes the maximum time allowed out of the bag at the distributor's facility.
- Table below presents the moisture sensitivity level definitions per IPC/JEDEC's J-STD-020C.

				Soak Req	uirements	
Level	_evel Floor Life		Stan	dard	Accelerated	Environment
	Time	Conditions	Time (hours)	Conditions	Time (hours)	Conditions
1	Unlimited	≤30°C / 85% RH	168 +5/-0	85°C / 85% RH	NA	NA
2	1 year	≤30°C / 60% RH	168 +5/-0	85°C / 60% RH	NA	NA
2a	4 weeks	≤30°C / 60% RH	696 +5/-0	30°C / 60% RH	120 +1/-0	60°C / 60% RH
3	168 hours	≤30°C / 60% RH	192 +5/-0	30°C / 60% RH	40 +1/-0	60°C / 60% RH
4	72 hours	≤30°C / 60% RH	96 +2/-0	30°C / 60% RH	20 +0.5/-0	60°C / 60% RH
5	48 hours	≤30°C / 60% RH	72 +2/-0	30°C / 60% RH	15 +0.5/-0	60°C / 60% RH
5a	24 hours	≤30°C / 60% RH	48 +2/-0	30°C / 60% RH	10 +0.5/-0	60°C / 60% RH
6	Time on Label (TOL)	≤30°C / 60% RH	Time on Label (TOL)	30°C / 60% RH	NA	NA

We Provide the Light to the world



Recommended Solder Pad Design



• All dimensions are in millimeters.

We Provide the Light to the world




Reflow Soldering Condition

Soldering Conditions Reflow Soldering Profile for lead free soldering Preconditioning acc. to JEDEC Level 5a (acc. to J-STD-020D.01)

Profile Feature	Pb-Free Assembly			
Profile Feature	Recommendation	Max. Ratings		
Ramp-up Rate to Preheat (25°C to 150°C)	2°C/sec.	3°C/sec. max.		
Time t _s from T _{Smin} to T _{Smax} (150°C to 200°C)	100 sec.	60-120 sec.		
Ramp-up Rate to Peak (180°C to T _P)	2°C/sec.	3°C/sec. max.		
Liquidus Temperture T _L	217°C			
Time t _L above T _L	80 sec.	100 sec. max.		
Peak Temperature T _P	245°C	250°C max.		
Time t_p within 5°C of the specified peak temperature (T_p - 5°C)	20 sec.	10-30 sec.		
Ramp-down Rate (T _P to 100°C)	3°C/sec.	6°C/sec. max.		
Time 25°C to Peak temperature		8 minutes max.		

All temperatures refer to the center of the package, measured on the top of the component



- Do not perform reflow soldering more than twice. Observe necessary precautions of handling moisture-sensitive devices as stated in the following section.
- Do not apply any pressure or force on the LED during reflow and after reflow when the LED is still hot.
- Use reflow soldering to solder the LED. Use hand soldering only for rework if unavoidable, but it must be strictly controlled to following conditions :

(1) Soldering iron tip temperature = 315°C maximum

(2) Soldering duration = 3s maximum

(3) Number of cycles = 1 only


(4) Power of soldering iron = 50W maximum

- Do not touch the LED package body with the soldering iron except for the soldering terminals, because it may cause damage to the LED.
- Confirm beforehand whether the functionality and performance of the LED is affected by soldering with hand soldering.

We Provide the Light to the world



Emitter Reel Packaging




Notes:

- 1. Drawing not to scale.
- 2. All dimensions are in millimeters.
- 3. Unless otherwise indicated, tolerances are \pm 0.10mm.

We Provide the Light to the world



Emitter Reel Packaging



Notes:

- 1. Empty component pockets sealed with top cover tape.
- 2. 1000 pieces per reel.
- 3. Drawing not to scale.
- 4. All dimensions are in millimeters.

We Provide the Light to the world



Handling of Moisture-Sensitive Devices


- Before use :
 - (1) An unopened moisture barrier bag (MBB) can be stored at <40° C/90% RH for 12 months. If the actual shelf life has exceeded 12 months and the humidity indicator card (HIC) indicates that baking is not required, it is safe to reflow the LEDs per the original MSL rating.</p>
 - (2) Do not open the MBB prior to assembly (for example, for IQC). If unavoidable, the MBB must be properly resealed with fresh desiccant and HIC. The exposed duration must be taken in as floor life.
- Control after opening the MBB :
 - (1) Read the HIC immediately upon opening of MBB.
 - (2) Keep the LEDs at < 30° C/60% RH at all times, and complete all high temperature-related processes, including soldering, curing, or rework within 24 hours.
- Control for unfinished reel :
- Store unused LEDs in a sealed MBB with desiccant or a desiccator at <5% RH.
- Control of assembled boards : If the PCB soldered with the LEDs is to be subjected to other high-temperature processes, store the PCB in a sealed MBB with desiccant or desiccator at <5% RH to ensure that all LEDs have not exceeded their floor life of 24 hours.
- Baking is required if :
 - (1) The HIC indicator indicates a change in color for 10% and 5%, as stated on the HIC.
 - (2) The LEDs are exposed to conditions of $> 30^{\circ}$ C/60%RH at any time.
 - (3) The LED's floor life exceeded 24 hours.
 - The recommended baking condition is: $65^{\circ}C \pm 5^{\circ}C$ for 24 hours.
 - Baking can only be done once.
- Storage :

The soldering terminals of these LEDs are silver plated. If the LEDs are exposed in ambient environments for too long, the silver plating might be oxidized, thus affecting its solderability performance. As such, keep unused LEDs in a sealed MBB with desiccant or in a desiccator at < 5% RH.

Handling of Silicone Lens LEDs

Notes for handling of silicone lens LEDs

- Please do not use a force of over 0.3kgf impact or pressure on the silicone lens, otherwise it will cause a catastrophic failure.
- The LEDs should only be picked up by making contact with the sides of the LED body.
- Avoid touching the silicone lens especially by sharp tools such as Tweezers.
- Avoid leaving fingerprints on the silicone lens.
- Please store the LEDs away from dusty areas or seal the product against dust.
- When populating boards in SMT production, there are basically no restrictions
 regarding the form of the pick and place nozzle, except that mechanical pressure
 on the silicone lens must be prevented.
- Please do not mold over the silicone lens with another resin. (epoxy, urethane, etc)





We Provide the Light to the world

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Prolight manufacturer:

Other Similar products are found below :

PACC-18FWL-BC8P PACD-40FNL-BCGP PACD-40FVL-DCGP PACE-28FNL-BC4P PACE-28FVL-BC4P PACE-28FWL-BC4P PACE-57FWL-BC8P PACG-110FVL-BCGP PACJ-28FNL-EC4N PACJ-28FVL-DC4N PACJ-28FWL-BC4N PACJ-28FWL-DC4N PACK-35FNL-EC5N PACK-35FWL-BC5N PACK-57FNL-BC8N PACK-57FNL-EC8N PACK-57FVL-BC8N PACK-57FVL-EC8N PACK-57FWL-BC8N PACL-115FVL-BCGN PACL-115FVL-ECGN PASB-16FNL-EC2NS40 PASB-16FVL-EC2NS27 PASB-16FVL-EC2NS30 PASQ-17FVL-D2030 PB2D-1CLA-TC PB2D-1JLA-TC PB2D-3JLA-G PB2D-3JLA-GM PB2D-UCLA-TC PBED-15F4E-A PBLA-3CLA-TC PBLB-1CQA-TCL PBLB-3LTE PBLB-3LTE-RGBN PBSD-10JLA-G PBSD-10JLA-GM PBSD-10JLA-GS PBSD-10KLA-G PBSD-10KLA-GS PBSD-12JLA-KC PBVF-31FWU-F9G PC8N-5L4E-C PC8N-5LTS-C PDSJ-15FQL-D2748 PDSJ-25FQL-D2748 PDSJ-35FQL-D1840M PDSJ-35FQL-D2748 PDSJ-40FQL-D2030 PDSQ-10FVL-D1930