




General Features

- High corrosion resistant performance: Pb-Ca multi-alloy grid
- > High energy density and power density
- Optimized capability of instant high-current discharging
- > Excellent charge acceptance ability
- > Excellent deep cycle discharge capability
- Strong high and low temperature performance
- Precision sealing technology





n F187

AGM battery 6V | 1.3Ah | max. 19.5A Product code: 53041

Applications

- > UPS/EPS
- > Power systems
- > Telecommunications system
- > Emergency lighting、Auto control system
- Solar/wind generating storage cyclic
- > Other general purpose

Specificatio	n								
Nominal Voltage	6V								
Nominal Capacity	1.3Ah								
Design life	5 years								
Terminal	F187								
Approx. Weight	Approx0.30kg (0.66lbs)								
Container Material	ABS								
Rated Capacity	1.300Ah 20Hour Rate (0.065A to 5.25V) 1.011Ah 3Hour Rate (0.337A to 5.25V) 0.858Ah 1Hour Rate (0.858A to 4.80V)								
Internal resistance	Full charged at 25°C: 60.0 m Ω								
Max. Discharge Cu	rrent 19.5A(5S)								
Operating Tempera	Discharge: -20 ~50℃(-4~ 122°F) ature Charge: -20 ~50 ℃(-4~ 122°F) Storage: -20 ~50℃(-4~ 122°F)								
	Charge current: Max.0.33A ; Recom.0.13A Float Charge: 6.75-6.90V,recom.6.75V(-9mV/ °C)								
Charge Method (25 °C)	Equalize charge:6.90-7.05V,recom.7.05V(-12mV/ °C)								
Cycle charge:7.20-7.50V,recom.7.20V(-15mV/ °C Self discharge 3% of capacity declined per month at 25°									


Constant Current Discharge Characteristics **Unit: A (25**°C, **77**°F) 1h 2h 3h 4h 8h 10h FV/Time 5min 10min 15min 30min 5h 20h 1.60V 2.51 5.15 3.37 1.64 0.858 0.491 0.359 0.287 0.244 0.161 0.129 0.069 1.65V 5.11 3.22 2.30 1.56 0.806 0.472 0.348 0.278 0.239 0.159 0.127 0.068 1.70V 4.19 3.03 2.15 1.51 0.780 0.463 0.342 0.264 0.237 0.156 0.125 0.066 1.75V 3.89 2.89 2.00 1.48 0.753 0.451 0.337 0.260 0.226 0.152 0.122 0.065 1.80V 3.58 2.72 1.86 1.43 0.727 0.439 0.319 0.255 0.217 0.148 0.120 0.062

Consta	Constant Power Discharge Characteristics $$ Unit: W/cell (25 $$ $^{\circ}\mathrm{C}$,77 $^{\circ}\mathrm{F}$)													
FV/Time	5min	10min	15min	30min	1h	2h	Зh	4h	5h	8h	10h	20h		
1.60V	9.66	6.07	4.59	2.78	1.57	0.921	0.678	0.544	0.462	0.304	0.249	0.137		
1.65V	8.91	5.74	4.31	2.76	1.48	0.886	0.659	0.527	0.453	0.300	0.245	0.133		
1.70V	8.15	5.57	4.12	2.75	1.43	0.869	0.648	0.501	0.440	0.297	0.243	0.132		
1.75V	7.39	5.40	3.97	2.72	1.39	0.849	0.639	0.494	0.431	0.284	0.237	0.129		
1.80V	6.63	5.22	3.79	2.70	1.37	0.843	0.622	0.490	0.420	0.275	0.232	0.128		


Disclaimer: Manufacturers have the right to self-modify the parameters of the product updates, please keep in touch with manufacturers to obtain the latest information.




Discharge characteristic




Charging characteristic




The effect of temperature on capacity




Curves of self-discharge



The effect of discharge depth on cycle life



The effect of temperature on float life





TEL:+48 32 231 16 82

Fax : +48 32 231 16 82

E-mail: ntec@ntec.pl Web: www.ntec.pl

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Sealed Lead Acid Battery category:

Click to view products by **QOLTEC** manufacturer:

Other Similar products are found below :

0809-0012 0819-0012 0850-0004 0859-0012 0800-0004 LC-R0612P LC-R061R3P PS-1250F1 APCRBC123 APCRBC124 LCRA1212P NP12-12 NP12-6 NP3.2-12 LC-P0612P LC-R063R4P LC-R067R2P1 LC-R121R3P LC-R122R2P LC-R0612P1 LC-R127R2P1 LC-X1220AP UP-VW1245P1 2320296 RBC32 RBC11A RBC36-SLT