




SPECIFICATION

(Reference sheet)

CL05X225MS5NSNC - Samsung P/N : - Supplier : Samsung electro-mechanics CAP, 2.2//F, 2.5V, ±20%, X6S, 0402 - Product : Multi-layer Ceramic Capacitor Description : A. Samsung Part Number CL <u>S</u> <u>05</u> 225 <u>s</u> <u>5</u> Ν <u>C</u> X Μ N 1 2 3 5 6 \overline{O} 8 9 10 (1) 4 ① Series Samsung Multi-layer Ceramic Capacitor ② Size 0402 (inch code) L: 1.00 ± 0.07 mm W: 0.50 ± 0.07 mm **③** Dielectric X6S (8) Inner electrode Ni Cu **④** Capacitance 2.2 µF Termination Sn 100% **5** Capacitance Plating ±20 % (Pb Free) tolerance 9 Product Size control code 6 Rated Voltage 2.5 V 10 Special Reserved for future use ⑦ Thickness 0.50 ± 0.07 mm 1 Packaging Cardboard Type, 7" reel

B. Structure & Dimension



Samsung P/N	Dimension(mm)			
	L	W	т	BW
CL05X225MS5NSNC	1.00 ± 0.07	0.50 ± 0.07	0.50 ± 0.07	0.25 ± 0.10

C. Samsung Reliablility Test and Judgement Condition

	Judgement	Test condition	
Capacitance	Within specified tolerance	1 ^{kHz} ±10% / 0.5±0.1Vrms	
Tan δ (DF)	0.1 max.	*A capacitor prior to measuring the capacitance is heat treated at 150° +0/- 10° for 1hour and maintained in ambient air for 24±2 hours.	
Insulation	10,000Mohm or 100Mohm× ^{µF}	Rated Voltage 60~120 sec	
Resistance	Whichever is smaller		
Appearance	No abnormal exterior appearance	Microscope (×10)	
Withstanding	No dielectric breakdown or	250% of the rated voltage	
Voltage	mechanical breakdown		
Temperature	X6S	·	
Characteristics	(From -55℃ to 105℃, Capacitance change	should be within ±22%)	
Adhesive Strength	No peeling shall be occur on the	500g.f, for 10±1 sec.	
of Termination	terminal electrode		
Bending Strength	Capacitance change : within ±12.5%	Bending to the limit (1mm)	
		with 1.0mm/sec.	
Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder	
	is to be soldered newly	245±5℃, 3±0.3sec.	
		(preheating : 80~120℃ for 10~30sec.)	
Resistance to	Capacitance change : within ±7.5%	Solder pot : 270±5℃, 10±1sec.	
Soldering Heat	Tan δ, IR : initial spec.		
Vibration Test	Capacitance change : within ± 10%	Amplitude : 1.5mm	
	Tan δ, IR : initial spec.	From 10Hz to 55Hz (return : 1min.)	
		2hours \times 3 direction (x, y, z)	
Moisture	Capacitance change : within ±12.5%	With rated voltage	
Resistance	Tan δ : 0.125 max	40±2℃, 90~95%RH, 500+12/-0hrs	
	IR : 500Mohm or 12.5Mohm× μ F		
	Whichever is smaller		
High Temperature	Capacitance change : within ±12.5%	With 150% of the rated voltage	
Resistance	Tan δ : 0.125 max	Max. operating temperature	
	IR : 1,000Mohm or 25Mohm× μ F	1,000+48/-0hrs	
	Whichever is smaller		
Temperature	Capacitance change : within ±15%	1 cycle condition	
Cycling	Tan δ, IR : initial spec.	Min. operating temperature \rightarrow 25°C	
		→ Max. operating temperature → 25° C	
		5 cycle test	

% The reliability test condition can be replaced by the corresponding accelerated test condition.

D. Recommended Soldering method :

Reflow (Reflow Peak Temperature : 260±5 $^\circ\!\!\mathbb{C}$, 30sec.)

A Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications,

please contact our sales personnel or application engineers.

Disclaimer & Limitation of Use and Application

The products listed in this Specification sheet are **NOT** designed and manufactured for any use and applications set forth below.

Please note that any misuse of the products deviating from products specifications or information provided in this Spec sheet may cause serious property damages or personal injury. We will **NOT** be liable for any damages resulting from any misuse of the products, specifically including using the products for high reliability applications as listed below.

If you have any questions regarding this 'Limitation of Use and Application', you should first contact our sales personnel or application engineers.

- *①* Aerospace/Aviation equipment
- 2 Automotive or Transportation equipment (vehicles, trains, ships, etc)
- 3 Medical equipment
- (4) Military equipment
- 5 Disaster prevention/crime prevention equipment
- 6 Power plant control equipment
- ⑦ Atomic energy-related equipment
- ③ Undersea equipment
- Itraffic signal equipment
- Data-processing equipment
- 1 Electric heating apparatus, burning equipment
- Description Safety equipment
- 13 Any other applications with the same as or similar complexity or reliability to the applications

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Multilayer Ceramic Capacitors MLCC - SMD/SMT category:

Click to view products by Samsung manufacturer:

Other Similar products are found below :

M39014/02-1225V M39014/22-0631 D55342E07B523DR-T/R NCA1206X7R103K50TRPF NCA1206X7R104K16TRPF NIN-FB391JTRF NIN-FC2R7JTRF NMC0201X5R474K4TRPF NMC0402NPO220J50TRPF NMC0402X5R105K6.3TRPF NMC0402X5R224K6.3TRPF NMC0402X7R103J25TRPF NMC0402X7R153K16TRPF NMC0603NPO201J50TRPF NMC0603NPO330G50TRPF NMC0603X5R475M6.3TRPF NMC0805NPO270J50TRPF NMC0805NPO820J50TRPF NMC0805X7R224K16TRPLPF NMC1206X7R102K50TRPF NMC-H0805X7R472K250TRPF NMC-L0402NPO7R0C50TRPF NMC-L0603NPO2R2B50TRPF NMC-Q0402NPO8R2D200TRPF C1206C101J1GAC C1608C0G2A221J C1608X7R1E334K C2012C0G2A472J 2220J2K00562KXT 1812J2K00332KXT CDR31BX103AKWR CDR33BX104AKUR CDR33BX683AKUS CGA2B2C0G1H010C CGA2B2C0G1H040C CGA2B2C0G1H181JT0Y0F CGA2B2C0G1H060D CGA2B2C0G1H070D CGA2B2C0G1H120J CGA2B2C0G1H151J CGA2B2C0G1H181JT0Y0F CGA2B2C0G1H1R5C CGA2B2C0G1H2R2C CGA2B2C0G1H390J CGA2B2C0G1H391J CGA2B2C0G1H3R3C CGA2B2C0G1H680J CGA2B2C0G1H6R8D CGA2B2C0G1H820J CGA2B2X8R1H152K