

CDCL3000C0-0002R7STZ

ULTRACAPACITOR CELL



SERIES

CDCL ULTRACAPACITOR CELL

Rev	Date	te Revision of historical records			
V2020-1	24-02-20	The First Release			
V2020-2	12-05-20	Version Update			

SCOPE

These are the specifications of SPSCAP (Electric Double Layer Capacitor) which you are using, please review this document and approve it.

FEATURES

Low ESR & High Power Density

Over 1,000,000 duty cycles

Threaded connection

APPLICATIONS

EV/HEV

Hybrid driven trains

Mass transportation braking energy recovery system

Heavy duty machinery

Locomotive engine start system

Document number: DT14-08-201912 Rev. & Date: V2020-2 2020.05.12 2.7V 3000F CDCL-STZ




CONSTRUCTION AND DIMENSIONS

1) Construction

Inside structure: fold anode and cathode electrode with separator

Outer structure: aluminum case, insulating sleeve

2) Dimensions



PART NUMBER	DIMENSION(mm)		
PART NOWIDER	L±0.3		
CDCL3000C0-0002R7STZ	138.0		

PART NUMBER NAMING SYSTEM										
	CDCL	3000 C 0		-	0002	R	7	STZ		
Pro	oduct Series	Nominal Capacitance (F)			Rated Voltage (V)		Terminal Design			
С	Cell	3000	3000			0002	2		ST	Threaded
D	Electric double layer	С	Decimal		Dash	R	Decimal		connection	connection
С	Cylindrical	0	0.0			7	0.	0.7	Z	Standard
L	Large	U					0.		Z	Design

Document number: DT14-08-201912 2.7V 3000F CDCL-STZ Rev. & Date: V2020-2 2020.05.12



GENERAL CHARACTERISTICS	
Items	Specification
Rated Voltage (V DC)	2.7
Surge Voltage (V DC)	2.85
Operating Temp. (°C)	-40 ∼ +65
Rated Capacitance (F)	3000
Capacitance Tolerance	0% ~ 20%
ESR Max. (AC@1KHz, mΩ)	0.22
ESR Max. (DC, $m\Omega$)	0.29
Maximum Continuous Current (ΔT=15°C, A)	129
Maximum Continuous Current (ΔT=40°C, A)	211
Maximum Peak Current (A) (1s)	2166
Max.LC (Room Temp. after 72hrs, mA)	5.2
Typical Thermal Resistance (R _{th} , Housing, °C/W)	3.1
Typical Thermal Capacitance (C _{th} , J/°C)	645
Weight (g)	548
Energy Stored (Wh)	3.04



RELIABILITY SPECIFICATIONS

ITEM		SPECIFICATION		CONDITION	
Temp.	Capacitance	Ctor 1	Change within 5% of Initial Value		
	ESR	Step. 1	Change within 50% of rated value		
	Capacitance	C 1 0	Change within 5% of Initial Value	Stan 1: 125±2°C 1h	
	ESR	Step. 2	Change within 50% of rated value	Step 1:+25±2°C, 1h Step 2:+65±2°C, 1h	
Characteristics	Capacitance	5 . 0	Change within 5% of Initial Value	Step 3: -25±2°C, 1h	
	ESR	Step. 3	Change within 50% of rated value	Step 4: -40±2°C, 1h	
	Capacitance		Change within 5% of Initial Value		
	ESR	Step. 4	Change within 50% of rated value		
	Capacitance	Initial Va	lue		
Vibration Test	ESR	Initial Va	lue	ISO16750-3 Table 14	
	Appearance	Not Mark	ked Defect		
Thermal Cycle	Capacitance	Initial Va	lue	Temp.: $-40^{\circ}\text{C} \sim 65^{\circ}\text{C}$ Cycle times: 6	
	ESR	Initial Va	lue	Test Time(One Cycle): -40°C 2hrs,	
	Appearance	Not Mark	ced Defect	+65°C 2hrs, Temp change 2hrs	
	Capacitance	Change w	vithin 20% of Initial Value	Temp.: +40±2℃	
Humidity Test	ESR	Change w	vithin 100% of Initial Value	Humidity: 90-95%RH Test Time: 240±8hrs	
	Appearance	Not Mark	ced Defect	lest Time: 240±8nrs	
DC Life	Capacitance	Change w	vithin 20% of Initial Value	Town 1 65 1 2°C	
	ESR	Change w	rithin 100% of Initial Value	Temp.: +65±2°C Voltage: 2.7V	
	Appearance	Not Mark	ced Defect	Time: 1,500hrs	
Shelf Life	Capacitance	Change w	rithin 20% of Initial Value		
	ESR	Change w	rithin 100% of Initial Value	Temp.: +70±2°C Time: 1,000hrs	
	Appearance	Not Mark	ked Defect	111110. 1,0001113	
Cycle Life	Capacitance	Change w	rithin 20% of Initial Value	Temp.: +25±2°C Cycles times:	
	ESR	Change w	vithin 100% of Initial Value		
	Appearance	Not Mark	ced Defect	1,000,000	



MEASURING METHOD

- 1) Charge and Discharge procedure (Figure 1)
 - A) Charge the capacitor using constant current I to rated voltage V₀
 - B) Keep rated voltage 5 mins
 - C) Discharge the capacitor using constant current I to half rated voltage, record discharge time T₁ during voltage change from V₁to V₂
 - D) Rest 2-5s, record voltage change ΔV
 - E) Discharge it to a very low voltage around 0.01V
 - F) $V_1 = 85\% V_0 V_2 = 50\% V_0$



 $C = I \cdot T_1 / (V_1 - V_2)$

C: Capacitance (F)

I: Constant Discharge Current (A)

T₁: Discharge Time (S)

 V_1 - V_2 : Voltage Change (V)



DC ESR= $\Delta V/I$

DC ESR: DC Equivalent Series Resistance (Ω)

ΔV: Voltage Change (V)

I: Constant Discharge Current (A)

4) AC ESR

Measure AC ESR using LCR meter

Frequency: 1KHz

Voltage: fully discharge




Figure 1

REMARK: SPSCAP EDLC SHOULD BE DISCHARGED WITH RESISTOR FOR AT LEAST 12 HOURS BEFORE MEASUREMENT OF CAPACITANCE OR ESR.




NOTES AND CAUTION

Please notice below points when you start use SPSCAP.

- 1) The SPSCAP gets polarity through aging/testing process before it is packed, so please mount it in accordance with its polarity to maintain the best condition;
- 2) Please only apply SPSCAP at rated voltage. If you apply more than rated voltage, capacitor will be damaged or broken due to electrolyte inside will be electrolyzed;
- 3) Ambient temperature greatly affects the lifetime of the capacitor, by reducing the temperature by 10°C, lifetime can be approximately doubled;
- 4) Storage: In long term storage, please store SPSCAP in following condition:
 - Temp.: 15 ~ 35°C
 - Humidity: 40 ~ 75 %RH
 - No-dust, non-acidic and/or non-alkaline atmosphere
 - Avoid direct sun light
- 5) Do not disassemble SPSCAP. It contains electrolyte;
- 6) Avoid serious mechanical impacts onto capacitor, such as force or twist capacitor;
- 7) Please contact us if you want to subject SPSCAP to severe vibrating conditions exceeding rated specification;
- 8) Please contact us if you want to connect a certain number of single capacitor to make a module;
- 9) Over-rated voltage may be applied to a single SPSCAP in series connection due to the deviation of capacitance and ESR of each SPSCAP. Please inform us if you are using SPSCAP in series connection and please design so as not to apply over-rated voltage to each capacitor, and use SPSCAP from same date code/lot.





All rights reserved. Design and specifications are subjected to change without notice.

NINGBO CRRC NEW ENERGY TECHNOLOGY CO.,LTD.

Add: No.199 Shidai Road, Wuxiang Town, Yinzhou District,

Ningbo,Zhejiang,China info@spscap.com

Email: info@spscap.co Website: www.spscap.com



X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Supercapacitors / Ultracapacitors category:

Click to view products by SPSCAP manufacturer:

Other Similar products are found below:

C-TEC1225 P SCCY73B407SLBLE CDCL3000C0-002R85STB CDCM0800C0-0002R7SPD FE0H473ZF MAL223551012E3

MAL223551014E3 MAL223551015E3 MAL223551016E3 MAL223551007E3 MAL223551001E3 MAL223551008E3 MAL219612474E3

CPM3225A-2K HS208F DRE10/2.5 DRL106S0TI25RRDAP DRL226S0TK25RR 106DCN2R7M SCCT30B156SRB

SCMR14C474MSBA0 SCMR22C155MSBA0 DRL475S0TG20RRDAP GW209F TV1020-3R0605-R TV1245-3R0346-R

SCCX50B207VSB PAS0815LS2R5105 HVZ0E475NF SCMR18F105PSBA0 FT0H565ZF FE0H224ZF SCCT30E156SRB

MAL222090006E3 SCCY68B407SSBLE CPH3225A-2K 207DCN2R7M DB5U307W35050HA SCCX50B227SSBLE DGH505Q5R5

DGH305Q2R7 DGH505Q2R7 DGH705Q2R7 DGH506Q2R7 DGH504Q5R5 DGH335Q2R7 DGH256Q2R7 DGH255Q5R5 DGH207Q2R7

DGH155Q5R5