EC Safety Data Sheet according to Directive 1907/2006

Trade name: Solder-wire KS 100 FLOWTIN ® TC (S-Sn99Cu1)

Date of issue: 01.04.2006 Revised on: 23.11.2011 Date of print: 17.02.2012 Page: 1(3)

1. Name of product, characterization and company name

Information on the product

Trade name: Solder-wire KS 100 FLOWTIN ® TC (S-Sn99Cu1)

Usage of the product / preparation Solder wire for soft soldering

Identification of the manufacturer / supplier

Address: Stannol GmbH

Oskarstr. 3 -7 42283 Wuppertal

Phone: 0202 585 0 **Fax:** 0202 585 155

Emergency call: 0202 585 119 (only during trading hour (8:00 h – 17:00 h)

E-mail: werner.kruppa@stannol.de

2. Possible hazards:

Not a composition for the purposes of the Dangerous Substances Regulations, but nevertheless observe items 4-16

Additional hazards for human health and environment:

May cause occupational asthma

3. Composition/Information on the components

Chemical characterization: Tin-Copper alloy (with <0,1 % other iron-metals) with flux max. 3,5 % modified resin (halide-free)

Composition according to EC 1907/2006:

 Contents
 CAS No.
 EINECS No.
 Symbols
 R-phrases:
 Substance

 remainder
 7440-31-5
 231-141-8
 Tin
 copper

 <0,9%</td>
 7440-50-8
 231-159-6
 copper
 modified resin

The wording of the R-phrases stated is indicated in Section 16

4. First Aid measures

General information:If casualty is unconscious but breathing, place in the recovery position.
If breathing has stopped apply artificial resuscitation or give oxygen by mask

After inhalation: Remove patient to fresh air. If irritation resists, obtain medical attention.

After skin contact: If any skin irritation develops seek medical attention

After eye contact: Flush immediately with plenty of water. In cases where spitting flux has entered the eye

seek medical attention.

After ingestion: Rinse mouth immediately and drink plenty of water. Seek medical advice.

Hints for doctors. Inhalation of the flux fumes given off at soldering temperatures will irritate the nose, throat and

respiratory system. Repeated or prolonged exposure to flux fumes may cause shortness of

breath and cough..

Physician's information

Treatment: Decontamination, treatment of symptoms.

5. Fire fighting measures

Suitable extinguishing media:

Use extinguishing media appropriate to surrounding fire conditions

Special protective equipment for fire fighting

Wear self-contained breathing apparatus and protective clothing to prevent contact with skin and

eves.

6. Accidental release measures

Pick up and place in appropriate container

7. Handling and storage

The fumes produced during soldering should be extracted away from the breathing zone of the operators. Ensure the area is well

ventilated. Wash hands with soap and warm water after handling, particularly before eating, drinking or smoking.

The product should be stored in a cool, dry area.

EC Safety Data Sheet according to Directive 1907/2006

Trade name: Solder-wire KS 100 FLOWTIN ® TC (S-Sn99Cu1)

Date of issue: 01.04.2006 Revised on: 23.11.2011 Date of print: 17.02.2012 Page: 2(3)

8. Exposure controls and personal protection

Additional information on system design:

Local exhaust or dilution ventilation and control of process conditions are suitable methods..

Substances with limit values to be monitored at the working place:

Danger to health at the working place:

Peak limit category:

Working place limit values according to TRGS 900 from Section 2 for Germany:

Product name CAS No. ml/m³ (ppm) mg/m³ Type

 Tin
 7440-31-5
 2
 MAK (NL)

 Copper
 7440-50-8
 1
 MAK (DFG)

 Skin resorption / Sensitization:
 Sensitization:

General protection and hygiene measures

Avoid direct contact with eyes, the skin and clothing.

Personal protection

Respiratory protection: If concentrations are over the exposure limit, use a supplied air respirator.

Hand protection:

Eye protection:

Personal protection:

Use heat resistant gloves if required.
Operators should wear goggles
Light protective clothing

9. Physical and chemical properties

Form: Tin-Copper Solder

Colour: silver

 Melting Point:
 227 °C

 Vapour Pressure:
 n.a.

 Density(20°C):
 7-8 g/cm³ g/cm³

10. Stability and reactivity

Reaction with substances: Possible with oxidising agents.

Hazardous combustion or none

decomposition products:

11. Toxicological information

The toxicological classification of the product is based on the results of the calculation procedure of the general preparation

directive 1999/45/EC.

Acute Effects:

None toxic metal.

12. Ecological information

General information: No effect to environment known

13. Disposal considerations

Disposal information

Product: Contact a licensed professional waste disposal service to dispose of this material.

Further information: Observe all federal, state and local environmental regulations. Collect metal for recycling

Waste identity number: Waste identity number EAK-code: 120104

14. Transport information

GGVS/ADR/RID: The product is not classified as hazardous for transport

EC Safety Data Sheet according to Directive 1907/2006

Trade name: Solder-wire KS 100 FLOWTIN ® TC (S-Sn99Cu1)

Date of issue: 01.04.2006 Revised on: 23.11.2011 Date of print: 17.02.2012 Page: 3(3)

15. Legal regulations:

Labelling information: The product is classified and labelled according to the EC Directives.

Not subject to current legislation

Water hazard class:

WGK 1 (weakly water-endangering)

Classification according to the TA Luft: Organic materials class III; whole-carbon-concentration: Max. acceptable

Emission50 mg/m³ (mass-flow-rate >= 0,5 kg/h)

Ingredients: Tin, copper, resin

16. Further information

R-phrases point 3:-----

n.k.: not known n.a.: not applicable

Other information

This statement is based on our current knowledge and offers no assurance of product properties.

Department issueing the data sheet

Stannol GmbH/Quality Assurance/Laboratory

Contact person Dr. Kruppa

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for stannol manufacturer:

Other Similar products are found below:

574114 574007 648111 810843 HS10 FAIR, 1.0MM, 250G 574101 593311 574402 574104 631946 631939 535768 HS10 2510 1,2MM 250G STANNOL 574112 HS10 2510 1,0MM 250G 593331 810041 594300 631962 810031 HS10 FAIR, 1.0MM, 5G 310457 594050 810899 810812 593132 HS10 2510 0,5MM 500G 593420 648110 594052 810916 631967 574117 574110 810913 593063 631965 810001 535759 535762 810863 810044 574400 810904 810045 593003 593032 810792 810793 574106