SPECIFICATION CONTROL DRAWING		44A7422
WIRE, RADIATION-CROSSLINKED, POLYALKENE-INSULATED, MEDIUM WEIGHT, 600 VOLT	7-28-11	Т

This specification sheet forms a part of the latest issue of Raychem Specification 44.

CONDUCTOR - E.C. ALUMINUM

JACKET - RADIATION-CROSSLINKED, MODIFIED PVDF
Thickness: .006 + .002 in.
- .001 in.

BRAIDS - 1st, GLASS BRAID
2nd, PET, TREATED TO
PREVENT FRAYING

	TABLE I. CONSTRUCTION DETAILS					
	SIZE STRAN		DIAMETER OF	FINISHED WIRE		
PART NUMBER 1/		CONDUCTOR STRANDING (number x AWG)	STRANDED CONDUCTOR (in.)	MAXIMUM RESISTANCE AT 20°C (ohms/1000 ft)	DIAMETER (in.)	MAXIMUM WEIGHT (lbs/1000 ft.)
44A7422-8-**	8	41 x 24	.155 ± .005	1.09	.217 ± .010	28.0
44A7422-6-**	6	70 x 24	.206 ± .005	.641	.275 ± .012	44.9
44A7422-4-**	4	107 x 24	.255 ± .007	.427	.327 ± .012	63.9
44A7422-2-**	2	168 x 24	.320 ± .010	.268	.400 ± .015	94.6
44A7422-1-**	1	219 x 24	.358 ± .010	.214	.440 ± .015	120.
44A7422-0-**	0	259 x 24	.408 ± .012	.169	.490 ± .015	142.
44A7422-00-**	00	334 x 24	.466 ± .012	.133	.560 ± .018	183.
44A7422-000-**	000	427 x 24	.523 ± .012	.109	.620 ± .020	223.
44A7422-0000-**	0000	523 x 24	.575 ± .012	.085	.680 ± .022	269.

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.

Tyco Electronics Corporation also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER. AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER

Page 1 of 2

Raychem, TE Connectivity, TE connectivity (logo) and TE (logo) are trademarks.

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.



Raychem Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-227-8816 Fax: 1-650-361-6297



## SPECIFICATION CONTROL DRAWING

Page 2 of 2

Revision SCD Number

Т

44A7422

TABLE II. PERFORMANCE DETAILS						
	BEND TESTING					
PART NUMBER	MANDREL DIAMETER (inch) (± 3%)			WEIGHT (lb) (± 3%)		
1/	IMMERSION LIFE CYCLE AND ACCELERATED AGING	COLD BEND	WRAP	IMMERSION LIFE CYCLE AND ACCELERATED AGING	COLD BEND	
44A7422-8-**	3.00	6.00	.750	3.00	6.00	
44A7422-6-**	4.00	8.00	1.00	3.00	10.0	
44A7422-4-**	5.00	10.0	1.25	3.00	10.0	
44A7422-2-**	6.00	12.0	3.00	4.00	15.0	
44A7422-1-**	7.00	13.0	4.00	4.00	15.0	
44A7422-0-**	8.00	14.0	4.00	4.00	15.0	
44A7422-00-**	9.00	16.0	5.00	4.00	15.0	
44A7422-000-**	10.0	18.0	6.00	4.00	15.0	
44A7422-0000-**	12.0	18.0	6.00	4.00	15.0	

## WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C

Maximum continuous conductor temperature VOLTAGE RATING: 600 volts (rms) at sea level \*ACCELERATED AGING: 300  $\pm$  2°C for 7 hours

Identification legibility, 225 ± 2°C \*BLOCKING: 150 ± 2°C for 6 hours

BRAID (PET) COLOR: For tan only, Munsell Color Limits are per Table III. (Note: Due to the braid treatment, braids may include intermitten color variations such as smudges, spots or marks.) FLAMMABILITY: 30 seconds (maximum); 3 in. (maximum); no flaming of facial tissue

\*HUMIDITY RESISTANCE: Insulation Resistance, 5000 megohms for 1000 ft. (minimum)

IMMERSION: Diameter increase 5% (maximum); no cracking, no dielectric breakdown.

INSULATION ELONGATION AND TENSILE STRENGTH:

Primary Insulation,

Elongation, 150% (minimum)

Tensile Strength, 2000 lbf/in2 (minimum)

**INSULATION FLAWS:** 

Primary Insulation,

Spark Test, 3.0 kV (rms)

Impulse Dielectric Test, 6.0 kV (peak)

Finished Wire,

Spark Test, 5.0 kV (rms) at 3 kHz Impulse Dielectric Test, 8.0 kV (peak) INSULATION RESISTANCE: 5000 megohms for 1000 ft. (minimum)

JACKET COLOR: White

LIFE CYCLE: 200 ± 2°C for 168 hours

LOW TEMPERATURE-COLD BEND: -65  $\pm$  2°C for 4 hours SHRINKAGE: 300  $\pm$  2°C, 0.125 in. (maximum) in 12 in.

SMOKE: 200 ± 2°C. No visible smoke.

\*SURFACE RESISTANCE: 500 megohms-in. (minimum), both readings

THERMAL SHOCK RESISTANCE: 150 ± 2°C, 0.060 in. (maximum)

VOLTAGE WITHSTAND (Post Environmental):

2500 volts (rms), 60 Hz, 5 minutes

PART NUMBER: The "\*\*" in the part numbers on pages 1 and 2 shall be replaced by color code designators.

1/ Example: AWG 8, tan; 44A7422-8-1L AWG 8, white; 44A7422-8-9

TABLE III. MUNSELL COLOR LIMITS (For Tan)		
HUE	5R - 5YR	
VALUE	3.0 - 5.0	
CHROMA	4.0 - 6.0	

<sup>\*</sup> NOTE: These tests to be conducted prior to the application of the braids.

## **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Hook-up Wire category:

Click to view products by TE Connectivity manufacturer:

Other Similar products are found below:

002333-000 M81044/12-22-6 M81044/9-8-9 743094-001 81044/12-18-9CS3209 ATFC0311-20-5D EF5675-000 BFWUL3239-24-PINK
22759/34-16-9CS2621 22759/42-24-9CS2620 933205-000 30802-009-250 99M0111-20-2 A00594-000 190571-000 22759/41-12-9CS2620
22759/41-16-9CS2620 22759/43-10-9CS2873 CM9524-000 31510-010-250 34401-010-250 34402-010-500 M81044/9-4-9 391441-BK007
400R0111-10-9 431660-000 ATFC0311-20-0 44/7024-26-9-9 44A0112-22-9CS3184 BFW-UL3239-24-WHITE 55/0312-26-6L-CS2570
55A0811-12-9 55A6087-20-9-9-9 55A7400-22-9/96-9CS2275 55A9002-30-5 55PC0211-20-5CS2502 55PC0811-6-9CS2637 55PC1211-22-9-9CS3278 C07683-000 34020-008-2000 391850-BK199 392075-RD199 W28-6HU 44A0112-24-9CS3184 44A0211-16-8-1KF/1
44A0211-16-9CS3030 084299-000 100E0111-0.50-9 100E0111-0.75-9 10603-0-0CS1803