

Flexible, adhesive-lined, polyolefin heat-shrinkable tubing

TAT-125 is an adhesive-lined, flexible, thin-wall, heat-shrinkable tubing. It provides one-step electrical insulation and moisture sealing for a wide variety of applications.

TAT-125 is especially suitable for applications where the moisture seal

must withstand flexing or other physical abuse. Because both tubing and adhesive are flexible, the moisture seal is resistant to bending of the substrate.

The thin adhesive lining of TAT-125 melts and flows with the heat of

application to form a positive environmental seal. The adhesive will adhere to a wide variety of plastics, rubbers, and metals, including PVC, polyethylene, neoprene, lead, and steel.

Temperature rating

| | |
|-----------------------------------|----------------|
| Full recovery temperature: | 121°C |
| Continuous operating temperature: | -55°C to 110°C |

Specifications*

| Type | Raychem | Military | UL |
|-------------------------|---------|------------------------|--------|
| TAT-125 Type 1 (colors) | RW-3032 | AMS-DTL-23053/4, Cl. 2 | E85381 |
| TAT-125 Type 2 (clear) | RW-3032 | | |

*When ordering, always specify latest issue.

Dimensions (millimeters/inches)



| Size | Inside diameter | | Recovered wall thickness** | | | |
|-------|-------------------------------------|----------------------------------------|----------------------------|--------------------------------|---|----|
| | D (min.) Expanded as supplied | d (max.) Recovered after heating | W Nominal total wall | W1 Nominal adhesive wall | W | W1 |
| 1/8 | 3.2 0.125 | 1.6 0.062 | 0.68 0.027 | 0.23 0.009 | | |
| 3/16 | 4.7 0.187 | 2.4 0.093 | 0.71 0.028 | 0.25 0.010 | | |
| 1/4 | 6.4 0.250 | 3.2 0.125 | 0.74 0.029 | 0.13 0.005 | | |
| 3/8 | 9.5 0.375 | 4.7 0.187 | 0.74 0.029 | 0.13 0.005 | | |
| 1/2 | 12.7 0.500 | 6.4 0.250 | 0.76 0.030 | 0.15 0.006 | | |
| 3/4 | 19.1 0.750 | 9.5 0.375 | 0.89 0.035 | 0.15 0.006 | | |
| 1 | 25.4 1.000 | 12.7 0.500 | 1.07 0.042 | 0.20 0.008 | | |
| 1 1/2 | 38.1 1.500 | 19.1 0.750 | 1.19 0.047 | 0.28 0.012 | | |
| 2 | 50.8 2.000 | 25.4 1.000 | 1.65 0.065 | 0.56 0.022 | | |
| 3 | 76.2 3.000 | 38.1 1.500 | 1.65 0.065 | 0.56 0.022 | | |
| 4 | 101.6 4.000 | 50.8 2.000 | 1.78 0.070 | 0.56 0.022 | | |

**Wall thickness will be less if tubing recovery is restricted during shrinkage.

Ordering information

| | |
|----------------------|--------------------------------------------------------------------------------------------------------------------------|
| Colors | Standard Black Nonstandard White, red, blue, yellow, green, orange, brown, violet, clear (non-flame-retardant jacket) |
| Size selection | Always order the largest size that will shrink snugly over the component being covered. |
| Standard packaging | 4-foot lengths |
| Nonstandard sizes | Sizes of 2 inches and larger are by special order only. Other nonstandard sizes are available upon special request. |
| Ordering description | Specify product name, size, and color; for example, TAT-125 1/4-0 (0=Black). |

Specification values

| | Property | Unit | Requirement | Method of test |
|----------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------|-----------------------------------------------------------------|---------------------------------|
| Physical | Dimensions | mm (<i>inches</i>) | See reverse | ASTM D 2671 |
| | Longitudinal change* | percent | +0, -5 maximum | ASTM D 2671 |
| | Tensile strength | psi | 1500 minimum | ASTM D 2671 |
| | Ultimate elongation | percent | 200 minimum | ASTM D 2671 |
| | Secant modulus (as supplied) | psi | 2.5 x 10 ⁴ maximum | ASTM D 2671 |
| | Cold impact (at -55°C/-67°F) | | No cracking | AMS-DTL-23053 |
| | Heat shock (4 hours at 250°C/482°F) | | No dripping, flowing, or cracking of outer wall | AMS-DTL-23053 |
| | Heat resistance (168 hours at 175°C/347°F) | | No dripping, flowing, or cracking of outer wall | AMS-DTL-23053 |
| | Color | | Pass | MIL-STD 104 |
| Color stability (24 hours at 175°C/347°F) | | Pass | MIL-STD 104 | |
| Electrical | Dielectric strength | volts/mil | | ASTM D 2671 |
| | Sizes 1/8" through 1" Sizes 1 1/2" and larger | | 500 minimum 400 minimum | |
| | Volume resistivity | ohm-cm | 1 X 10 ¹² minimum | ASTM D 2671 |
| Chemical | Copper corrosion (16 hours at 121°C/250°F) | | No corrosion | ASTM D 2671 Procedures A & B |
| | Flame retardancy** | | Self-extinguishing within 1 minute, 25% maximum flag burn | AMS-DTL-23053 Test A |
| | Fungus resistance | | Rating of 1 or less | ASTM G21 |
| | Water absorption (24 hours at 23°C/73°F) | percent | 0.5 maximum | ASTM D 2671 |
| | Fluid resistance (24 hours at 24°C/75°F) in: Hydraulic fluid (MIL-H-5606) JP-8 fuel (MIL-T-5624) Lubricating oil (MIL-L-7808 and MIL-I-23699) | | AMS-DTL-23053 | |
| | Salt water, 5% (O-S-1926) De-icing fluid (MIL-A-8243) Followed by tests for: | | | |
| | Tensile strength | psi | 1000 minimum | ASTM D 2671 |
| | Dielectric strength | volts/mil | | ASTM D 2671 |
| | Sizes 1/8" through 1" | | 400 minimum | |
| | Sizes 1 1/2" and larger | | 300 minimum | |

Note: Except for dimensions and longitudinal change, specification values apply to outer jacket only. *Sizes and colors not included in AMS-DTL-23053/4, Class 2 have a longitudinal change requirement of +0, -10 maximum. **Only the outer jacket of TAT-125 is flame-retardant; the outer jacket of clear TAT-125, however, is not flame-retardant.

| Typical properties | Adhesive | |
|--------------------|------------------|-------------------|
| | Peel strength | T-PEEL, 2"/minute |
| Polyethylene | 15 lb./in. width | |
| Neoprene | 10 lb./in. width | |
| PVC | 10 lb./in. width | |
| Lead | 5 lb./in. width | |
| Steel | 15 lb./in. width | |

Raychem is a trademark of Tyco Electronics Corporation.

Users should independently evaluate the suitability of the product for their application.

Tyco Electronics Corporation

300 Constitution Drive
Menlo Park, CA 94025-1164
USA
Tel: (800) 926-2425 (US & Canada)
Tel: +1 (650) 361-3860 (All other countries)

Faraday Road
Dorcan, Swindon, SN3 5HH
United Kingdom
Tel: +44 1793 528171

3816 Noborito, Tama-ku
Kawasaki, Kanagawa 214-8533
Japan
Tel: +81 44 900 5102

Asia Pacific Headquarters
26 Ang Mo Kio, Industrial Park 2
Singapore 569507
Tel: +65 4866 151

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics Corporation makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Tyco Electronics Corporation's only obligations are those in the Standard Terms and Conditions of Sale for these products and in no case will Tyco Electronics Corporation be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use, or misuse of the product. Tyco Electronics Corporation's Specifications are subject to change without notice. In addition, Tyco Electronics Corporation reserves the right to make changes in materials or processing without notification to the Buyer which do not affect compliance with any applicable specification.

For more information about this product visit www.tycoelectronics.com

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [Heat Shrink Tubing and Sleeves](#) category:

Click to view products by [TE Connectivity](#) manufacturer:

Other Similar products are found below :

[770-006S102](#) [5685710001](#) [CR6145-000](#) [CR8248-000](#) [CR9960-000](#) [603312-4](#) [607381P039](#) [611112-000](#) [617867N001](#) [6500750004](#) [CZ1420-000](#) [D-306-38](#) [770-003S106W2](#) [770-005S105W1](#) [770-005S106W1](#) [770-007A303](#) [770-010Y106W1](#) [770-010Y706W1](#) [7771210001](#) [MFP-1/4"-Clear](#) [MFP-3/64"-Clear](#) [790-3012](#) [MFT-MT2000-NO.14-0-SP](#) [MHHT-4-15K2-G-104](#) [MIL-LT-1-1/2-4-SP](#) [MIL-LT-1-1/2-9-STK](#) [MIL-LT-1/2-2-STK](#) [MIL-LT-3-0-SP](#) [MIL-LT-3/32-0-SP](#) [MIL-LT-3/32-6-SP](#) [MIL-LT-3/4-6-SP](#) [MIL-LT-3/8-0-SP](#) [8159270001](#) [839602-000](#) [8423-6](#) [FP301-116-6"-Black](#) [FP301-1/2-48"-Black](#) [FP301-12-48"-Black-Hdr](#) [FP301-1/4-48"-Black](#) [FP301-1/4-48"-White-Hdr](#) [FP301-18-48"-Black-Hdr](#) [FP301-1/8-6"-Black](#) [FP301-18-6"-Black-Bulk](#) [FP301-316-48"-Blue-Hdr](#) [FP301-316-6"-Clear](#) [FP301-332-6"-Black](#) [912229N002](#) [120-126-16BL](#) [121-001-09](#) [121-018-32](#)