### SPECIFICATION CONTROL DRAWING

CHEMINAX

.0250

052

± .002

111

.127

(nominal)

.135

(maximum)

77 OHM, AWG 24, 19 STRANDS OF AWG 36, DATA BUS CABLE, OUTER SPACE USE

7724E2664 Date:

F

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200.

#### CONSTRUCTION DETAILS

CONDUCTORS AWG 24,

**DIELECTRICS** 

SHIELD - Flat

**JACKET** 

Designate outer jacket color with a dash number in accordance

will be white designated by a "-9" appended to the part number,

Other codes and suffixes may be added to the part number, as

necessary, to capture any additional requirements imposed by

with MIL-STD-681. Unless otherwise specified, outer jacket color

Modified ETFE

19 Strands of AWG 36.

Strength Copper Alloy

Radiation-Crosslinked,

Colors - Light Blue/White

.0015 Strand Thickness.

Silver-Coated Copper

Radiation-Crosslinked,

Modified ETFE

Silver-Coated High-

DIMENSIONS ARE NOMINAL VALUES IN INCHES, UNLESS OTHERWISE DESIGNATED.

**ELECTRICAL CHARACTERISTICS** 

CHARACTERISTIC IMPEDANCE MUTUAL CAPACITANCE

77 ± 7 ohms. Method C at 1 MHz 30.0 pF/ft. (maximum)

**ATTENUATION** 

1.0 dB/100 ft. (nominal) at 1 MHz 8.0 dB/100 ft. (maximum) at 10 MHz

SURFACE TRANSFER IMPEDANCE 70 milliohms/meter (nominal) at 10 MHz

Revision:

## ADDITIONAL REQUIREMENTS

#### COMPONENT WIRE PRIOR TO CABLING (Test procedures per SAE AS22759)

CONDUCTOR RESISTANCE 26.5 ohms/1000 ft. (nominal)

CROSSLINKING PROOF TEST 300 ± 3°C for 1 hour, .500 inch mandrel,

.500 lb, 2.5 kV dielectric test

INSULATION (DIELECTRIC)

**ELONGATION** 50% (minimum) TENSILE STRENGTH 5000 lbf/in2 (minimum)

INSULATION FLAWS

SPARK TEST 3.0 kV (rms) **IMPULSE TEST** 8.0 kV (peak)

INSULATION RESISTANCE 5000 megohms for 1000 ft. (minimum) LOW TEMPERATURE-COLD BEND -65 ± 3°C for 4 hours, .500 inch mandrel,

1.00 lb, 2.5 kV dielectric test

**SHRINKAGE** 200 ± 3°C for 1 hour.

.125 inch (maximum) in 12 inches

#### **FINISHED CABLE**

#### (Test procedures per NEMA WC 27500, unless otherwise specified)

**BLOCKING** 200°C for 6 hours

CABLE LAY LENGTH .75 inch (minimum), 1.25 inches (maximum) CROSSLINKED VERIFICATION 300 ± 5°C for 6 hours, 6.00 inch mandrel 3 seconds (maximum), 3 inches (maximum); **FLAMMABILITY** 

(Method B of Spec 1200) no flaming of facial tissue

**JACKET** 

**ELONGATION** 50% (minimum) **TENSILE STRENGTH** 5000 lbf/in2 (minimum)

JACKET FLAWS

SPARK TEST 1.0 kV (rms) **IMPULSE TEST** 6.0 kV (peak) JACKET THICKNESS .008 inch (nominal)

LOW TEMPERATURE-COLD BEND -55 ± 5°C for 4 hours, 6.00 inch mandrel

SHIELD COVERAGE 90% (minimum)

**VOLTAGE WITHSTAND** 1000 volts (rms) (minimum)

(DIELECTRIC)

WEIGHT 10.4 lbs/1000 ft. (nominal)

RADIATION RESISTANCE 500 megarads/3.75 inch mandrel

VACUUM STABILITY TOTAL MASS LOSS (TML) **VOLATILE CONDENSABLE** 

1.00% (maximum) 0.10% (maximum)

**OUTER SPACE REQUIREMENTS** 

MATERIAL (VCM)

WEIGHT LOSS 0.45% (maximum)

**ENGINEERING REFERENCE** 

TEMPERATURE RATING 200°C (maximum)

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. TE Connectivity also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

Page 1 of 1

Cheminax, Raychem, TE Connectivity, and TE connectivity (logo) are trademarks.



e.g. 7724E2664-9.

the purchase order.

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Coaxial Cables category:

Click to view products by TE Connectivity manufacturer:

Other Similar products are found below:

89880-003-1000 CY2389-000 8221-010-U1000 9116-010-U500 1322R-010-1000 1807A-B59-U1000 2020K8421-9X-CS3417 9251-010-1000 9275-010-U1000 935240-000 980704-001 CF2823-000 33312-010-500 CZ1589-000 5022W0809-0CS3263 10610-4-4 EF8108-000 1673B TIN100 672525-001 144517-000 735A1-008-1000 8212-010-U500 480414-000 7915A 009U1000 5024A1311-0 1281S5 010250 1530A 010U1000 9248 010U1000 9244 0101000 1694A 0081000 1190A 0101000 8241F J5C1000 1674A TIN50 7915A 0091000 TRCH-50-2 9066 0031000 7805R 008100 1674A TIN100 9116SB 0101000 9271 0061000 1613A 0101000 1807A B591000 5339Q5 009U500 539945 0091000 9116R 0101000 89207 010100 9058 0101000 8241A 0101000 DA7805R 0101000 C6424