## SPECIFICATION CONTROL DRAWING

7726D3664

**CHEMINAX** 

.0200

.037

.025

.091

.108

.124

77 OHM. AWG 26. 19 STRANDS OF AWG 38. OPTIMIZED DOUBLE SHIELD, DATA BUS CABLE, MIL-STD-1553

4-29-13 Date Revision В

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200

### CONSTRUCTION DETAILS

**ELECTRICAL CHARACTERISTICS** 

DIMENSIONS ARE NOMINAL VALUES IN INCHES UNLESS OTHERWISE

CONDUCTORS AWG 26, 19 Strands of

AWG 38, Silver-Coated High-Strength Copper Alloy

**DIELECTRICS** 

Radiation-Crosslinked. Modified ETFE Colors - Light Blue/White

**FILLERS** 

Radiation-Crosslinked, Modified ETFE

1ST SHIELD

AWG 38, Tin-Coated Copper Optimized

2<sup>ND</sup> SHIELD

AWG 38.

Tin-Coated Copper Optimized

**JACKET** 

Radiation-Crosslinked, Modified ETFE

CHARACTERISTIC IMPEDANCE

77 ± 5 ohms, Method C at 1 MHz

MUTUAL CAPACITANCE 30.0 pF/ft. (maximum)

**ATTENUATION** 1.5 dB/100 ft. (maximum) at 1 MHz

SURFACE TRANSFER IMPEDANCE 10 milliohms/meter (maximum)

(Per MIL-DTL-85485 at 30 MHz)

## ADDITIONAL REQUIREMENTS

**COMPONENT WIRE PRIOR TO CABLING (Test Procedures per SAE AS22759)** 

CONDUCTOR RESISTANCE 42.0 ohms/1000 ft. (nominal)

CROSSLINKING PROOF TEST 300 ± 3°C for 1 hour, .500 inch mandrel,

.250 lb., 2.5 kV dielectric test INSULATION (DIELECTRIC)

**ELONGATION** 50% (minimum) TENSILE STRENGTH 5000 lbf/in2 (minimum)

**INSULATION FLAWS** SPARK TEST 3.0 kV (rms) 8.0 kV (peak)

IMPULSE TEST INSULATION RESISTANCE 5000 megohms for 1000 ft. (minimum) -65 ± 3°C for 4 hours, .500 inch mandrel, LOW TEMPERATURE-COLD BEND

.500 lb., 2.5 kV dielectric test

**SHRINKAGE** 200 ± 3°C for 1 hour,

.125 inch (maximum) in 12 inches

#### **FINISHED CABLE**

(Test Procedures per NEMA WC 27500, unless otherwise specified)

**BLOCKING** 

CABLE LAY LENGTH

**CROSSLINKED VERIFICATION** 

**FLAMMABILITY** 

(Method B of Spec 1200)

JACKET

**ELONGATION** TENSILE STRENGTH

JACKET FLAWS SPARK TEST

**IMPULSE TEST** JACKET THICKNESS

LOW TEMPERATURE-COLD BEND

**VOLTAGE WITHSTAND** 

(DIELECTRIC)

WEIGHT

200°C for 6 hours

.75 inch (minimum), 1.25 inches (maximum) 300 ± 5°C for 6 hours, 3.00 inch mandrel 3 seconds (maximum); 3 inches (maximum);

no flaming of facial tissue

50% (minimum)

5000 lbf/in2 (minimum)

1.0 kV (rms) 6.0 kV (peak) .008 inch (nominal)

-55 ± 5°C for 4 hours. 3.00 inch mandrel

1500 volts (rms)

16.6 lbs/1000 ft. (nominal)

Outer jacket color will be white (designated by a "-9" appended to the part number, e.g. 7726D3664-9) unless otherwise specified

Designate outer jacket color with a dash number in accordance with MIL-STD-681. Other codes and suffixes may be added to the part number, as necessary, to capture any additional requirements imposed by the purchase order.

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics Corporation also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

Page 1 of 1 Cheminax, Raychem, TE Connectivity, TE connectivity (logo) and TE (logo) are trademarks.



# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for TE Connectivity manufacturer:

Other Similar products are found below:

D38999/24FJ4AN 570416-000 CLTEQ-M81CE-SSRELAY-4-20V 4-1195131-0 650069-000 SMD100-2 358838-000 CB-1022B-78

RM707012 RP410012 MMS42 1-640426-8 2EDL4CM DTS20W19-11PD-3028-LC RM202615 NC6-P104-06 MSPS103B DTS26F2141HE-LC DTS26F21-41AE DTS26F21-41PE-LC DTS26F21-11SE-3028-LC 30DCB6 1932144-1 293545-4 LVR125S MS27466T25F4PB

CKB-38-78010 TR04AI-TINELLOCKRING 1206SFF150F/63-2 D38999/20JB35HA TE1500A2R2J D38999/20WC8BB DTS24F19-11SC3028-LC D38999/24WG11HA D38999/24WG11HN MS27467T21F11H DJT16E21-11HA MS27467T21F35J MS27467T21F11J

MS27467T21F16H-LC MS27467T21F35H MS27467T21F41H-LC 1206SFH150F/24-2 RP330024 DJT16E21-11PA-LC DJT16E21-11HA
LC DJT16E21-11AA MS27467T21B11JA DJT16E21-11JA MS27467T21B11JA-LC