DWFR Highly Flame-Retardant, Dual Wall Polyolefin Heat-Shrinkable Tubing




Table 1: <u>Dimensions</u>: mm (in)

Shrink Ratio	Size	Minimum Inside Diameter as supplied (D) mm (<i>in</i>)	Maximum Inside Diameter after recovery (d) mm (<i>in</i>)	Total Wall Thickness after recovery (W) mm (<i>in</i>)	Minimum Inner Meltable Wall Thickness after recovery mm (<i>in</i>)
3:1	3/1	3.0 (0.118)	1.0 (0.039)	$1.12 \pm 0.25 (.044 \pm .010)$	0.25 (0.010)
	6/2	6.0 (0.236)	2.0 (0.079)	$1.14 \pm 0.25 (.045 \pm .010)$	0.25 (0.010)
	9/3	9.0 (0.354)	3.0 (0.118)	$1.40 \pm 0.25 \; (.055 \pm .010)$	0.56 (0.022)
	12/4	12.0 (0.472)	4.0 (0.157)	$1.78 \pm 0.36 \ (.070 \pm .014)$	0.58 (0.023)
	19/6	19.0 (0.748)	6.0 (0.236)	$2.25 \pm 0.50 \; (.088 \pm .020)$	0.58 (0.023)
	24/8	24.0 (0.945)	8.0 (0.315)	$2.54 \pm 0.50 \; (.100 \pm .020)$	0.79 (0.031)
	40/13	40.0 (1.575)	13.0 (0.512)	$2.54 \pm 0.50 \; (.100 \pm .020)$	0.86 (0.034)
4:1	4/1	4.0 (0.157)	1.0 (0.039)	$1.12 \pm 0.25 (.044 \pm .010)$	0.25 (0.010)
	8/2	8.0 (0.315)	2.0 (0.079)	$1.14 \pm 0.25 \; (.045 \pm .010)$	0.25 (0.010)
	12/3	12.0 (0.472)	3.0 (0.118)	$1.40 \pm 0.25 \; (.055 \pm .010)$	0.56 (0.022)
	16/4	16.0 (0.630)	4.0 (0.157)	$1.78 \pm 0.36 \ (.070 \pm .014)$	0.58 (0.023)
	24/6	24.0 (0.945)	6.0 (0.236)	$2.25 \pm 0.50 \; (.088 \pm .020)$	0.58 (0.023)
	32/8	32.0 (1.260)	8.0 (0.315)	$2.54 \pm 0.50 \; (.100 \pm .020)$	0.79 (0.031)
	52/13	52.0 (2.047)	13.0 (0.512)	$2.54 \pm 0.50 \; (.100 \pm .020)$	0.86 (0.034)

Material:

The tubing shall be fabricated from a modified irradiated polyolefin compounded to produce a homogeneous, uniform product whose outside surface is essentially free from flaws, defects, pinholes, seams, cracks, or inclusions. The interior wall is coated with a thermoplastic adhesive. The standard color is black.

© 2016 Tyco Electronics Corporation. All Rights Reserved				Customer Drawing		
			Tubing TE CONNECTIVITY 300 Constitution Drive Menlo Park, CA 94025 USA	Title: DWFR Highly Flame-Retardant, Dual Wall Polyolefin Heat-Shrinkable Tubing		al Wall Polyolefin
TE Connectivity reserves the right to amend this drawing at any time. Users should evaluate the suitability of the product for their application			Document No : DWFR			
Cage Code: 06090	Scale: None	Size: A	Rev. Date: 28-January-16		Rev. E	Sheet: 1 of 2

If this document is printed it becomes uncontrolled. Check for the latest revision.

<u>Properties</u>:

PROPERTY	UNIT	REQUIREMENT	TEST METHOD
PHYSICAL			
*Dimensions	mm (<i>in</i>)	In accordance with Table 1	ASTM D 2671
Longitudinal Change	Percent	0, -15%	ASTM D 2671
*Tensile Strength	psi (MPa)	1500 minimum (10.3)	
			ASTM D 2671
*Ultimate Elongation	Percent	200 minimum	
Secant Modulus (Expanded)	psi (MPa)	2.5 x 10 ⁴ maximum (172)	ASTM D 882, 2% strain
Cold Bend Test		No cracking	UL 224, section 5.9
at $-30 \pm 1.0^{\circ}$ C (-22 $\pm 1.8^{\circ}$ F) for 1			
hour			
*Heat Shock		No dripping, flowing or	UL 224, section 5.8
4 hours at 250.0 \pm 1.0°C (482 \pm		cracking of outer wall	
1.8°F)			
Heat Resistance			UL 224
168 hours at $158.0^{\circ}C \pm 1.0^{\circ}C$ (316.4			
$\pm 1.8^{\circ}F)$			
Followed by test for:			
- Tensile Strength	psi (MPa)	Min. 70% of original	
- Elongation	Percent	100% minimum	
Sealing Efficiency		No openings on reheat	AMS-DTL 23053/4
ELECTRICAL			
Dielectric Strength	Volts/mil	300 minimum (11,811 min)	ASTM D 2671
	(volts/mm)	on dual wall specimen	
Volume Resistivity	ohm-cm	10^{14} minimum on dual wall	ASTM D 2671
		specimen	
CHEMICAL			
Corrosion of the bare copper		No pitting or blackening of	UL 224, section 5.16
168 hours at $158.0^{\circ}C \pm 1.0^{\circ}C$ (316.4		copper	
$\pm 1.8^{\circ}F)$			
Copper stability		Show no sign of degradation	UL 224, section 5.17
168 hours at $158.0^{\circ}C \pm 1.0^{\circ}C$ (316.4			
$\pm 1.8^{\circ}F)$			
Followed by test for:			
- Elongation	Percent	100% minimum	
Flammability		Self-extinguishing within 1	
		minute, 25% maximum flag	UL 224, VW-1
		burn and 0% cotton burn	
Water Absorption	Percent	0.5 maximum	ASTM D 2671
24 hours at 23°C (73°F)			

* Denotes Lot Acceptance Test

		Customer	Drawing
Rev. Date:	Rev.:	Document No.	Sheet:
28-January-16	E	DWFR	2 of 2

If this document is printed it becomes uncontrolled. Check for the latest revision.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Heat Shrink Tubing and Sleeves category:

Click to view products by TE Connectivity manufacturer:

Other Similar products are found below :

 5685710001
 CR9960-000
 5734012004
 607381P039
 611112-000
 6284592002
 CX4711-000
 CZ1420-000
 D-306-38
 770-006S302
 770

 010Y106W1
 770-020S705
 MFP-3/64"-Clear
 790-3012
 MHHT-4-15K2-G-104
 8003012003
 MIL-LT-1/2-4-SP
 MIL-LT-1/2-9-STK

 MIL-LT-1/2-2-STK
 MIL-LT-3-0-SP
 MIL-LT-3/32-0-SP
 MIL-LT-3/32-6-SP
 MIL-LT-3/4-4-STK
 MIL-LT-3/4-6-SP
 839602-000
 8423-6

 FP301-116-48"-Clear
 FP301-12-6"-Clear
 FP301-1/4-48"-White-Hdr
 FP301-18-48"-Black-Hdr
 FP301-1/8-6"-Black
 FP301-18-6"-Black-Bulk

 FP301-316-48"-Blue-Hdr
 912229N002
 R280637030
 HDCW-5515-1000
 HDT-0300-48A-BLACK
 HDT-0400-48A-Black
 HDT-0800-48A-Black-Black

 RED
 HDT1100-48A-BLK
 HDT1500-48A-BLK
 HDT-2000-48A-Black
 RHW-70/20-1200/ADH-0
 DWP-125-0.450-4-55MM-CS879
 156082-000

 000
 MT5500-3/8-X-SP
 MT-FEP-045-032-008-X-60IN
 EPS200-1/4-48"-Black
 EPS200-3/16-48"-Black
 EPS200-3/16-48"-Black