

RW-175

Raychem

Thin-wall, semirigid, fluoropolymer heat-shrinkable tubing

RW-175 heat-shrinkable tubing is a tough, semirigid, very-thin-wall insulation. It is especially suitable for applications requiring high-temperature performance, outstanding abrasion and cut-through resistance, or superior chemical and solvent properties. The translucent polyvinylidene fluoride material permits visual inspection of covered components.

RW-175 tubing provides electrical insulation and strain relief of multipin connectors and solder joints. It is also widely used as insulation for high-temperature components and heater leads. With its thin-wall construction, RW-175 is ideal for applications that require dense packing of components.

RW-175 provides protection from most industrial solvents, fuels, and chemicals – including JP-8, oxidants, and strong acids. It is UL-recognized and CSA-certified at 150°C, 600 V, with VW-1 and OFT flame-retardancy ratings.

Wall thickness

Temperature rating

Full recovery temperature:	175°C
Continuous operating temperature:	-55°C to 175°C
Recommended maximum temperature for use as a primary insulator	: 135°C

Specification	?S*		91	(1) °	
Туре	Raychem	Military	UL	CSA	
RW-175	RW-3029/2	AMS-DTL-23053/8	E35586 VW-1	LR31929 OFT	

^{*}When ordering, always specify latest issue.

Dimensions (millimeters/inches)

Incida diamatar



Incida diamatar

Wall thickness

inside diameter wall thickness		inside diameter			wali thickness						
	D (m	in.)	d (m	ax.)	W			D (min.)	d (max.)	W	
	Expa	nded	Rec	overed	Recovered			Expanded	Recovered	Recovered	
Size	as su	upplied	afte	r heating	after heatin	g**	Size	as supplied	after heating	after heatin	g**
3/64	1.2	0.046	0.6	0.023	0.25 ± 0.05	0.010 ± 0.002	1/2	12.7 <i>0.500</i>	6.4 0.250	0.33 ± 0.05	0.013 ± 0.002
1/16	1.6	0.063	0.8	0.031	0.25 ± 0.05	0.010 ± 0.002	3/4	19.1 <i>0.750</i>	9.5 <i>0.375</i>	0.43 ± 0.08	0.017 ± 0.003
3/32	2.4	0.093	1.2	0.046	0.25 ± 0.05	0.010 ± 0.002	1	25.4 1.000	12.7 0.500	0.48 ± 0.08	0.019 ± 0.003
1/8	3.2	0.125	1.6	0.062	0.25 ± 0.05	0.010 ± 0.002	1 1/2	38.1 <i>1.500</i>	19.1 <i>0.750</i>	0.51 ± 0.08	0.020 ± 0.003
3/16	4.7	0.187	2.4	0.093	0.25 ± 0.05	0.010 ± 0.002	2	50.8 <i>2.000</i>	25.4 1.000	0.51 ± 0.08	0.020 ± 0.003
1/4	6.4	0.250	3.2	0.125	0.33 ± 0.05	0.013 ± 0.002	3	76.2 3.000	38.1 <i>1.500</i>	0.64 ± 0.10	0.025 ± 0.004
3/8	9.5	0.375	4.7	0.187	0.33 ± 0.05	0.013 ± 0.002	4	101.6 <i>4.000</i>	50.8 <i>2.000</i>	0.76 ± 0.13	0.030 ± 0.005
**Wall thic	ckness wil	l be less if tub	ing recov	ery is restrict	ed during shrinka	ge.					

Ordering information

Colors	Standard	Translucent (clear)			
	Nonstandard	Black			
Size selection	Always order the largest size that will shrink snugly over the component being covered.				
Nonstandard sizes	Sizes of 2 inches and larger are by special order only. In addition, a variety of nonstandard sizes are available.				
Standard packaging	4-foot lengths				
Ordering description	Specify product name, size, and color; for example, RW-175 1/4-X (X=Clear).				

	n values Property	Unit	Requirement	Method of test
Physical	Dimensions	mm (inches)	See reverse	ASTM D 2671
,	Longitudinal change	percent	+0, –10 maximum	ASTM D 2671
	Tensile strength	psi (MPa)	5000 <i>(34.5)</i> minimum	ASTM D 2671
	Ultimate elongation	percent	150 minimum	ASTM D 2671
	Secant modulus (expanded)	psi (MPa)	1 x 10 ⁵ (690) minimum	ASTM D 2671
	Specific gravity	1 ()	1.8 maximum	ASTM D 2671
	Low-temperature flexibility (4 hours at -55°C/-67°F)		No cracking	AMS-DTL-23053/8
	Heat shock (4 hours at 300°C/572°F)		No dripping, flowing, or cracking	AMS-DTL-23053
	Heat resistance (168 hours at 250°C/482°F) Followed by test for:			ASTM D 2671
	Ultimate elongation	percent	50 minimum	ASTM D 2671
	Vacuum outgassing			ASTM E 595
	TML (total mass loss)	percent	1.0 maximum	
	VCM (volatile condensable material)	percent	0.1 maximum	
Electrical	Dielectric strength	volts/mil (kV/mm)		ASTM D 2671
	Sizes 3/64 through 1/2		800 (31.5) minimum	
	Sizes 3/4 through 2		600 (23.6) minimum	
	Volume resistivity	ohm-cm	10 ¹³ minimum	ASTM D 2671
Chemical	Copper mirror corrosion (16 hours at 175°C/347°F)		Noncorrosive	ASTM D 2671 Procedure A
	Copper contact corrosion (168 hours at 175°C/347°F)		No pitting or blackening of copper	ASTM D 2671 Procedure B
	Followed by test for:		100	107115 0171
	Ultimate elongation	percent	100 minimum	ASTM D 2671
	Flammability (average time of burning)	seconds	15 maximum	ASTM D 2671 Procedure A
	Fungus resistance			ISO 846 Method B
	Followed by tests for:	. (1.15.)		
	Tensile strength	psi (MPa)	5000 <i>(34.5)</i> minimum	ASTM D 2671
	Ultimate elongation	percent	150 minimum	ASTM D 2671
	Dielectric strength	volts/mil (kV/mm)	000 (01 505)	ASTM D 2671
	Sizes 3/64 through 1/2		800 <i>(31,500)</i> minimum	
	Sizes 3/4 through 2		600 <i>(23,600)</i> minimum	
	Water absorption	percent	0.5 maximum	ASTM D 2671
	(24 hours at 23°C/73°F)			107115 0771
	Fluid resistance (24 hours at 23°C/73°F) in: JP-8 fuel (MIL-T-5624) Skydrol 500 Hydraulic fluid (MIL-H-5606) Aviation gasoline 100/300 (MIL-G-5572) Salt water (5% salt) Anti-icing fluid (MIL-A-8243)			ASTM D 2671
	Lubricating oil (MIL-L-7808)			
	Followed by tests for:	volte/mil /kl//mml		∆CTN/ D 2471
	Dielectric strength	volts/mil (kV/mm)	700 (27.4) minimum	ASTM D 2671
	Sizes 3/4 through 1/2		700 <i>(27.6)</i> minimum	
	Sizes 3/4 through 2	noi (M/Do)	500 (19.7) minimum	ACTM D 2/71
	Tensile strength RW-3029/2 for specific details about test procedu	psi <i>(MPa)</i>	5000 <i>(34.5)</i> minimum	ASTM D 2671

Skydrol is a trademark of Monsanto Company. Raychem is a trademark of Tyco Electronics Corporation.

Users should independently evaluate the suitability of the product for their application.

Tyco Electronics Corporation 300 Constitution Drive

Menlo Park, CA 94025-1164 USA

Tel: (800) 926-2425 (US & Canada) Tel: +1 (650) 361-3860 (All other countries) Faraday Road Dorcan, Swindon, SN3 5HH United Kingdom Tel: +44 1793 528171 3816 Noborito, Tama-ku Kawasaki, Kanagawa 214-8533 Japan Tel: +81 44 900 5102 Asia Pacific Headquarters 26 Ang Mo Kio, Industrial Park 2 Singapore 569507 Tel: +65 4866 151

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics Corporation makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Tyco Electronics Corporation's only obligations are those in the Standard Terms and Conditions of Sale for these products and in no case will Tyco Electronics Corporation be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use, or misuse of the product. Tyco Electronics Corporation's Specifications are subject to change without notice. In addition, Tyco Electronics Corporation reserves the right to make changes in materials or processing without notification to the Buyer which do not affect compliance with any applicable specification.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Heat Shrink Tubing and Sleeves category:

Click to view products by TE Connectivity manufacturer:

Other Similar products are found below:

5685710001 CR9960-000 5734012004 607381P039 611112-000 6284592002 CX4711-000 CZ1420-000 D-306-38 770-006S302 770-020S705 MFP-3/64"-Clear 790-3012 MHHT-4-15K2-G-104 8003012003 MIL-LT-1-1/2-4-SP MIL-LT-1-1/2-9-STK MIL-LT-1/2-2-STK MIL-LT-3/0-SP MIL-LT-3/32-0-SP MIL-LT-3/32-6-SP MIL-LT-3/4-4-STK MIL-LT-3/4-6-SP 839602-000 8423-6 FP301-116-48"-Clear FP301-12-6"-Clear FP301-1/4-48"-White-Hdr FP301-18-48"-Black-Hdr FP301-1/8-6"-Black FP301-18-6"-Black-Bulk FP301-316-48"-Blue-Hdr 912229N002 R280637030 HDCW-5515-1000 HDT-0300-48A-BLACK HDT-0400-48A-Black HDT-0800-48A-RED HDT1100-48A-BLK HDT1500-48A-BLK HDT-2000-48A-Black RHW-70/20-1200/ADH-0 DWP-125-0.450-4-55MM-CS879 156082-000 MT5500-3/8-X-SP MT-FEP-045-032-008-X-60IN EPS200-1/4-48"-Black EPS200-1-48"-Black EPS200-3/16-48"-Black EPS200-38-48"-Black-Bulk