

QSW (Quick Shrink Wrap) Adhesive-Lined Polyolefin Wraparound Repair Sleeve




Table 1: Dimensions

Size	Substrate Diameter Range	Dimension P +1 mm (0.04 in.), - 0	Dimension R ± 6 mm (0.24 in.)
	mm (in.)		
QSW-60-100	10 (0.4) – 20 (0.8)	60 (2.4)	100 (4.0)
QSW-60-200	20 (0.8) – 50 (2.0)	60 (2.4)	200 (7.9)
QSW-60-300	40 (1.6) – 75 (3.0)	60 (2.4)	300 (11.8)
QSW-60-400	50 (2.0) – 100 (4.0)	60 (2.4)	400 (15.7)
QSW-100-100	10 (0.4) – 20 (0.8)	100 (4.0)	100 (4.0)
QSW-100-200	20 (0.8) – 50 (2.0)	100 (4.0)	200 (7.9)
QSW-100-300	40 (1.6) – 75 (3.0)	100 (4.0)	300 (11.8)

- Notes:**
1. Dimension **W** (wall thickness): 0.65 mm (0.025 in.) nominal
 2. Dimension **R** (length of sheet) shrinks approximately 10%

Material: QSW sleeves shall be fabricated from irradiated modified polyolefin compounded to produce a homogeneous, uniform product whose exterior surface is essentially free from flaws, defects, pinholes, seams, cracks or inclusions, and the color shall be black. The interior shall be coated with a hot melt thermoplastic adhesive.

OBSOLETE
NOT the LATEST REVISION

© 2007,2011 Tyco Electronics Corporation, a TE Connectivity Ltd. Company. All Rights Reserved. Customer Drawing

	TE Connectivity 305 Constitution Drive Menlo Park, CA 94025 USA		Raychem Tubing	Title: QSW (Quick Shrink Wrap) Adhesive-Lined Polyolefin Wraparound Repair Sleeve		
	TE Connectivity reserves the right to amend this drawing at any time. Users should evaluate the suitability of the product for their application.			Document No.: QSW		
Cage Code: 06090	Scale: None	Size: A	Rev. Date: 15-Apr-11	Rev: B1	Sheet: 1 of 2	

Table 2: Properties

Property	Unit	Requirement	Test Method
Tensile Strength	psi (MPa)	2466 (17) minimum	ASTM D412
Ultimate Elongation	percent	350 minimum	ASTM D412
Specific Gravity	- - -	1.05 maximum	ASTM D792
Hardness	shore D	40-50	ASTM D2240
Accelerated Aging 168 hrs @ 150 ± 2°C (302 ± 4°F) followed by tests for:			ASTM D2671
Tensile Strength	psi (MPa)	1740 (12) minimum	ASTM D412
Ultimate Elongation	percent	200 minimum	ASTM D412
Low Temperature Flexibility 4 hrs @ -40 ± 3°C (-40 ± 5°F)	---	No cracking	ASTM D2671 Procedure C
Dielectric Strength	V/mil (kV/cm)	500 (200) minimum	ASTM D2671
Volume Resistivity	ohm-cm	1 x 10 ¹² minimum	ASTM D2671
Water Absorption 168 hrs @ 23 ± 2°C (73 ± 4°F)	percent	0.2 maximum	ASTM D2671
Fluid Resistance 24 hours @ 23 ± 2°C (73 ± 4°F) in: Hydraulic Fluid (MIL-H-5606) JP-8 (MIL-T-5624) Lubricating Oil (MIL-L-7808) Lubricating Oil (MIL-L-23699) 5 percent NaCl (A-A-694) Deicing Fluid (MIL-A-8243) Skydrol 500			AMS-DTL-23053/5
Followed by tests for:			
Tensile Strength	psi (MPa)	1000 (6.9) minimum	ASTM D412
Dielectric Strength	V/mil (kV/mm)	400 (15.8) minimum	ASTM D2671
Weathering	The material from which QSW is manufactured contains carbon black to protect it from ultraviolet radiation.		

- Acceptance Tests:**
- 1. Dimensional** (1 piece per lot): Shall meet the specified dimensions.
 - 2. Visual** (20 pieces per lot): Both backing and adhesive surfaces shall be essentially free from flaws, defects, pinholes, seams or cracks, and must have clean cut edges.
 - 3. Application** (1 piece per lot): 15 minutes @ 175 ± 2°C; No slip page, bubbles or flaws.

Customer Drawing

Rev. Date: 15-Apr-11	Rev.: B1	Document No. QSW	Sheet: 2 of 2
-------------------------	-------------	---------------------	------------------

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [Heat Shrink Tubing and Sleeves](#) category:

Click to view products by [TE Connectivity](#) manufacturer:

Other Similar products are found below :

[770-006S102](#) [5685710001](#) [CR8248-000](#) [CR9960-000](#) [603312-4](#) [607381P039](#) [611112-000](#) [617867N001](#) [6500750004](#) [CZ1420-000](#) [D-306-38](#)
[770-003S106W2](#) [770-005S105W1](#) [770-005S106W1](#) [770-007A303](#) [770-010Y106W1](#) [770-010Y706W1](#) [7771210001](#) [MFP-1/4"-Clear](#) [MFP-3/64"-Clear](#) [790-3012](#) [MFT-MT2000-NO.14-0-SP](#) [MHHT-4-15K2-G-104](#) [MIL-LT-1-1/2-4-SP](#) [MIL-LT-1-1/2-9-STK](#) [MIL-LT-1/2-2-STK](#)
[MIL-LT-3-0-SP](#) [MIL-LT-3/32-0-SP](#) [MIL-LT-3/32-6-SP](#) [MIL-LT-3/4-6-SP](#) [MIL-LT-3/8-0-SP](#) [8159270001](#) [839602-000](#) [8423-6](#) [FP301-116-6"-Black](#) [FP301-1/2-48"-Black](#) [FP301-12-48"-Black-Hdr](#) [FP301-1/4-48"-Black](#) [FP301-1/4-48"-White-Hdr](#) [FP301-18-48"-Black-Hdr](#) [FP301-1/8-6"-Black](#) [FP301-18-6"-Black-Bulk](#) [FP301-316-48"-Blue-Hdr](#) [FP301-316-6"-Clear](#) [FP301-332-6"-Black](#) [912229N002](#) [120-126-16BL](#) [121-001-09](#) [121-018-32](#) [121-018-40](#)