

SCT

Adhesive-lined, semirigid, polyolefin heat-shrinkable tubing (extended temperature range)

SCT is a high-quality, dual-wall tubing designed to insulate and seal automotive wire splices and components made by ultrasonic welding, clip-and-dip, or soldering. Typical applications are insulating and sealing splices in an under-the-hood automotive environment.

SCT has a tough outer wall made of radiation crosslinked, flame-retardant, semirigid polyolefin. The inner wall is a unique, specially formulated hotmelt adhesive designed to function at an extended temperature range. The adhesive forms an outstanding barrier against moisture and automotive fluids.

This barrier provides exceptional protection against corrosion.

Because SCT has a high shrink ratio, only a few sizes are needed to cover a wide range of splice and component diameters.

0.060

1.52

Temperature rating


| Full recovery temperature: | 135°C |
|-----------------------------------|----------------|
| Continuous operating temperature: | -40°C to 150°C |

Specifications*

| Туре | Raychem |
|------|---------|
| SCT | SCT SCD |

^{*}When ordering, always specify latest issue.

Dimensions (millimeters/inches)



Recovered wall thickness**

0.100 ± 0.012

| moido | iliside diametei | | | | Necovered wall trickness | | | |
|----------|--|---|---|--|---|---|---|--|
| D (min.) | | d (max.) | | W | | W1 (min.) | | |
| Expan | ided as | Reco | vered after | Total | | Adhes | ive | |
| suppli | ed | heati | ng | wall | | wall | | |
| 5.1 | 0.200 | 1.3 | 0.050 | 1.4 ± 0.30 | 0.055 ± 0.012 | 0.76 | 0.030 | |
| 7.6 | 0.300 | 1.7 | 0.065 | 1.52 ± 0.30 | 0.060 ± 0.012 | 0.76 | 0.030 | |
| 9.0 | 0.355 | 2.3 | 0.090 | 1.52 ± 0.30 | 0.060 ± 0.012 | 0.76 | 0.030 | |
| 11.6 | 0.455 | 2.5 | 0.100 | 2.29 ± 0.30 | 0.090 ± 0.012 | 1.40 | 0.055 | |
| 17.8 | 0.700 | 4.4 | 0.175 | 2.54 ± 0.30 | 0.100 ± 0.012 | 1.52 | 0.060 | |
| | D (mir Expan suppli 5.1 7.6 9.0 11.6 | D (min.) Expanded as supplied 5.1 0.200 7.6 0.300 9.0 0.355 11.6 0.455 | D (min.) d (ma Expanded as Reco supplied heati 5.1 0.200 1.3 7.6 0.300 1.7 9.0 0.355 2.3 11.6 0.455 2.5 | D (min.) d (max.) Expanded as Recovered after supplied heating 5.1 0.200 1.3 0.050 7.6 0.300 1.7 0.065 9.0 0.355 2.3 0.090 11.6 0.455 2.5 0.100 | D (min.) d (max.) W Expanded as supplied Recovered after heating Total wall 5.1 0.200 1.3 0.050 1.4 ± 0.30 7.6 0.300 1.7 0.065 1.52 ± 0.30 9.0 0.355 2.3 0.090 1.52 ± 0.30 11.6 0.455 2.5 0.100 2.29 ± 0.30 | D (min.) d (max.) W Expanded as supplied Recovered after heating Total wall 5.1 0.200 1.3 0.050 1.4 ± 0.30 0.055 ± 0.012 7.6 0.300 1.7 0.065 1.52 ± 0.30 0.060 ± 0.012 9.0 0.355 2.3 0.090 1.52 ± 0.30 0.060 ± 0.012 11.6 0.455 2.5 0.100 2.29 ± 0.30 0.090 ± 0.012 | D (min.) d (max.) W W1 (m Expanded as supplied Recovered after heating Total wall Adhes 5.1 0.200 1.3 0.050 1.4 ± 0.30 0.055 ± 0.012 0.76 7.6 0.300 1.7 0.065 1.52 ± 0.30 0.060 ± 0.012 0.76 9.0 0.355 2.3 0.090 1.52 ± 0.30 0.060 ± 0.012 0.76 11.6 0.455 2.5 0.100 2.29 ± 0.30 0.090 ± 0.012 1.40 | D (min.) d (max.) W W1 (min.) Expanded as supplied Recovered after heating Total Adhesive wall 5.1 0.200 1.3 0.050 1.4 ± 0.30 0.055 ± 0.012 0.76 0.030 7.6 0.300 1.7 0.065 1.52 ± 0.30 0.060 ± 0.012 0.76 0.030 9.0 0.355 2.3 0.090 1.52 ± 0.30 0.060 ± 0.012 0.76 0.030 11.6 0.455 2.5 0.100 2.29 ± 0.30 0.090 ± 0.012 1.40 0.055 |

0.330

 2.54 ± 0.30

1.100

27.9

Inside diameter

Ordering information

SCT No. 5

| Color | Black |
|----------------------|---|
| Size selection | Always order the largest size that will shrink snugly over the component being covered. |
| Standard packaging | Cut pieces. See reverse for information on standard cut lengths. |
| Marking | Tubing will be marked with the number size (for example, SCT-0, SCT-1, SCT-2, SCT-3, SCT-4, SCT-5). |
| Ordering description | Specify product name, size, and color, and cut length; for example, SCT-No.2-0-50MM (0=Black). |

^{**}Wall thickness will be less if tubing recovery is restricted during shrinkage.

Specification values

| | Property | Unit | Requirement | Method of test |
|------------|-----------------------------------|-------------|--------------------------|----------------|
| Physical | Dimensions | mm (inches) | See reverse | ASTM D 2671 |
| | Longitudinal change | percent | +0, –10 | ASTM D 2671 |
| | Tensile strength | psi | 1500 minimum | ASTM D 2671 |
| | Ultimate elongation | percent | 300 minimum | ASTM D 2671 |
| | Secant modulus (as supplied) | psi | 35,000 minimum | ASTM D 2671 |
| | Concentricity (as supplied) | percent | 60 minimum | ASTM D 2671 |
| | Heat shock | | No cracking, dripping or | ASTM D 2671 |
| | (4 hours at 250°C/482°F) | | flowing of jacket | |
| Electrical | Dielectric strength (jacket only) | volts/mil | 500 minimum | ASTM D 149 |
| | Volume resistivity | ohm-cm | 10 ¹³ minimum | ASTM D 257 |
| | Immersion leak resistance | microamps | 0.25 maximum | See note below |
| | Thermal aging | | | See note below |
| | (1000 hours at 150°C/302°F) | | | |
| | Followed by test for: | | | |
| | Immersion leak resistance | microamps | 0.25 maximum | |
| | Thermal cycling | | | See note below |
| | 25 cycles | | | |
| | (-40°C to 135°C/-40°F to 225°F) | | | |
| | Followed by test for: | | | |
| | Immersion leak resistance | microamps | 0.25 maximum | |
| Chemical | Fluid resistance | | | See note below |
| | (24 hours at 25°C/77°F) in: | | | |
| | ASTM Reference Fuel C | | | |
| | VV-F-800 Diesel Fuel | | | |
| | (24 hours at 100°C/212°F) in: | | | |
| | ASTM #3 Oil | | | |
| | Followed by test for: | | | |
| | Immersion leak resistance | microamps | 0.25 maximum | |

Note: Consult Raychem SCT SCD for specific details about test procedures.

Standard cut lengths

| Part number | Standard cut length | Cut length tolerance | |
|-------------|-------------------------------------|----------------------|--|
| SCT No. 0 | 50 mm, 7 5 mm, 105 mm | ± 1.5 mm | |
| 00111010 | 1220 mm | ± 25.4 mm | |
| SCT No. 1 | 27 mm, 50 mm, 65 mm | ± 1.5 mm | |
| | 1220 mm | ± 25.4 mm | |
| SCT No. 2 | 27 mm, 50 mm, 65 mm | ± 1.5 mm | |
| | 1220 mm | ± 25.4 mm | |
| SCT No. 3 | 27 mm, 65 mm, 75 mm | ± 1.5 mm | |
| | 1220 mm | ± 25.4 mm | |
| SCT No. 4 | 27 mm, 75 mm, 90 mm | ± 1.5 mm | |
| | 1220 mm | ± 25.4 mm | |
| SCT No. 5 | 50 mm, 200 mm | ± 1.5 mm | |
| | 1220 mm | ± 25.4 mm | |

Users should independently evaluate the suitability of the product for their application.

te.com

 $\ensuremath{\text{@}}$ 2016 TE Connectivity Ltd. family of companies. All Rights Reserved.

SCT_DS APL 6/2016

 $TE\ Connectivity, TE, TE\ connectivity\ (logo)\ and\ RAYCHEM\ are\ trademarks\ of\ the\ TE\ Connectivity\ Ltd.\ family\ of\ companies.$

Other logos, product and/or company names might be trademarks of their respective owners.

While TE has made every reasonable effort to ensure the accuracy of the information in this document, TE does not guarantee that it is error-free, nor does TE make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. TE reserves the right to make any adjustments to the information contained herein at any time without notice. TE EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES REGARDING THE INFORMATION CONTAINED HEREIN, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. In ne event will TE be liable for any direct, incidental, special or consequential damages arising from or related to recipient's use of the information. It is the sole responsibility of the recipient of this information to verify the results of this information using their engineering and product environment. Recipient assumes any and all risks associated with the use of the information. The dimensions in this catalog are for reference purposes only and are subject to change without notice. All specifications are subject to change without notice. Consult TE for the latest dimensions and design specifications.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Heat Shrink Tubing and Sleeves category:

Click to view products by TE Connectivity manufacturer:

Other Similar products are found below:

770-006S102 5685710001 CR6145-000 CR8248-000 CR9960-000 603312-4 607381P039 611112-000 617867N001 6500750004 CZ1420-000 D-306-38 770-003S106W2 770-005S105W1 770-005S106W1 770-007A303 770-010Y106W1 770-010Y706W1 7771210001 MFP-1/4"-Clear MFP-3/64"-Clear 790-3012 MFT-MT2000-NO.14-0-SP MHHT-4-15K2-G-104 MIL-LT-1-1/2-4-SP MIL-LT-1-1/2-9-STK MIL-LT-1/2-2-STK MIL-LT-3/0-SP MIL-LT-3/32-0-SP MIL-LT-3/32-6-SP MIL-LT-3/4-6-SP MIL-LT-3/8-0-SP 8159270001 839602-000 8423-6 FP301-116-6"-Black FP301-1/2-48"-Black FP301-12-48"-Black-Hdr FP301-1/4-48"-Black FP301-1/4-48"-White-Hdr FP301-18-48"-Black-Hdr FP301-1/8-6"-Black FP301-18-6"-Black FP301-316-48"-Blue-Hdr FP301-316-6"-Clear FP301-332-6"-Black 912229N002 120-126-16BL 121-001-09 121-018-32