

ELASTOSIL[®] E43 TRANSPARENT



Moisture Curing Silicone Rubber (RTV-1)

ELASTOSIL[®] E43 TRANSPARENT is a self levelling, one-component acetoxy-cure silicone rubber which cures at room temperature under the influence of atmospheric moisture.

It shows excellent mechanical properties, has good adhesion properties to many substrates. In particular used as adhesive on cured silicone rubber

Properties

- moderately self-levelling
- excellent adhesion on cured silicone rubber
- high-tear grade
- good temperature resistance of permanently 180°C and peak temperatures of 200°C

Special features

- Excellent mechanical properties
- Good adhesion to metals, glass and ceramics
- High elongation
- High tear-resistant
- Ready to use
- Solvent-free

Technical data

Properties Uncured

Property	Condition	Value	Method
Skin formation time ⁽¹⁾	-	10 min	-
Viscosity, dynamic D = 0.5 1/s	25 °C	250000 mPa·s	ISO 3219
Viscosity, dynamic D = 25 1/s	25 °C	175000 mPa·s	ISO 3219
Density in water	20 °C	1.09 g/cm ³	DIN EN ISO 1183-1 / ISO 2781
Color	-	transparent	-
Curing time	23 °C 50 % r.h.	12 h/mm	-

¹at 23 °C / 50 % r.h.

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

curing conditions: 2 mm, 14 days storage at 23 °C and 50 % RH.

Property	Condition	Value	Method
Elongation at break	-	500 %	DIN 53504 S1 / ISO 37
Tensile strength	-	6.50 N/mm ²	DIN 53504 S1 / ISO 37
Hardness Shore A	-	30	DIN 53 505 / ISO 868
Density in water	23 °C	1.10 g/cm ³	DIN EN ISO 1183-1 / ISO 2781
Color	-	transparent	-
Tear strength	-	11.5 N/mm	ASTM D 624

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Appliances Industry
- Small Appliances
- Bonding, Fixing & Sealing
- Aerospace

- Appliances Industry
- Small Appliances
- Industrial Adhesives

Application details

Multipurpose sealant and adhesive for general industry and electronics for FIPG applications. Particularly suitable as adhesive on cured rubber or silicone coated textiles like seam sealing.

Processing

ELASTOSIL® E43 is a ready-to-use, one-part silicone rubber which starts curing when exposed to air moisture. Typical curing characteristics are given in the table "Properties Uncured".

As RTV-1 silicones require humidity for curing, free access of air moisture to the silicone rubber is essential. Additionally, the vulcanization time of ELASTOSIL® E43 can be greatly reduced by increasing the level of air's relative humidity. Please note that, unlike the initial skin formation, the total curing rate of RTV-1 silicones is limited by moisture's diffusion speed in silicone rubber.

As increasing the curing temperature has just a minor effect both on the skin forming time and the curing speed, ELASTOSIL® E43 typically is vulcanized at room temperature. Heat curing is recommended only for applications where the silicone rubber is applied as a thin film (thickness less than 0.5 mm), because otherwise blistering is likely to occur due to the quick release of acetic acid.

After completion of the vulcanization the silicone elastomer may continuously be exposed to constantly changing climatic conditions, UV radiation and high temperature without damage. Cured ELASTOSIL® E43 usually shows good primerless adhesion to many substrates, e.g. glass, ceramics, metals, plastics and powder coatings.

Removal: If removal of the silicone from machines or dispensing equipment is necessary, white spirit or similar nonpolar solvents are recommended. However, cleaning ideally should take place before the silicone rubber is fully vulcanized. Cured silicone needs to be rubbed off or removed mechanically, if necessary in combination with a swelling agent (solvent) or a chemical silicone remover ELASTOSIL E43 shows good primerless adhesion to many substrates. We recommend running preliminary tests to optimize conditions for the particular application.

Detailed information about the processing of RTV-1 silicones is given in our brochure "ROOM TEMPERATURE VULCANIZING (RTV) SILICONES - MATERIAL AND PROCESSING GUIDELINES".

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

During vulcanization of ELASTOSIL® E43 TRANSPARENT, a total of 4% by weight of acetic acid is split off. These vapours should not be inhaled for long periods or in high concentration. Work areas should therefore be well ventilated. Contact of unvulcanized silicone rubber with eyes and mucous membranes must be avoided as this would cause irritation. However if it does happen, rinse the affected area thoroughly with water.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code ELASTOSIL® E43 TRANSPARENT



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [Wacker manufacturer](#):

Other Similar products are found below :

[ELASTOSIL E43N 310ML 908-51362](#) [RT602 A+B 1KG](#) [RT6071KGA+B](#) [P12](#) [ELASTOSIL A33](#) [ELASTOSIL E4 908-51341](#) [ELASTOSIL N10 310ML](#) [ELASTOSIL E41 90ML 908-51331](#) [ELASTOSIL E43 310ML](#) [ELASTOSIL E43 908-51351](#)