

DATA SHEET

SURFACE-MOUNT CERAMIC MULTILAYER CAPACITORS

C-Array

NP0/X7R/Y5V

16 V TO 50 V

sizes 0508 (4 \times 0402) / 0612 (4 \times 0603) RoHS compliant & Halogen Free



YAGEO Phícomp



17

SCOPE

This specification describes NP0/X7R/Y5V 4-capacitor Array with lead-free terminations.

YAGEO Phicomp

APPLICATIONS

- · Professional electronics
- High density consumer electronics

FEATURES

- · Supplied in tape on reel
- Nickel-barrier end termination
- 0508 (4x0402) / 0612 (4x0603) capacitors (of the same capacitance value) per array
- Less than 50% board space of an equivalent discrete component
- High volumetric efficiency
- Increased throughout, by time saved in mounting
- RoHS compliant
- · Halogen Free compliant

ORDERING INFORMATION-GLOBAL PART NUMBER, PHYCOMP CTC & 12NC

All part numbers are identified by the series, size, tolerance, TC material, packing style, voltage, process code, termination and capacitance value. Please note that 12 digits ordering code will expire at the end of 2010.

YAGEO BRAND ordering code GLOBAL PART NUMBER (PREFERRED)

CA $\underline{xxxx} \underline{x} \underline{x} \underline{x} \underline{xxx} \underline{x} B \underline{x} \underline{xxx}$ (1) (2) (3) (4) (5) (6) (7)

(I) SIZE - INCH BASED (METRIC)

0508 (1220)

0612 (1632)

(2) TOLERANCE

 $J = \pm 5\%$

 $K = \pm 10\%$

 $M = \pm 20\%$

Z = -20% to +80%

(3) PACKING STYLE

R = Paper/PE taping reel; Reel 7 inch

P = Paper/PE taping reel; Reel 13 inch

(4) TC MATERIAL

NPO

X7R

Y5V

(5) RATED VOLTAGE

7 = 16 V

8 = 25 V

9 = 50 V

(6) PROCESS

N = NP0

B = class 2 material

(7) CAPACITANCE VALUE

2 significant digits+number of zeros

The 3rd digit signifies the multiplying factor, and letter R is decimal point

Example: $121 = 12 \times 10^{1} = 120 \text{ pF}$




CONSTRUCTION

YAGEO, Phicomp

The capacitor consists of a rectangular block of ceramic dielectric in which a number of interleaved metal electrodes are contained. This structure gives rise to a high capacitance per unit volume.

The inner electrodes are connected to the two end terminations and finally covered with a layer of plated tin (NiSn).


The terminations are lead-free. An outline of the structure is shown in Fig.I.



DIMENSIONS

Table I	0508	0612
	(4 X 0402)	(4 X 0603)
L (mm)	2.0 ±0.15	3.2 ±0.15
W (mm)	1.25 ±0.15	1.60 ±0.15
$T_{min.}$ (mm)	0.50	0.70
$T_{\text{max.}}$ (mm)	0.70	0.90
A (mm)	0.28 ±0.10	0.4 ±0.10
B (mm)	0.2 ±0.10	0.3 ±0.20
P (mm)	0.5 ±0.10	0.8 ±0.10

OUTLINES





NP0/X7R/Y5V

16 V to 50 V

CAPACITANCE RANGE & THICKNESS FOR 4C-ARRAY

Table 2	Temperature	characteristic	material from NP0	
---------	-------------	----------------	-------------------	--

CAPACITANCE	0508 (4 × 0402)	0612 (4 × 0603)	
	50 V	50 V	100V
10 pF			
15 pF			
18 pF			
22 pF			
33 pF			
39 pF			
47 pF			
56 pF	0.6±0.1		
68 pF			
82 pF		0.8±0.1	0.8±0.1
100 pF			
120 pF			
150 pF			
180 pF			
220 pF			
270 pF			
330 pF			
390 pF			
470 pF			
560 pF			
680 pF			
820 pF			
1.0 nF			

NOTE

Values in shaded cells indicate thickness class in mm



CAPACITANCE RANGE & THICKNESS FOR 4C-ARRAY

Table 3 Temperature characteristic material from X7R

YAGEO Phicomp

CAPACITANCE	0508 (4 x 0402)	Z Material Mont X7		0612 (4 × 0603)		
	16 V	25 V	50 V	16 V	25 V	50 V
180 pF						
220 pF						
270 pF						
330 pF						
390 pF						
470 pF						
560 pF						
680 pF						
820 pF _						
I.O nF			0.6±0.1			
I.2 nF						0.8±0.1
I.5 nF						0.8±0.1
1.8 nF						
2.2 nF						
2.7 nF					0.8±0.1	
3.3 nF		0.6±0.1				
3.9 nF				0.8±0.1		
4.7 nF						
5.6 nF						
6.8 nF						
8.2 nF	0.6±0.1					
I0 nF	0.0±0.1					
I2 nF						
15 nF						
18 nF						
22 nF						
27 nF						
33 nF						
47 nF						
56 nF						
68 nF						
82 nF						
100 nF						

NOTE

Values in shaded cells indicate thickness class in mm

Surface-Mount Ceramic Multilayer Capacitors 4C-Arroy

NP0/X7R/Y5V

16 V to 50 V

CAPACITANCE RANGE & THICKNESS FOR 4C-ARRAY

Table 4 Temperature characteristic material from Y5V

 $0612 (4 \times 0603)$ CAPACITANCE

25 V

17

10 nF	
22 nF	
47 nF	0.6±0
100 nF	

NOTE

Values in shaded cells indicate thickness class in mm

THICKNESS CLASSES AND PACKING QUANTITY

Table 5				
SIZE	THICKNESS	TAPE WIDTH QUANTITY	Ø180 MM / 7 INCH	Ø180 MM / 13 INCH
CODE	CLASSIFICATION	PER REEL	Paper	Paper
0508	0.6 ±0.1 mm	8 mm	4,000	20,000
0612	0.8 ±0.1 mm	8 mm	4,000	15,000





YAGEO Phicomp

Table 6

4C-ARRAY DIELECTRIC CAPACITORS; NISN TERMINATIONS


Unless otherwise stated all electrical values apply at an ambient temperature of 20±1 °C, an atmospheric pressure of 86 to 106 kPa, and a relative humidity of 63 to 67%.


	VALUE
	10 pF to 100 nF
NP0	50 V
X7R	0508: 16 V, 0612: 16 V to 50 V
Y5V	0612: 25 V
NP0	±5%, ±10%
X7R	±10%, ±20%
Y5V	-20% to +80%
NP0	≤ 0.1%
	16 ∨ ≤ 3.5%, 25∨ ≤ 2.5%, 50∨ ≤ 2.5%
X7R	12nF~100nF, Df ≤5%
Y5V	0508 ≤ 9%, 0612 ≤ 7%
	$R_{ins} \ge 10 \text{ G}\Omega \text{ or } R_{ins} \times C_r \ge 500 \text{ seconds whichever is less}$
е	
NP0	±30 ppm/°C
X7R	±15%
Y5V	+22% to -82%
NP0	-55 °C to +125 °C
X7R	–55 °C to +125 °C
Y5V	-30 °C to +85 °C
	X7R




NP0 0508/0612 50 V

YAGEO Phicomp












9/17

X7R 0508 16 V










17

X7R 0612 16 V to 50 V


YAGEO Phicomp









Y5V 0612 25 V







TESTS AND REQUIREMENTS

Table 7 Test procedures and requirements

TEST	TEST MET	HOD	PROCEDURE	REQUIREMENTS
Mounting	IEC 60384- 21/22	4.3	The capacitors may be mounted on printed-circuit boards or ceramic substrates	No visible damage
Visual Inspection and Dimension Check		4.4	Any applicable method using × 10 magnification	In accordance with specification
Capacitance		4.5.1	Class I: $f = 1 \text{ MHz for C} \le 1 \text{ nF, measuring at voltage 1 V}_{rms} \text{ at } 20 \text{ °C}$ $f = 1 \text{ KHz for C} > 1 \text{ nF, measuring at voltage 1 V}_{rms} \text{ at } 20 \text{ °C}$ Class 2: $f = 1 \text{ KHz for C} \le 10 \mu\text{F, measuring at voltage 1 V}_{rms} \text{ at } 20 \text{ °C}$ $f = 120 \text{ Hz for C} > 10 \mu\text{F, measuring at voltage 0.5 V}_{rms} \text{ at } 20 \text{ °C}$	Within specified tolerance
Dissipation Factor (D.F.)		4.5.2	Class I: $f = 1 \text{ MHz for C} \le 1 \text{ nF} \text{ , measuring at voltage I V}_{rms} \text{ at } 20 \text{ °C}$ $f = 1 \text{ KHz for C} > 1 \text{ nF, measuring at voltage I V}_{rms} \text{ at } 20 \text{ °C}$ Class 2: $f = 1 \text{ KHz for C} \le 10 \mu\text{F, measuring at voltage I V}_{rms} \text{ at } 20 \text{ °C}$ $f = 120 \text{ Hz for C} > 10 \mu\text{F, measuring at voltage } 0.5 \text{ V}_{rms} \text{ at } 20 \text{ °C}$	In accordance with specification
Insulation Resistance		4.5.3	At U _r (DC) for I minute	In accordance with specification



Surface-Mount Ceramic Multilayer Capacitors

NP0/X7R/Y5V

16 V to 50 V

REQUIREMENTS <General purpose series>

 Δ C/C: ± 30 ppm

X7R: Δ C/C: ±15% Y5V: Δ C/C: 22~-82%

<High Capacitance series>

 \times 7R/ \times 5R: Δ C/C: \pm 15% Y5V: Δ C/C: 22~-82%

Class I:

Class2:

Class2:

TEST **Temperature**

Coefficient

TEST METHOD

4.6

PROCEDURE

Capacitance shall be measured by the steps shown in the following table.

The capacitance change should be measured after 5 min at each specified temperature stage.

Step	Temperature(°C)	
a	25±2	
b	Lower temperature±3°C	
С	25±2	
d	Upper Temperature±2°C	
е	25±2	

(I) Class I

Temperature Coefficient shall be calculated from the formula as

Temp, Coefficient =
$$\frac{C2 - C1}{C1 \times \Delta T} \times 10^6 \text{ [ppm/°C]}$$

C1: Capacitance at step c

C2: Capacitance at 125°C

 ΔT : 100°C(=125°C-25°C)

(2) Class II

Capacitance Change shall be calculated from the formula as below

$$\Delta C = \frac{C2 - C1}{C1} \times 100\%$$

C1: Capacitance at step c

C2: Capacitance at step b or d

Adhesion

4.7 A force applied for 10 seconds to the line joining the terminations and in a plane parallel to the substrate

Force

size ≥ 0603: 5N

size = 0402: 2.5N

size = 0201: 1N



YAGEO Phicomp

16 V to 50 V

TEST	TEST METHOD		PROCEDURE	REQUIREMENTS	
Bond Strength of	IEC 60384- 21/22	4.8	Mounting in accordance with IEC 60384-22 paragraph 4.3	No visible damage	
Plating on End Face			Conditions: bending I mm at a rate of I mm/s, radius jig 340 mm	<pre><general purpose="" series=""> $\Delta C/C$ Class 1: NP0: within $\pm 1\%$ or 0.5 pF, whichever is greater Class2: $\times 5R/\times 7R/Y5V: \pm 10\%$ <high capacitance="" series=""> $\Delta C/C$ Class2:</high></general></pre>	
				X5R/X7R/Y5V: ±10%	
Resistance to Soldering Heat		4.9	keep for 24 ± 1 hours at room temperature Preheating for size ≤ 1206 : $120 ^{\circ}\text{C}$ to $150 ^{\circ}\text{C}$ for 1 minute Preheating for size ≥ 1206 : $100 ^{\circ}\text{C}$ to $120 ^{\circ}\text{C}$ for 1 minute and $170 ^{\circ}\text{C}$ to $200 ^{\circ}\text{C}$ for 1 minute Solder bath temperature: $260 \pm 5 ^{\circ}\text{C}$ Dipping time: 10 ± 0.5 seconds Recovery time: 24 ± 2 hours	Dissolution of the end face plating shall not exceed 25% of the length of the edge concerned	
				<pre><general purpose="" series=""> $\Delta C/C$ Class 1: NP0: within $\pm 0.5\%$ or 0.5 pF, whichever is greater Class2: $X5R/X7R: \pm 10\%$ $Y5V: \pm 20\%$</general></pre>	
				<high capacitance="" series=""></high>	
				ΔC/C Class2: X5R/X7R: ±10% Y5V: ±20%	
				D.F. within initial specified value	
				R _{ins} within initial specified value	
Solderability		4.10	Preheated the temperature of 80 °C to 140 °C and maintained for 30 seconds to 60 seconds.	The solder should cover over 95% of the critical area of each termination	
			Test conditions for lead containing solder alloy Temperature: 235 ± 5 °C Dipping time: 2 ± 0.2 seconds Depth of immersion: 10 mm Alloy Composition: $60/40 \text{ Sn/Pb}$		
			Number of immersions: I		
			Test conditions for leadfree containing solder alloy Temperature: 245 ± 5 °C Dipping time: 3 ± 0.3 seconds Depth of immersion: 10 mm Alloy Composition: SAC305 Number of immersions: 1 ± 0.3		



Surface-Mount Ceramic Multilayer Capacitors 4C-Array NP0/X7R/Y5V

16 V to 50 V

TEST	TEST METHOD		PROCEDURE	REQUIREMENTS
Rapid Change of	IEC 60384- 21/22	4.11	Preconditioning; I50 +0/–I0 °C for I hour, then keep for	No visual damage
Temperature			24 ±1 hours at room temperature	<general purpose="" series=""></general>
				ΔC/C
			5 cycles with following detail:	Class I:
			30 minutes at lower category temperature	NP0: within $\pm 1\%$ or 1 pF, whichever is greater
			30 minutes at upper category temperature	Class2:
			Recovery time 24 ±2 hours	X5R/X7R: ±15%
			Necovery time 21 ±2 nodrs	Y5V: ±20%
				<high capacitance="" series=""></high>
				ΔC/C
				Class2:
				X5R/X7R: ±15%
				Y5V: ±20%
			-	D.F. meet initial specified value
				R _{ins} meet initial specified value
				Tyns Theet initial specified value
Damp Heat with U _r Load		4.13	1. Preconditioning, class 2 only: 150 +0/-10 °C /1 hour, then keep for	No visual damage after recovery
			24 ±1 hour at room temp	<general purpose="" series=""></general>
			2. Initial measure:	ΔC/C
			Spec: refer initial spec C, D, IR	Class I:
			3. Damp heat test:	NP0: within $\pm 2\%$ or 1 pF, whichever is greater
			500 ± 12 hours at 40 ± 2 °C;	Class2:
			90 to 95% R.H. 1.0 U _r applied	X5R/X7R: ±15%; Y5V: ±30%
			4. Recovery:	D.F.
			Class 1: 6 to 24 hours	Class I: NP0: $\leq 2 \times \text{specified value}$
			Class 2: 24 ±2 hours	Class2:
			5. Final measure: C, D, IR	X5R/X7R: ≤ 16V: ≤ 7%
				≥ 25V: ≤ 5%
			P.S. If the capacitance value is less than the	Y5V: ≤ 15%
			minimum value permitted, then after the	R _{ins}
			other measurements have been made the	Class I:
			capacitor shall be precondition according to	NP0: \geq 2,500 M Ω or R _{ins} \times C _r \geq 25s whichever is less
			"IEC 60384 4.1" and then the requirement shall be met.	Class2:
			shan be met.	$X5R/X7R/Y5V$: $\geq 500 \text{ M}\Omega$ or $R_{\text{ins}} \times C_r \geq 25s$
				whichever is less
				<high capacitance="" series=""></high>
				ΔC/C
				Class2: X5R/X7R: ±20%; Y5V: ±30%
				D.F.
				Class2: 2 × initial value max
				R _{ins}
				Class2: 500 M Ω or R _{ins} x C _r \geq 25s, whichever is less

NP0/X7R/Y5V

4C-Array



Surface-Mount Ceramic Multilayer Capacitors

TEST TEST METHOD PROCEDURE REQUIREMENTS IEC 60384-**Endurance** No visual damage 1. Preconditioning, class 2 only: 21/22 150 +0/-10 °C /I hour, then keep for <General purpose series> 24 ±1 hour at room temp Δ C/C 2. Initial measure: Class I: Spec: refer initial spec C, D, IR NPO: within ±2% or 1 pF, whichever is greater 3. Endurance test: Temperature: NP0/X7R: 125 °C X5R/Y5V: 85 °C X5R/X7R: ±15%; Y5V: ±30% Specified stress voltage applied for 1,000 hours: D.F. Applied $2.0 \times U_r$ for general product. Class I: Applied 1.5 \times U_r for high cap. product. NP0: $\leq 2 \times$ specified value High voltage series follows with below stress Class2: condition: X5R/X7R: ≤ 16V: ≤ 7% Applied $1.3 \times U_r$ for 500V series ≥ 25V: ≤ 5% Applied 1.2 x U_r for 1 KV, 2 KV, 3 KV series Y5V: ≤ 15% 4. Recovery time: 24 ±2 hours R_{ins} 5. Final measure: C. D. IR Class I: NP0: $\geq 4.000 \text{ M}\Omega$ or P.S. If the capacitance value is less than the $R_{ins} \times C_r \ge 40s$ whichever is less minimum value permitted, then after the other Class2: measurements have been made the capacitor shall $X5R/X7R/Y5V: \ge 1,000 M\Omega$ or be precondition according to "IEC 60384 4.1" and $R_{ins} \times C_r \ge 50s$ whichever is less then the requirement shall be met. <High Capacitance series> Δ C/C Class 2: X5R/X7R: ±20%; Y5V: ±30% D.F. Class 2: 2 x initial value max R_{ins} Class 2: 1,000 M Ω or R_{ins} x C_r \geq 50s, whichever is less



Specified stress voltage applied for I minute $U_r \le 100 \text{ V}$: series applied 2.5 U_r $100 \text{ V} < U_r \le 200 \text{ V}$ series applied (1.5 $U_r + 100$) 200 V < U_r ≤ 500 V series applied (1.3 U_r + 100) $U_r > 500 \text{ V}: 1.3 U_r$ I: 7.5 mA

No breakdown or flashover



REVISION HISTORY

YAGEO Phicomp

REVISION	DATE	CHANGE NOTIFICATION	DESCRIPTION
Version 3	May 21, 2014	-	- Product range updated
Version 2	Jun. 17, 2013	-	- Product range updated
Version I	Feb 05, 2010	-	- The statement of "Halogen Free" on the cover added
Version 0	Jun 22, 2009	-	- New datasheet for 4C-Array series with RoHS compliant
			- Replace from pdf files: 0508_16V to 50V_1, 0612_16V to 50V_0,
			C-Array_NP0_50V_0508_7, C-Array_NP0_50V_0612_7,
			C-Array_X7R_16V_25V_50V_0612_6, C-Array_X7R_16V_0508_5,
			C-Array_Y5V_25V_0508_0, C-Array_Y5V_25V_0612_5
			- Define global part number
			- Description of "Halogen Free compliant" added
			- Test method and procedure updated



X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Capacitor Arrays & Networks category:

Click to view products by Yageo manufacturer:

Other Similar products are found below:

20109D1X102K5P CKCA43C0G1H150K CKCA43X7R1H222M CKCL22C0G1H101K CKCL22C0G1H150K CKCL22C0G1H680K
CKCL22X5R0J105M CKCL22X5R1A474M CKCL22X7R1H103M CKCL44C0G1H151K CKCL44X7R1C223M CKCM25C0G1H470K
CKCM25C0G1H680K CKCM25X5R0J474M CKCM25X5R1C223M CKCM25X7R1H222M W2L16C473MAT1S W2L16C683MAT1A
CKCM25X5R1A473M CKCM25X7R1H472M CKCM25X5R0J105M CKCL44X5R1A473M CKCL22X7R1H223M CKCL22X7R1H102M
CKCL22X5R1C224M CKCL22C0G1H470K CKCL22C0G1H221K CKCL22C0G1H151K NCA0805NPO220K50TRPF
W2L16C474MAT1A W2L14Z225MAT1A NCA1206X7R103M50TRPF 2255-126-15636 W2L1YC104MAT1F CA064X102K1RACTU
CA064X102K3RACTU CA064X102K4RACTU CA064X150J5GACTU CA064X151J5GACTU CA064X181J5GACTU
CA064X331J5GACTU CA064X391J5GACTU NCA0805NPO470K50TRPF NCA1206X7R103K16TRPF CA0508KRNPO9BN101
CA0508KRNPO9BN470 CA0612JRNPO9BN221 CA0612KRNPO9BN151 CA0612KRX7R9BB103 CA064C103M5RACTU